Historic, archived document

Do not assume content reflects current scientific knowledge, policies, or practices.

Ponderosa Pine

Forest Service

U. S. DEPARTMENT OF AGRICULTURE

PONDEROSA PINE

(*Pinus ponderosa*)

By H. S. BETTS, senior engineer, Division of Forest Products

Ponderosa pine is one of the most widely distributed and important of the western timber trees. It is a hardy species and grows under a wide range of conditions in the Pacific and Rocky Mountain regions from southern British Columbia to Mexico, and has a total stand greater than that of any other species in North America except Douglas-fir. Ponderosa pine is practically the only timber tree in extensive regions of the Southwest, where its value in maintaining forests and as a source of lumber, fuel, etc., can scarcely be overestimated. Ponderosa pine lumber, especially the higher-grade material, is shipped throughout the United States, and is bound to continue to hold a very important place in the markets of the East as well as of the West. Under favorable conditions mature trees from 350 to 500 years old occasionally reach a height of 200 feet and a diameter of 6 feet.¹ The wood varies widely in quality. Lumber cut from the outer portions of the larger trees is frequently soft and quite uniform in texture, while that cut from the inner portions or from small trees may be knotty and resinous with sharply marked annual rings, and is sometimes comparatively hard. The high-grade lumber is used principally for doors, sash, frames, paneling, mouldings, siding, etc., and the lower grade material for boxes, sheathing, joists, rafters, and railroad ties. Experiments in "tapping" ponderosa pine in Arizona and California gave yields of turpentine and rosin not much below those obtained from longleaf pine and slash pine which are the source of the naval stores (turpentine and rosin) produced in the United States.

Nomenclature.—The name ponderosa pine is now commonly used in place of a variety of names formerly applied to the species with resultant confusion and misunderstanding. Among the former names for ponderosa pine, some of which are still in limited use, are western pine, western yellow pine, pondosa pine, western soft pine, western white pine, California white pine, yellow pine, Oregon white pine, bull pine, and black jack. Jeffrey pine (*Pinus jeffreyi*), an associate of ponderosa pine in the forests of California and Oregon, is usually marketed in mixture with ponderosa pine and sold under that name.²

Distribution and growth.—Ponderosa pine grows in every State west of the Great Plains (fig. 1) and also in British Columbia and northern Mexico. It is found on a wide variety of soils, sites, and elevations and occurs both in pure stands and in mixture with other species. The tree has a deep-reaching taproot and long and strong

¹ The largest trees occur in California, and reach a maximum of 230 feet in height and 10 feet in diameter.

² Jeffrey pine was formerly considered to be a variety of ponderosa pine.

laterals and can resist drought better than its associates. On moist sites, however, it is replaced by other species better adapted to such conditions. Excellent stands of ponderosa pine occur where the annual rainfall is only 18 inches. Where the precipitation drops but a little below 15 inches the forest gives way to sagebrush. Ponderosa pine shows a preference for sunny climates and warm situations but can endure severe winters. Stands are nearly always rather open because the tree is intolerant of shade in the drier locations, because of the

FIGURE 1.—Range of ponderosa pine (*Pinus ponderosa*).

competition of far-reaching roots for soil moisture. Mature trees in the Northwest under favorable conditions of growth generally reach a height of 125 to 140 feet and a diameter of 3 to 4 feet. In typical ponderosa pine forests in Oregon the average growth is as follows: 50 years—height 24 feet, diameter 4.7 inches; 100 years—height 62 feet, diameter 13.2 inches; 200 years—height 104 feet, diameter 23.4 inches. In California, on the west slope of the Sierra Nevada the diameter of ponderosa pine is generally somewhat greater than in Oregon, and the height growth is considerably greater. Ponderosa pine growing in

California on the east slope of the Sierra Nevada reaches about the same size as Oregon timber. In Arizona and New Mexico both the diameter and height growth are less than in Oregon—the height growth considerably so. Ponderosa pine produces seed fairly abundantly after reaching middle age. Good seed years occur about every 3 years. A considerable proportion of the seed crop is eaten by squirrels and other animals. The seed germinate freely but their mortality is high.

The most destructive enemy of ponderosa pine is fire. It kills reproduction, impoverishes the soil, and causes scars on the butts of merchantable trees which lower the grade of lumber cut from butt logs and provide a ready entrance for decay in the standing tree. Next to fire comes damage from insects, which is widespread. Bark beetles³ and a defoliator known as the “pine butterfly”⁴ are the most destructive. Mistletoe is another enemy of the tree. Severe damage to reproduction is often caused by sheep.

Supply.—Recent estimates place the total stand of ponderosa pine of saw-timber size at 218,245,000 board feet distributed as follows:

	Lumber tally (million board feet)
Oregon:	
Eastern part.....	¹ 71, 978
Western part.....	² 5, 228
	77, 206
California (inc. Nevada).....	³ 49, 740
Idaho.....	³ 21, 400
Washington:	
Eastern part.....	⁴ 19, 325
Western part.....	² 109
	³ 19, 434
Arizona.....	³ 17, 940
New Mexico.....	³ 10, 060
Montana.....	³ 9, 760
Colorado.....	³ 5, 190
South Dakota.....	³ 3, 090
Wyoming.....	² 2, 310
Utah.....	³ 2, 080
Plains Region.....	³ 35
Total.....	⁵ 218, 245

¹ See COWLIN, R. W., BRIEGLER, P. A., AND MORAVETS, F. L. FOREST RESOURCES OF THE PONDEROSA PINE REGION OF WASHINGTON AND OREGON. U. S. Dept. Agr. Misc. Pub. 490, 99 pp., illus. 1942.

² See ANDREWS, H. J. and COWLIN, R. W. FOREST RESOURCES OF THE DOUGLAS-FIR REGION. U. S. Dept. Agr. Misc. Pub. 389, 169 pp., illus. 1940.

³ This is an estimate based on such information as is available from various sources. It is, of course, subject to change when more definite data become available from a forest survey of the United States now under way.

⁴ See U. S. Dept. Agr. Misc. Pub. 490 (footnote 1). Also U. S. FOREST SERVICE, NORTHERN ROCKY MOUNTAIN FOREST AND RANGE EXPERIMENT STATION. FOREST STATISTICS, PEND OREILLE COUNTY, WASHINGTON. Forest Survey Release 2, 24 pp., illus. 1937. [Processed.]; FOREST STATISTICS, SPOKANE COUNTY, WASHINGTON. Forest Survey Release 4, 24 pp., illus. 1937. [Processed.]; and FOREST STATISTICS, STEVENS COUNTY, WASHINGTON. Forest Survey Release 5, 24 pp., illus. 1937. [Processed.]

⁵ See UNITED STATES CONGRESS, JOINT COMMITTEE ON FORESTRY. FOREST LANDS OF THE UNITED STATES. 77th Cong., 1st sess., Senate Doc. 32, 44 pp. 1941.

Oregon contains approximately one-third of the stand of ponderosa pine saw timber and California approximately one-quarter. About 94 percent of the stand of ponderosa pine in Oregon and Washington is

³ *Dendroctonus brevicornis* and *Dendroctonus monticolae*.

⁴ *Neophasia menapia*.

located east of the summit of the Cascade Range. Similarly in California the larger part of the ponderosa pine timber is on the east slope of the Sierra.

Production.—In 1869⁵ the production of ponderosa pine lumber amounted to 285,000,000 board feet. (See fig. 2.) Forty years later, in 1909—the year in which the lumber cut of the United States reached its maximum—the production of ponderosa pine had increased to 1,500,000,000 feet. By 1920 it had risen to 2,290,000,000 feet and by 1929 to 3,288,000,000 feet. After that production fell off owing to the depression in business, and in 1932 dropped as low as 1,288,000,000 feet. By 1941 it had recovered to 4,250,000,000 feet—the maximum annual production so far attained. This cut came from 12 States. Production in 1942 was 4,030,000,000 board feet. California was the leading State in the production of ponderosa pine lumber up to 1924.⁶ In that year Oregon took first place and has held it ever since, with California second, and Washington⁷ third. The 1943 production was 3,871,855,000 board feet.

The average annual production of ponderosa pine lumber for the 10-year period 1933–42 was 3,029,000,000 board feet. About 43 percent of this average annual cut came from Oregon, about 25 percent from California, about 11 percent from Washington, and about 6 percent from Idaho. Montana, Arizona, and New Mexico each furnished from 3 to 4 percent of the total. Since 1922 ponderosa pine has ranked third in amount of lumber produced, being exceeded only by Douglas-fir and southern yellow pine.

In addition to the lumber produced from ponderosa pine, considerable amounts are cut locally throughout its range for fuel and fence posts. Smaller amounts are used for piling, poles, hewed ties,⁸ mine timbers, etc. The average annual cut of ponderosa pine for all purposes in recent years is estimated at approximately 3,250,000,000 board feet.

Properties.—The wood of ponderosa pine varies considerably in appearance and properties. Botanically, ponderosa pine belongs to the yellow pine group rather than to the white pine group. A considerable proportion of the wood, however, approaches the white pines⁹ in appearance and properties rather than the yellow pines. The heartwood is light reddish brown and the wide sapwood nearly white to pale yellow. The annual growth rings are generally distinct and moderately wide in the heartwood of mature trees and less distinct and comparatively narrow in the sapwood. They are made up of a light-colored band of springwood and a darker band of summerwood. The transition from springwood to summerwood is generally abrupt.

The wood in the outer portions of ponderosa pine of saw-timber size is in general moderately light in weight,¹⁰ moderately weak, not stiff, moderately soft, and moderately low in shock resistance. It is generally straight-grained, has a moderately small shrinkage, is quite

⁵ The earliest year for which production figures for ponderosa pine lumber are available.

⁶ Except in 1918, 1919, and 1920, when Oregon was first.

⁷ Except in 1924, when Idaho was third.

⁸ Sawed ties, which comprise approximately 90 percent of all ponderosa pine ties, are included in the records of lumber production obtained from sawmills and are classed as lumber.

⁹ The commercial white pines are Eastern white pine (*Pinus strobus*), Western white pine (*Pinus monticola*), and sugar pine (*Pinus lambertiana*).

¹⁰ The average weight of ponderosa pine when thoroughly air dry (12 percent moisture) is 28 pounds per cubic foot.

uniform in texture, has little tendency to warp and twist, can be easily glued, and is slightly resinous. The wood in young trees and in the heartwood of older trees is sometimes heavier, harder, and stronger than that in the outer portions of older trees and is generally more resinous and contains more knots and other defects.

The regions of maximum growth for ponderosa pine (and for some other pines) may produce less valuable timber than regions where the growth is comparatively slow. For example, the wood of ponderosa pine grown on the east side of the Sierra Nevada, where there is little rain, is comparatively soft and uniform in texture and of slow growth, while the wood grown on the west side of the mountains, where the rainfall is greater and the growth faster, is harder, less uniform in texture, and more resinous.

In ability to hold paint, ponderosa pine is rated below the three commercial white pines and above southern pine and Douglas-fir. It

FIGURE 2.—Lumber production of ponderosa pine (*Pinus ponderosa*), 1869-1942.

does not split easily in nailing but is low in ability to hold nails. In decay resistance ponderosa pine is rated below the white pines. The heartwood as well as the sapwood can be easily treated with preservatives.

The wood of ponderosa pine can be readily reduced to paper pulp by the sulfate process to yield a pulp with very strong, long fibers and good felting qualities suitable for the manufacture of high-grade wrapping papers and fiberboard. When the wood is reduced by the sulfite process or by the mechanical process the results are much less satisfactory. Ponderosa pine is not used for paper pulp (1943) because of the abundance of other western woods suitable for paper pulp and located more favorably with respect to markets and the ample water supplies needed in paper-making operations.

Principal uses.—Ponderosa pine is used principally for lumber and to a less extent for piling, poles, posts, mine timbers, veneer, and

hewed ties. It is widely used for fuel, especially the low-grade material. The lumber has a variety of uses ranging from high-grade millwork and cabinet work to rough construction. The clearer, softer wood goes largely into sash, doors, blinds, mouldings, paneling, mantels, trim, and built-in cases and cabinets. Lower grade lumber is much used for boxes and crates. The wood is well fitted for boxes on account of its moderate weight, light color, and ease in working and nailing. On the Pacific coast it competes with sugar pine and Western white pine as a fruit-box material, and large quantities of apples, peaches, citrus fruit, raisins, prunes, cherries, etc., from the far west and the Rocky Mountain region are shipped in ponderosa pine boxes. A considerable proportion of the lumber of intermediate or low grade goes into sheathing, subflooring, roof boards, floor joists, studs, and rafters. Knotty ponderosa pine paneling for interior finish has recently come into wide use. Other uses of ponderosa pine lumber include caskets and coffins, furniture, toys, fixtures, shade and map rollers, and laundry appliances.

The following tabulation shows the amounts of ponderosa pine used in the manufacture of wooden products in 1912, 1928, 1933, and 1940. The material was largely in the form of lumber with much smaller amounts of veneer, and short logs and bolts.

TABLE 1.—*Ponderosa pine used in the manufacture of wooden products*

[Thousands of board feet]

Product	1912	1928	1933	1940
Airplanes		3		24
Agricultural implements	219	733	5	1,134
Boot and shoe findings				124
Boxes, baskets and crating	288,292	1,005,527	1,742,069	1,115,216
Boxes, cigar and tobacco		240	11	15
Car construction and repair	4,242	14,766	1,865	1,361
Caskets and burial boxes	544	13,353	17,998	40,841
Conduits, pumps, and wood pipe		500		16
Dairy, poultry and apiary supplies	(2)	3,165	2,938	3,573
Dowels and skewers	390			
Electrical equipment		12,104		1,061
Fixtures	962	3,502	2,123	9,525
Flooring	(4)	(4)	339	6,782
Furniture	1,837	4,386	5,961	36,620
Handles	7	310	21	68
Instruments, musical		474	134	213
Instruments, professional and scientific	8	90	1,006	1,443
Ladders	(2)	(2)		2,587
Laundry appliances	5	4,259	3,799	7,508
Machinery	17	62	34	60
Patterns and flasks	136	4,029	1,127	2,250
Pencils and penholders	(3)			
Playground equipment		30	3	51
Printing material		20		1
Radio and phonograph cabinets	(1)	(6)	43	1,168
Refrigerators	750	7,059	21	2,524
Rollers, shade and map		457	4,830	8,016
Sash, doors, and general millwork	8264,954	81,021,395	9235,649	9854,002
Ship and boat building	519	544	944	905
Shuttles, spools, bobbins, and looms	(10)	(10)	(10)	543
Signs, scenery, and displays	1,000	3,971	882	3,672
Sporting and athletic goods			77	86
Surgical supplies				5
Tanks	127	200	82	22
Toys		1,760	2,694	15,500
Trunks and valises	361	2,731	941	5,191
Vehicles, motor	(11)	3,396	151	3,070

See footnotes at end of table.

TABLE 1.—*Ponderosa pine used in the manufacture of wooden products—Con.*

Product	1912	1928	1933	1940
Vehicles, nonmotor.....	182	178	48	129
Venetian blinds.....	(⁹)	(⁹)	(⁹)	5,720
Woodenware and novelties.....	265	100	1,391	3,688
Total.....	563,817	2,109,344	1,030,186	2,134,709

¹ These figures for 1933 and 1940 include ponderosa pine used for boxes and crates by plants not classified as manufacturers of wooden products and not included in 1912 and 1928. The amounts included for non-manufacturers of wooden products were as follows: For 1933, 46,371,000 board feet; and for 1940, 223,075,000 board feet.

² Included with Woodenware and novelties.

³ Dowels only, skewers included in butchers' blocks.

⁴ Included with sash, doors, and general millwork.

⁵ Included with Instruments, professional and scientific.

⁶ Included with Furniture.

⁷ Includes kitchen cabinets.

⁸ Includes planing-mill products such as flooring, siding, and ceiling.

⁹ Planing-mill products, which were included in 1912 and 1928 canvases, were not included in 1933 and 1940 except flooring which is listed separately.

¹⁰ Does not include looms.

¹¹ Included with Vehicles, nonmotor.

REFERENCES

- FOREST LANDS OF THE UNITED STATES. UNITED STATES CONGRESS, JOINT COMMITTEE ON FORESTRY. 77th Cong., 1st sess., Senate Doc. 32, 44 pp. 1941.
- FOREST RESOURCES OF THE DOUGLAS-FIR REGION. H. J. ANDREWS and R. W. COWLIN. U. S. Dept. Agr. Misc. Pub. 389, 169 pp., illus. 1940.
- FOREST RESOURCES OF THE PONDEROSA PINE REGION OF WASHINGTON AND OREGON. R. W. COWLIN, P. A. BRIEGLEB, and F. L. MORAVETS. U. S. Dept. Agr. Misc. Pub. 490, 99 pp., illus. 1942.
- GROWTH IN SELECTIVELY CUT PONDEROSA PINE FORESTS OF THE PACIFIC NORTHWEST. W. H. MEYER. U. S. Dept. Agr. Tech. Bul. 407, 64 pp., illus. 1934.
- LUMBER USED IN MANUFACTURE—1928, 1933, AND 1940. (Summary Tables.) U. S. Forest Service, Preliminary Statistics—Forest Survey of the United States.
- LUMBER USED IN THE MANUFACTURE OF WOODEN PRODUCTS. J. C. NELLIS. U. S. Dept. Agr. Bul. 605, 18 pp., illus. 1918.
- NATURAL REPRODUCTION OF WESTERN YELLOW PINE IN THE SOUTHWEST. G. A. PEARSON. U. S. Dept. Agr. Bul. 1105, 144 pp., illus. 1923.
- PONDEROSA PINE, THE PICK OF THE PINES: ITS PROPERTIES, USES, AND GRADES. Western Pine Assoc. 80 pp., illus. 1931.
- POSSIBILITIES OF WESTERN PINES AS A SOURCE OF NAVAL STORES. H. S. BETTS. U. S. Forest Serv. Bul. 116, 23 pp., illus. 1912.
- TIMBER GROWING AND LOGGING PRACTICE IN THE CALIFORNIA PINE REGION. S. B. SHOW and W. B. GREELEY. U. S. Dept. Agr. Bul. 1402, 76 pp., illus. 1926.
- TIMBER GROWING AND LOGGING PRACTICE IN PONDEROSA PINE IN THE NORTHWEST. R. H. WIEDMAN. U. S. Dept. Agr. Tech. Bul. 511, 92 pp., illus. 1936.
- TIMBER GROWING AND LOGGING PRACTICE IN THE SOUTHWEST AND IN THE BLACK HILLS REGION. U. S. Dept. Agr. Tech. Bul. 480, 80 pp., illus. 1935.
- WESTERN YELLOW PINE IN ARIZONA AND NEW MEXICO. T. S. WOOLSEY. U. S. Forest Serv. Bul. 101, 64 pp., illus. 1911.
- WESTERN YELLOW PINE IN OREGON. T. T. MUNGER. U. S. Dept. Agr. Bul. 418, 48 pp., illus. 1917.
- YIELD OF EVEN-AGED STANDS OF PONDEROSA PINE. W. H. MEYER. U. S. Dept. Agr. Tech. Bul. 630, 60 pp., illus. 1938.