Historic, archived document

Do not assume content reflects current scientific knowledge, policies, or practices.

UNITED STATES DEPARTMENT OF AGRICULTURE

DEPARTMENT BULLETIN No. 1485

Washington, D. C.

May, 1927

THE SUITABILITY OF AMERICAN WOODS FOR PAPER PULP

By

SIDNEY D. WELLS, Engineer in Forest Products
and

JOHN D. RUE, In Charge of Section of Pulp and Paper
Forests Products Laboratory, Forest Service

CONTENTS

	Page
Introduction	1
Standard Pulping Methods	5
Experimental Procedure	11
Pulping Characteristics of Groups of Woods	17
Suitability of Individual Species for Pulping	21
Tables of Cooking and Strength Data	65

UNITED STATES DEPARTMENT OF AGRICULTURE

DEPARTMENT BULLETIN No. 1485

Washington, D. C.

May, 1927

THE SUITABILITY OF AMERICAN WOODS FOR PAPER PULP¹

By SIDNEY D. WELLS, *Engineer in Forest Products*, and JOHN D. RUE, *in charge of Section of Pulp and Paper, Forest Products Laboratory, Forest Service*

CONTENTS

	Page		Page
Introduction.....	1	Suitability of individual species for pulping.....	21
Scope and objects of the investigation.....	1	Estimation of pulping value.....	21
The pulp wood situation.....	2	Application of data to operating condi-	
Standard pulping methods.....	5	tions.....	23
Mechanical process.....	5	Summaries by species.....	25
Chemical processes.....	7	1. Spruces.....	25
Experimental procedure.....	11	2. Pines.....	29
Equipment.....	11	3. Firs.....	38
Conduct of tests.....	11	4. Hemlocks and other conifers.....	42
Species investigated.....	16	5. Hardwoods—diffuse porous.....	47
Pulping characteristics of groups of woods.....	17	6. Hardwoods—ring porous.....	57
Softwoods.....	17	7. Miscellaneous species.....	62
Hardwoods.....	20	8. Chilean woods.....	64
Bark disposal.....	21	Tables of cooking and strength data.....	65

INTRODUCTION

SCOPE AND OBJECTS OF THE INVESTIGATION

In 1906 the Forest Service commenced, at its pulp and paper laboratory, then located in South Boston, Mass., a study of the pulping characteristics of American woods for the manufacture of paper pulp. Since that time the work has been continued as one of the major research projects of the service. This bulletin is a report of what may be termed the general or "extensive" phase of the investigation, covering all available species which seemed to offer possibilities.

Most of the 94 species studied have been tested by the soda, sulphate, and sulphite processes. Twenty-two have also been tested by the mechanical process in the commercial sized experimental unit operated at Wausau, Wis., from 1911 to 1914, and

¹ The investigation herein reported was started by the Forest Service in 1906-07 under the supervision of H. S. Bristol, at South Boston, Mass. In 1907 the work was transferred to Washington, D. C., where Edwin Sutermeister was in charge, and since 1910 has been carried on at the Forest Products Laboratory, Madison, Wis. The following have been successively in charge of the section of pulp and paper at the laboratory: H. E. Surface, O. L. E. Weber, Otto Kress, and John D. Rue. Pulping experiments have been supervised by: Mechanical process, J. H. Thickens and G. C. McNaughton; soda and sulphate processes, R. E. Cooper and Sidney D. Wells; sulphite process, R. E. Cooper, C. S. Gwynne, S. E. Lunak, V. P. Edwards, and R. N. Miller. Throughout the investigation the beater and paper-machine runs have been superintended by J. J. Laing.

reported upon in Department of Agriculture Bulletin No. 343, "Ground-Wood Pulp," by J. H. Thickers and G. C. McNaughton. A small compilation of the chemical pulping experiments up to 1912, by H. E. Surface, was published as an unnumbered Forest Service bulletin entitled "Paper pulps from Various Woods." Since 1912 articles on the subject have appeared from time to time in trade and technical journals, but this bulletin is the first attempt to present a report of the survey as a whole.

The work had two objects: (1) To determine the suitability for paper manufacture of species growing on the national forests, so that the Forest Service might be able to guide timber sales efforts intelligently; and (2) to ascertain the relative merits of species not in common use but available to established pulp mills, so that suitable species might be found to supplement the waning supplies of spruce. The results of the investigation of western species have already been used in consummating national forest timber sales have influenced the establishment not only of pulp mills dependent on national forest timber but also of mills dependent on private holdings. The severe shortage of materials experienced by the paper industry in 1919 emphasized the importance of supplementing the supplies of spruce, and it may be profitable to survey briefly conditions as they are now in order to bring out more clearly the possible application of this part of the experimental work.

THE PULP WOOD SITUATION

According to the latest available statistics, one group of conifers, the spruces, supply 55 per cent, and three groups, the spruces, firs, and hemlocks, supply 77 per cent of the wood consumed by the pulp industry of the United States. Table 1 shows the proportion of the material that principal pulp woods supply for each pulping process.

TABLE 1.—*Pulp wood consumption, by species and processes of manufacture, for the United States, 1922*¹

Species pulped	Mechanical process		Sulphite process		Soda process		Sulphate process		Totals by species	
	Cords	Per cent	Cords	Per cent	Cords	Per cent	Cords	Per cent	Cords	Per cent
Spruces.....	1,303,169	87.3	1,650,660	59.7	1,121	.1	77,940	15.5	3,032,890	54.7
Firs.....	89,537	6.0	224,415	8.1			39,378	7.8	353,330	6.4
Hemlocks.....	65,776	4.4	795,980	28.8	3,671	.5	27,768	5.5	893,195	16.1
Poplars.....	8,115	.5	2,135	.1	311,488	39.6	16,193	3.2	337,931	3.1
Yellow poplar.....					102,200	13.0			102,200	1.8
Gums.....					52,058	6.6			52,058	.9
Pines.....	25,240	1.7	9,865	.3	117,094	14.9	270,525	53.9	422,724	7.6
Larches.....	2,100	.1	10,599	.4			55,595	11.1	69,294	1.2
All other species ²	90	.0	71,625	2.6	199,336	25.3	15,169	3.0	286,220	5.2
Total by processes.....	1,494,027	26.9	2,765,279	49.9	786,968	14.2	502,568	9.0	5,548,842	100.0

¹ Based on Table 4, "Pulp wood consumption and wood-pulp production, 1922," Bureau of the Census.

² Includes slabs and other mill waste. Species are basswood, beech, birch, maple, chestnut, cottonwood, Douglas fir, white pine, and willow.

Over 80 per cent of all pulp wood in the United States is consumed in mills situated in the New England, Lake, and Middle Atlantic States. The stand of spruce, fir, and hemlock in this territory is estimated at 3 per cent of the total timber stand of the United States and at about 27 per cent of the total stand of the species mentioned.

As a result of these conditions, pulp wood is now being transported by land and water to many mills over distances of from 500 to 1,000 miles. Imports from the Dominion of Canada are very large. In 1922 Maine depended on Canada for 13 per cent of her spruce, New Hampshire for 35, New York for 64, Pennsylvania for 99, and Michigan for 33 per cent. In addition, 53 per cent of the poplar used by United States mills was imported from Canada. On account of the limited supply and the increased influence of the transportation factor, the average cost of spruce pulp wood f. o. b. mill in the Northeastern States in 1922 was between \$15 and \$28 a cord, depending on whether it was rough, peeled, or rossed.

With steadily rising pulp wood costs the less efficient mills, without their own timber supply, will eventually be forced out of business. It is only by improvement in operation, in processes, in the handling of timber lands, and by the use of other species, that even the better-equipped and managed of the present mills can continue to operate. The use of hemlock by the Wisconsin mills is an example of what can be done with wood once considered unsuitable for pulp.

The necessity for the older mills to turn to other species and to grow their own pulp wood is indicated by United States Department of Agriculture Bulletin 1241, "How the United States Can Meet Its Present and Future Pulp-wood Requirements." It is there stated that because pulp wood use is confined so largely to a small group of species, over one-half of the 9,148,000 cords required to manufacture the United States paper requirements in 1922 were imported as pulp wood, pulp, or paper. Many States are forced to rely upon wood from without their boundaries. In New England and the Lake States, where much of the industry is concentrated, imports of pulp wood and wood pulp are being relied upon to a greater and greater extent to maintain production levels. Throughout the pulp and paper manufacturing regions there are insufficient forest resources to maintain production for an extended period without an intensive program of timber growing, the elimination of waste, a general tightening up in the manufacturing processes, and the extensive use of other than commonly used species for pulp wood.

A study of the distribution of the stand of timber in the United States by species will indicate the supply of pulp wood available for existing mills and what could be added by the use of additional species. Table 2 shows such distribution as accurately as it can be ascertained with the information at present available.

TABLE 2.—*Total stands of timber of principal kinds suitable for pulp, in millions of cords, by regions*

Species of timber	New England	Middle Atlantic	Lake	Central	South Atlantic	Lower Mississippi	Rocky Mountain	Pacific coast	Total United States	South east Alaska
Sulphite, mechanical, and sulphate pulp:										
Spruce and fir.....	85.5	14.0	17.1	3.4	3.4	-----	85.5	205.1	414.0	45.3
Hemlock.....	6.4	23.9	51.3	19.7	6.4	-----	2.5	200.9	311.1	121.4
Jack pine.....	-----	-----	38.4	-----	-----	-----	-----	-----	38.4	-----
Total.....	91.9	37.9	106.8	23.1	9.8	-----	88.0	406.0	763.5	166.7
Soda pulp:										
Aspen and cottonwood.....	6.4	2.2	27.3	10.7	5.1	21.4	12.8	-----	85.9	.2
Birch, beech, maple.....	29.0	80.3	136.8	102.6	16.2	16.3	-----	-----	381.2	.1
Yellow poplar.....	-----	.7	-----	29.9	15.4	1.0	-----	-----	47.0	-----
Basswood.....	2.6	2.2	17.1	10.7	1.7	-----	-----	-----	34.3	-----
Red gum.....	-----	.9	-----	18.8	51.3	97.4	-----	-----	168.4	-----
Black and tupelo gums.....	-----	1.1	-----	21.3	54.7	54.7	-----	-----	131.8	-----
Total.....	38.0	87.4	181.2	194.0	144.4	190.8	12.8	-----	848.6	.3
Sulphate pulp:										
Southern yellow pine.....	1.1	15.1	-----	21.4	453.0	487.2	-----	-----	977.8	-----
Tamarack and larch.....	.9	-----	21.4	-----	-----	-----	34.2	12.8	69.3	-----
White and sugar pines.....	35.0	22.2	21.4	2.5	4.3	-----	42.7	81.2	209.3	-----
Western yellow pine.....	-----	-----	-----	-----	-----	-----	136.8	384.6	521.4	-----
Lodgepole pine.....	-----	-----	-----	-----	-----	-----	128.2	12.8	141.0	-----
Total.....	37.0	37.3	42.8	23.9	457.3	487.2	341.9	491.4	918.8	-----
Regional total.....	166.9	162.6	330.8	241.0	611.5	678.0	442.7	897.4	530.9	167.0
Regional total per cent.....	7.9	8.4	8.9	18.3	24.6	15.5	4.6	11.8	100.0	-----

Taken from Dept. Bull. No. 1241 "How the United States Can Meet Its Present and Future Pulpwood Requirements," by Earle H. Clapp and Chas. W. Boyce.

¹ Contains no allowance for deduction in stand by spruce bud worm, which amounts to 40 per cent or about 27½ million cords in Maine.

In order to make clearer the advantages to be gained by extending the pulp-wood supply to other species, Tables 3 and 4 are presented. These show the amounts of pulp wood consumed in each process in the United States in 1922 and the production of paper by types, together with observations as to the species pulped and the pulps or other raw materials used in the various types of paper.

TABLE 3.—*Pulp wood consumed in the United States, 1922, by processes*

Pulping process	Cords consumed 1922 ¹	Species required
Mechanical.....	1,494,027	Easily ground, white, long-fibered species such as spruces and firs.
Sulphite.....	2,765,279	Nonresinous long-fibered species such as spruces, firs, and hemlocks. Process may be applied to many of the pines and hardwoods.
Soda.....	786,968	Easily pulped, easily bleached hardwoods, such as poplars, birches, maples, beech, and gums. Process may be applied to the conifers.
Sulphate.....	502,568	Any species of conifer. Process may be applied with advantage to hardwoods also.

¹ From Table 1.

TABLE 4.—*Paper production of the United States for 1922*

Kind of product	Tons produced	Pulps or other raw materials used
Newsprint paper.....	¹ 1, 447, 688	Ground wood 80 per cent, sulphite 20 per cent. Old newspapers can be used.
Paper boards.....	2, 153, 835	Old papers, ground wood, sulphate, sulphite, and straw.
Book paper.....	981, 919	Bleached and unbleached sulphite, bleached soda, waste papers free from ground wood, cotton linters, rags.
Wrapping paper.....	836, 271	Sulphite, sulphate, ground wood, old papers, rope, textile waste, straw.
Bag paper.....	212, 122	Sulphate and sulphite.
Fine papers.....	361, 050	Rags, cotton linters, bleached sulphite, bleached sulphate, bleached soda.
Tissue paper.....	197, 524	Rags, sulphite, sulphate, rope, textile waste, flax straw.
Hanging paper.....	91, 894	Old papers, ground wood, sulphite, sulphate, soda.
Felts.....	420, 119	Rags, textile wastes, spent tan bark.
Other grades.....	311, 433	

Compiled from reports of paper production made by the Federal Trade Commission.

¹ 2,530,000 tons of newsprint was manufactured in the United States and Canada in 1922, over 80 per cent of which was consumed in the United States.

On examination of the tables it can be seen how, by the more extended employment of bleached sulphate in book and of semi-bleached or unbleached sulphate in wrapping and bag paper—in many cases with improved results—the use of the more plentiful and less commonly used species may be greatly increased.

Experimental work at the Forest Products Laboratory has demonstrated that the sulphate process applied to the southern pines, in combination with the gums and similar hardwoods of the South, will yield pulps which may be bleached by proper methods and used in the manufacture of book, magazine, and similar high-grade printing papers at reasonable manufacturing cost. The value of this experimental work is emphasized by the fact that the South is advantageously situated in respect to nearness to the publishing centers and availability of fuel, chemicals, and other raw materials. Not only has it enormous quantities of suitable woods available, but owing to climatic conditions the amount of wood which can be grown in the South is from 35 to 40 per cent of the potential productivity of the entire area of forest land in the United States. The growing capacity of unit areas is also very high.

On the other hand, for pulps which require spruce, hemlock, and fir, woods of established value in making paper, there are stands in Oregon, Washington, and Alaska sufficient, under proper timber-growing methods, to supply approximately 5,000,000 cords a year. It has been due largely to economic conditions that the extensive development of these pulp resources has so long been retarded. Up to recent years the only outlet for mills on the Pacific coast has been the local consumption of paper and export to foreign countries. With the rapidly increasing cost of wood in the East greater margins will be created to allow for the cost of transporting pulp and paper from the Pacific coast to other parts of the United States; and such shipments will continue to be an increasing factor in the general situation.

STANDARD PULPING METHODS

At the present time there are two main classes of pulp made from wood, mechanical and chemical.

MECHANICAL PROCESS

Mechanical pulp is made by simply grinding the wood to pulp on a stone, enough water being used to control the temperature. The

wood for grinding is first cut into bolts of the desired length and the bark completely removed. The clean bolts are then ground either hot or cold, according to the character of pulp desired. The difference in the results obtained is largely in the "freeness," or the rate at which water will drain from the pulp on the paper machine. Water will drain away much faster from hot-ground pulp than from cold-ground pulp. Hot grinding, the American practice, is done by adding only sufficient water at the grindstone to keep the temperature of the pulp in the neighborhood of 150° F. In cold grinding, which is more commonly employed in Europe, much larger quantities of water are used, with a resulting temperature very little above the temperature of the water. Some ground-wood pulp is manufactured from wood that has been steamed or boiled before grinding, but the quantity is so small that it is not considered in this publication. The reader is referred to Department Bulletin No. 343, "Ground-Wood Pulp," for more specific information and reports of tests on various species in the manufacture of mechanical pulp.

In the mechanical process, since very little, if any, chemical action takes place, the physical properties of the wood are of first consideration. One of the most important qualities is the color of the wood, which is directly reflected in the color of the pulp obtained. Only the lightest colored woods can be considered for use in the manufacture of newsprint, for which almost all mechanical pulp is utilized. Although the mechanical process is very destructive to the fibers of the wood and their average length is seriously reduced in the operation, nevertheless long-fibered woods, such as spruce, are desired, since the longer the fibers present in the wood the greater the average fiber length of the pulp obtained.

The hardness and structure of the wood are reflected in the power consumed in grinding pulp of standard strength and in the amount of disintegration caused by the action of the stone in tearing the fibers from the mass. Hardwoods with a dense medullary structure consume from two to three times as much power as softer, lighter woods, and their fibers are to a great extent torn to pieces. As a rule, therefore, their use is barred. Woods which give soft, spongy pulps are also undesirable, as are woods which yield pulps composed of mixtures of fine slivers and débris. A measure of control, however, can be exerted over pulp properties by the manner of dressing the stone.

The size and shape of the pieces of wood used in grinding are of considerable importance in the mechanical process with the customary equipment. The greater the number of pieces of wood fed to the grinders per ton of pulp the greater the number of splinters, since from each piece there is usually a thin slab which passes from the pocket without further reduction after a certain minimum thickness is reached.

Specific gravity is an important consideration, because the higher the specific gravity the greater the weight of pulp obtained from a cord.

The pitch content is also important, since, under given conditions, more than a certain amount will cause trouble in the subsequent paper-making operations.

Discolorations in the wood caused by fungi, molds, or bacteria are usually reflected in the pulp obtained. The durability of the wood used in the mechanical process, i. e., its resistance to the organisms of

decay, is, therefore, of great importance. Not only the color but also the physical properties of the pulps, as well as their paper-making qualities, are seriously influenced by decay, which often causes considerable loss of material. Decay has more serious effects in this process than in any of the chemical processes.

CHEMICAL PROCESSES

Of the chemical processes the sulphite, soda, and sulphate processes are standard, and all the wood pulp made by chemical means on a commercial scale is the product of one of the three.

SULPHITE PROCESS

The sulphite process is by far the most important from the standpoint of annual tonnage. It consists of the removal of the incrusting matter in the wood by means of a solution of sulphur dioxide in an aqueous solution of calcium or magnesium bisulphite or a mixture of the two. The pulp is usually light colored and in many products may be used without bleaching. The wood is first barked and then chipped to suitable dimensions to permit proper contact and circulation of the cooking liquor during digestion. As the liquor will not dissolve bark, great care must be exercised in the barking operation; for this reason the size and shape of the wood as received at the mill must be taken into consideration. Round wood down to 3 inches in diameter is used in some instances, but the cost of removing the bark and the relatively large proportion of wood lost in the operation have greatly retarded the use of small material. The same reason has discouraged the use of mill waste from lumbering or wood-working operations, and the quantity of such material reported as having been used in the manufacture of paper pulp in 1920 was actually less than that reported in 1914.

Decay often gives considerable trouble in the manufacture of sulphite pulp, since certain fungi prevent the wood from being completely acted on by the liquor. Discolorations in the wood appear in the pulp, the wood affected is incompletely pulped, and trouble from uncooked portions is encountered.

On account of the acid character of the process, resinous matter, tannins, and other extractive substances are not dissolved, and their presence, by resisting the penetration of the cooking liquor, often prevents complete pulping. In the mill they cause trouble on account of shives or excessive screenings. The pitch particles themselves, either alone or combined or agglomerated with the cooking base, create difficulties on the paper machine in numerous ways familiar to the paper maker.

The spruces, firs, and hemlocks are all capable of reduction by the sulphite process without undue trouble from pitch. Most of the pines, cedars, larches, cypresses, and sequoias, and Douglas fir are too resinous or contain other extractive matter which retards the penetration of the cooking liquor. A few of the pines are used to a limited extent, and it seems probable that with more definite information in regard to the fundamental scientific principles governing the sulphite process the rapidly growing and more easily pulped species such as jack pine, loblolly pine, and Virginia pine will come into more general use, especially when the wide range of some of

them is considered. Although some of these species may give as high as 6 per cent screenings on account of knots or small local portions more resinous than the rest of the wood, the uncooked portions can usually be successfully removed with standard equipment, leaving relatively clean pulps of satisfactory color. The pines of the white pine series that were tested (northern white pine, sugar pine, limber pine, and piñon) can not be satisfactorily pulped, even though on inspection they show less resin than the other pines mentioned above. Although the amounts of screenings are small, the pulps contain particles of partially cooked wood which pass through the screen plate slots with the fiber and cause the pulps to be specky and of poor color. Not only do the extractive substances affect penetrability, but often the structure of the wood itself has considerable influence, and many species show differences in cooking which can be attributed only to this cause.

Although the fibers are separated by the sulphite process without reduction in ultimate length, fiber length is of such importance that, as a rule, only long-fibered woods are pulped in this way. The color is usually of minor significance, except in the case of deeply colored woods, whose coloring substances are often not dissolved in the cooking operation, so that the color of the pulps is affected.

Specific gravity of the wood has the same importance in affecting the yield per cord as in the case of ground-wood pulp, and it also directly affects the quantity of wood per digester charge and thereby the output of the mill.

The bleachability of the pulp and the ease or difficulty of hydration are important considerations. They both depend to a considerable extent on the cooking conditions.

Although the soda process is generally used on hardwoods on account of the greater opacity of the pulp, the sulphite process produces from many species (such as the birches, maples, and gums) greater yields of pulp that can be bleached with much lower consumption of bleach.

SODA PROCESS

The soda process is almost entirely devoted to the pulping of hardwoods. When the Forest Service pulping experiments were started the species in commercial use were the true poplars, yellow poplar, the soft maples, basswood, and possibly a few other of the most easily pulped species. At present, by the use of improved methods, birches, hard maples, gums, beech, chestnut, sycamore, and numerous others are also being pulped. The pulp is usually bleached. It holds loading materials and takes coatings well. It also possesses soft, bulky, and absorbent qualities which, when it is properly mixed with bleached or unbleached sulphite, give an opaque, well felted, and well formed sheet of paper highly esteemed by the printer. Soda pulp is consequently used largely in the manufacture of book, magazine, lithograph, and other papers for printing purposes, and considerable quantities are employed in the manufacture of blotting paper.

The soda process can be applied without difficulty to coniferous woods and to a limited extent is so applied. Usually, however, the greater strength and toughness of pulp produced by the sulphate process from the same wood has limited the use of the soda process for producing strong pulps. Soda pulp from conifers is hard to bleach, and the process is, therefore, little used for bleached pulp

from such species. It is not, however, handicapped by the disagreeable odor characteristic of sulphate mills, which is probably the reason it has not been supplanted entirely by the more recent process.

The soda process consists of the disintegration and solution of the incrusting matter in the wood by means of an aqueous solution of sodium hydroxide, the wood being prepared in a manner similar to that used in the sulphite process. It is not so important, however, to remove entirely the bark, knots, or decayed portions, because under proper conditions the soda liquor disintegrates them. Nevertheless, the wood is usually peeled so as to avoid the consumption of alkali in the solution of the bark or of decayed portions which yield no pulp.

Pitch is not objectionable in the soda process, as it is readily dissolved in the cooking liquor. Tannins, however, consume caustic soda and make necessary the use of larger quantities. Also tannins not removed (by means of water extraction) before the cooking operation usually darken the pulp and render it much more difficult to bleach.

Although fiber length is important, it is not so much so as in the sulphite process, because soda pulp is used almost entirely in the manufacture of printing papers where printing qualities outweigh strength. The color of the wood is also a minor factor, since the coloring matter is in many cases dissolved by the liquor and removed from the pulp. With some woods, however, the coloring matter persists throughout the cooking action, and is apparent in the pulp.

The specific gravity of the wood has the same importance as in the sulphite and mechanical processes.

SULPHATE PROCESS

The sulphate process, only recently introduced into America, was first used in continuous commercial operation in Quebec in 1907. Since that time the production of sulphate pulp has increased very rapidly. In 1914 about 52,000 tons were produced in the United States. By 1922 production had risen to over 243,000 tons. The reasons for this increase are the larger yields of pulp and the greater strength of the paper.

It is a modification of the soda process in which the active ingredients of the cooking liquor consist of caustic soda and sodium sulphide, usually in the proportion of 2 to 1. Its use is confined almost entirely to conifers. There is no reason why it should not be applied to hardwoods; with the majority of these species easier bleaching pulps are obtained with equal yields. The unbleached pulp from conifers is commonly used in the manufacture of kraft wrapping paper or, in combination with waste papers, for high-test container board.

Although the practice of bleaching sulphate pulp is not very prevalent, work at the Forest Products Laboratory has demonstrated that by using modified methods of bleaching with the standard solutions, and with quantities of bleaching powder not in excess of common commercial practice, very satisfactory results may be obtained. Although the pulp obtained by ordinary methods of bleaching is yellow and does not approach the brilliant white characteristic of bleached sulphite pulp, pulp comparable in brightness is obtained by the modified methods. The opacity of the bleached pulp is

usually greater than that of bleached sulphite pulp. It thus becomes possible to obtain from sulphate pulp papers having printing properties superior to those of papers from bleached sulphite pulp, unless the latter is combined with bleached soda pulp from hardwoods.

The main drawback of the sulphate process lies in the disagreeable odors which characterize it; on this account the mills are usually located on the fringes of population.

The wood is usually barked, although in some mills this step is omitted and any fragments of bark which pass the screening operation are dissolved in the digester. The consequent high consumption of cooking liquor without any return, however, makes it more economical to bark the wood before chipping. Decayed wood does not affect the quality of the pulp as it does in the sulphite process,

FIG. 1.—Digester used for alkaline cooks prior to 1916, and for sulphite cooks prior to 1911

but it very seriously affects the yields and consumption of alkali to a ton of pulp. The durability of the wood used is therefore an important consideration from the economic standpoint.

Charred wood is objectionable in this process (as well as in the others), since the particles of carbon survive the cooking operation and appear in the pulp. Pitch, fats, or waxes occasion no trouble, these being readily soluble in the sulphate liquors and furnishing to the cooking liquor combustible matter which helps later in the recovery of the soda.

The penetrability of the wood is a considerable factor in the quality and uniformity of the pulp. The length of the fibers is of major importance, as sulphate pulps are ordinarily used for purposes where strength is required. The color of the wood is a secondary consideration except in a few instances where the coloring matter survives the cooking operations. The specific gravity of the wood is directly reflected in the yield of pulp obtained per cord.

EXPERIMENTAL PROCEDURE ²

EQUIPMENT

In the course of the Forest Service experiments several digesters were used for making the cooks. In Figure 1 is shown the lead-lined digester which was used until 1911. From 1911 to 1916 the same equipment, with the lead lining removed, was used for the alkaline cooks only, the equipment shown in Figure 2 being used for the sulphite cooks. Since 1916 the equipment shown in Figures 3 and 4 has been used for the sulphite cooks and that in Figures 5 and 6 for the alkaline cooks. All these digesters held between 60 and 70 gallons, and all gave similar results. All were stationary with the exception of the one shown in Figures 3, and 4, which could be revolved on trunnions to obtain positive circulation. In all the digesters except the earliest, indirect heat as well as direct steam

FIG. 2.—Digester used for sulphite cooks from 1911 to 1916, inclusive

was supplied in order to overcome the excessive radiation characteristic of small-sized apparatus. By that means condensation was obtained comparable in amount to that in commercial equipment. The chipper used was of the usual disk type but of laboratory size. Figure 7 shows the semicommercial beater used, and Figure 8 the combination 12-inch cylinder and Fourdrinier paper machine on which the paper samples were made. Operating in conjunction with the paper machine was a Jordan refining engine of laboratory size, so that the results obtained were comparable to mill practice.

CONDUCT OF TESTS

The chips, cut five-eighths along the grain, were carefully screened to remove sawdust, bark, large pieces, and large knots. Before charging, the moisture content of the wood was determined and the quantities of cooking chemicals and the volume of liquor were calculated from the oven-dry weight of the wood. During cooking,

² Tests on chemical pulps only. For experiments on mechanical pulps see THICKENS, J. H., and McNAUGHTON, G. C., GROUND-WOOD PULP. Dept. Agr. Bul. 343, p 151, illus., 1916.

pressure and temperature were carefully regulated and observations recorded at 15-minute intervals. At the end of the cooking period samples of liquor were taken and, in the case of sulphite cooking, analysis was made and color observed. The digester contents were then discharged into the blow pit. There the pulp was washed free of cooking liquor and drained. In the case of impregnation cooks the digester was completely filled with chips and cooking

FIG. 3.—Digester used for sulphite cooks since 1916 (end elevation)

liquor and the cover bolted on. The pressure tank, I in Figure 3, was next filled, and, by forcing steam into the top of I and opening the connections therefrom to the digester, hydrostatic pressure was set up around the chips, forcing the liquor into them until at the end of from 15 to 30 minutes at a pressure of from 100 to 110 pounds to the square inch they were well penetrated. The digester was then inverted, the valves in the relief pipe L and pipe O (fig. 4) were opened, and the proper quantity of liquor was blown back

into tank X from which it was originally obtained, steam being admitted to the digester above it to supply the force necessary. By weighing and analyzing the liquor before impregnation and during its return the quantity of chemical remaining in the digester could be determined and controlled. After sufficient liquor had been returned to the tank to leave the desired quantity in the digester, the connections referred to were closed, water was added if necessary

FIG. 4.—Digester used for sulphite cooks since 1916 (side elevation)

to give the desired volume in the digester, and the cook was carried on in the usual manner. The usual procedure applied also to screen- and other treatments.³

After the pulp was completely washed and drained it was hydraulically pressed, opened up in a swing-hammer shredder, and weighed and sampled for moisture. From the moisture determination the

³ KRESS, OTTO, WELLS, SIDNEY D., and EDWARDES, VANCE P. NAMES FIRST THE EQUIPMENT AND OPERATION OF AN EXPERIMENTAL LABORATORY. Paper, April 19, 1920.

bone-dry weight of the pulp was ascertained, and thereby the yield. The pulp was then passed through a diaphragm screen and the screenings were dried and weighed. Samples of the pulp were

FIG. 5.—Digester used for alkaline cooks since 1916 (front elevation)

saved for bleach tests; the rest was treated in the beater to produce the desired quality of waterleaf paper and was run over the machine. Standard strength tests were made on the papers obtained.

Bleaching tests were made by treating various samples of equal weight with quantities of bleach ranging from 5 to 40 per cent of

the weight of the pulp, according to requirements estimated from preliminary observations. Forty grams of pulp in 1,600 cubic centimeters of total liquid were used in each test. The mixture

FIG. 6.—Digester used for alkaline cooks since 1916 (end elevation)

was kept in constant agitation at a temperature of between 100° and 110° F. until the bleach was exhausted. Hand sheets were made of the pulp, and the measure of bleaching was taken as the quantity of bleach beyond which no improvement in color was observable.

SPECIES INVESTIGATED

The species tested are listed in Table 5, together with their botanical names and the locality where the material obtained was grown.

TABLE 5.—*Species tested, and locality of growth*

Common name	Botanical name	Where grown
Softwoods:		
Black spruce.....	<i>Picea mariana</i>	Wisconsin.
Blue spruce.....	<i>Picea pungens</i>	Colorado.
Engelmann spruce.....	<i>Picea engelmannii</i>	Idaho.
Norway spruce.....	<i>Picea abies</i>	Iowa.
Red spruce.....	<i>Picea rubra</i>	Tennessee.
Sitka spruce.....	<i>Picea sitchensis</i>	Oregon.
White spruce.....	<i>Picea glauca</i>	Wisconsin.
Limber pine.....	<i>Pinus flexilis</i>	Colorado.
Piñon.....	<i>Pinus edulis</i>	Do.
Sugar pine.....	<i>Pinus lambertiana</i>	California.
Northern white pine.....	<i>Pinus strobus</i>	Wisconsin.
Jack pine.....	<i>Pinus banksiana</i>	Do.
Loblolly pine.....	<i>Pinus taeda</i>	Virginia and South Carolina.
Lodgepole pine.....	<i>Pinus contorta</i>	Montana.
Long-leaf pine.....	<i>Pinus palustris</i>	Louisiana.
Monterey pine.....	<i>Pinus radiata</i>	California.
Norway pine.....	<i>Pinus resinosa</i>	Wisconsin.
Pitch pine.....	<i>Pinus rigida</i>	Tennessee.
Pond pine.....	<i>Pinus rigida serotina</i>	South Carolina.
Sand pine.....	<i>Pinus clausa</i>	Florida.
Scotch pine.....	<i>Pinus sylvestris</i>	Iowa.
Virginia pine.....	<i>Pinus virginiana</i>	Maryland and Tennessee.
Short-leaf pine.....	<i>Pinus echinata</i>	Louisiana.
Slash pine.....	<i>Pinus caribaea</i>	Florida.
Western yellow pine.....	<i>Pinus ponderosa</i>	Oregon.
Pehuén (Monkey-puzzle).....	<i>Araucaria araucana</i>	Argentina.
Alpine fir.....	<i>Abies lasiocarpa</i>	Montana.
Balsam fir.....	<i>Abies balsamea</i>	Wisconsin.
Lowland white fir.....	<i>Abies grandis</i>	Washington.
Noble fir.....	<i>Abies nobilis</i>	Oregon.
Red fir.....	<i>Abies magnifica</i>	California.
Silver fir.....	<i>Abies amabilis</i>	Washington.
White fir.....	<i>Abies concolor</i>	California and Oregon.
Douglas fir.....	<i>Pseudotsuga taxifolia</i>	Oregon.
Carolina hemlock.....	<i>Tsuga caroliniana</i>	Georgia.
Eastern hemlock.....	<i>Tsuga canadensis</i>	Wisconsin.
Western hemlock.....	<i>Tsuga heterophylla</i>	Washington.
Tamarack.....	<i>Larix laricina</i>	Wisconsin.
Western larch.....	<i>Larix occidentalis</i>	Montana.
Incense cedar.....	<i>Libocedrus decurrens</i>	California.
Port Orford cedar.....	<i>Chamaecyparis lawsoniana</i>	Oregon.
Southern white cedar.....	<i>Chamaecyparis thyoides</i>	North Carolina.
Eastern red cedar.....	<i>Juniperus virginiana</i>	Arkansas.
Western red cedar.....	<i>Thuja plicata</i>	Washington.
Southern cypress.....	<i>Taxodium distichum</i>	Missouri.
Redwood.....	<i>Sequoia sempervirens</i>	California.
Hardwoods (diffuse-porous):		
Aspen.....	<i>Populus tremuloides</i>	Wisconsin.
Balsam poplar.....	<i>Populus balsamifera</i>	Montana.
Eastern cottonwood.....	<i>Populus deltoides</i>	Wisconsin.
Norway poplar.....	<i>Populus canadensis eugeni</i>	Minnesota.
Large-tooth aspen.....	<i>Populus grandidentata</i>	Wisconsin.
Yellow poplar.....	<i>Liriodendron tulipifera</i>	West Virginia.
Basswood.....	<i>Tilia glabra</i>	Wisconsin.
Black willow.....	<i>Salix nigra</i>	Missouri.
Sandbar willow.....	<i>Salix longifolia</i>	Ohio.
Red alder.....	<i>Alnus rubra</i>	Washington.
Balsa.....	<i>Ochroma lagopus</i>	Canal Zone.
Box elder.....	<i>Acer negundo</i>	Wisconsin.
Red maple.....	<i>Acer rubrum</i>	South Carolina.
Sugar maple.....	<i>Acer saccharum</i>	Michigan.
Paper birch.....	<i>Betula papyrifera</i>	New Hampshire.
Yellow birch.....	<i>Betula lutea</i>	Wisconsin.
Beech.....	<i>Fagus grandifolia</i>	Pennsylvania.
Black gum.....	<i>Nyssa sylvatica</i>	South Carolina and Tennessee.
Tupelo gum.....	<i>Nyssa aquatica</i>	Louisiana and Florida.
Red gum.....	<i>Liquidambar styraciflua</i>	Tennessee and South Carolina.
Cucumber magnolia.....	<i>Magnolia acuminata</i>	West Virginia.
Sweet bay.....	<i>Magnolia virginiana australis</i>	Florida.
Sycamore.....	<i>Platanus occidentalis</i>	Maryland.
Butternut.....	<i>Juglans cinerea</i>	Virginia.
Ohio buckeye.....	<i>Aesculus glabra</i>	Tennessee.
Mangrove.....	<i>Rhizophora mangle</i>	Florida.

TABLE 5.—*Species tested, and locality of growth*—Continued

Common name	Botanical name	Where grown
Hardwoods (ring-porous):		
Common catalpa.....	Catalpa bignonioides.....	Kansas.
Chestnut.....	Castanea dentata.....	Virginia.
Hackberry.....	Celtis occidentalis.....	Indiana.
Sassafras.....	Sassafras varifolium.....	Tennessee.
Rock elm.....	Ulmus racemosa.....	Wisconsin.
Slippery elm.....	Ulmus fulva.....	Indiana.
American elm.....	Ulmus americana.....	Wisconsin.
White ash.....	Fraxinus americana.....	Arkansas.
Red oak.....	Quercus borealis maxima.....	Tennessee.
White oak.....	Quercus alba.....	Do.
Mockernut hickory.....	Hicoria alba.....	Virginia.
Black locust.....	Robinia pseudoacacia.....	Georgia.
Ailanthus.....	Ailanthus altissima.....	Pennsylvania.
Miscellaneous:		
Soapweed.....	Yucca elata.....	Arizona.
Cabbage palmetto.....	Sabal palmetto.....	Florida.
Cane.....	Arundinaria macrosperma.....	Louisiana.
Chilean woods:		
Olivillo.....	(?).....	Chile.
Laurel.....	Laurelia aromatica.....	Do.
Coigue.....	Nothofagus dombeyi.....	Do.
Lingue.....	Persea lingue.....	Do.
Roble pellin.....	Nothofagus obliqua.....	Do.
Quillai.....	Quillaja saponaria.....	Do.

The material was selected from localities, within the commercial range of the species, where average conditions existed. Representative specimens were taken and efforts were made to maintain the amounts of heartwood and sapwood in the chips at as nearly as possible the same proportions as would occur in the usual run of pulp wood at the mill.

The Chilean woods listed were tested in response to a request from the Department of State in 1913. The species studied were submitted by Alejandro Rosselot, of Santiago, Chile, and represented what he considered the most important Chilean species from the standpoint of paper manufacture. At a later date tests were made on pehuén (*Araucaria aurocana*) submitted by a Chicago lumber concern, the material having been obtained from a stand about 500 miles south of Mendoza, Argentina, on the eastern slope of the Andes. The species is native to both Argentina and Chile. The data here presented on South American species are not at all complete. Much more detailed information as to the extent of the stands of various species, paper consumption, transportation facilities, labor, fuel, water supply, etc., will be necessary before any application of the pulping data is warranted.

PULPING CHARACTERISTICS OF GROUPS OF WOODS

SOFTWOODS

All of the spruces tested are suitable for pulping by any of the processes and are capable of yielding pulp of the best quality. The main considerations with the spruces are the size, straightness, and density of the wood. Although they vary somewhat in fiber length, even the species with the shortest fiber are capable of producing pulp of the best quality.

The hemlocks are used in all chemical processes. Sulphite pulp from hemlock hydrates more readily than that from spruce and will

not make paper of quite as great strength. The unbleached pulp is darker and requires more bleach. Western hemlock is much more easily pulped than eastern hemlock, and the pulp more nearly resembles that from spruce. Western hemlock is used to a certain extent in the manufacture of mechanical pulp, but the power requirements to produce pulp of the same strength as spruce are somewhat greater; or, if pulp is produced with the same power consumption, a weaker pulp requiring more sulphite in the manufacture of standard newsprint is obtained.

The firs can be used in all the processes. They produce pulp very similar to that from spruce in practically every characteristic. With

FIG. 7.—Beater of semicommercial type used in the pulping experiments

red fir, however, both the sulphite and mechanical pulps are darker colored, and the sulphite is more difficult to bleach.

As to the pines, general statements can not be made with the same assurance. Lodgepole pine and western yellow pine have been used successfully in extensive experiments in the manufacture of mechanical pulp, the color of which was satisfactory and the strength, power consumption considered, closely comparable to that of spruce. Under the sulphite process, jack pine, loblolly pine, lodgepole pine, Norway pine, pond pine, sand pine, and Virginia pine yielded pulp of very fair quality, capable of bleaching with reasonable quantities of chemical. In the case of loblolly pine, lodgepole pine, Norway pine, sand pine, and Virginia pine the uniformity of the digestion

was very satisfactory. With jack pine and pond pine the screenings ran from 3 to 6 per cent—which, however, is not prohibitive.

Northern white pine, sugar pine, limber pine, and piñon are all capable of manufacture into mechanical pulp of excellent quality. In the sulphite process, however, penetration by the cooking liquors is very slow and the results are unsatisfactory. All the pines reduce readily under the alkaline processes and produce pulp that may be bleached, although the product is less satisfactory than the standard bleached sulphite pulps.

Larches, Douglas fir, southern cypress, and cedars with light-colored wood can be pulped by the sulphite process, although with

FIG. 8.—Combination cylinder and Fourdrinier paper machine upon which the paper samples were made

more difficulty than hemlock. The quantities of bleach required are high but are within the range of commercial feasibility. None of these woods has been satisfactorily reduced by the alkaline processes to pulp bleachable with a reasonable quantity of bleach. Southern cypress is the most difficult. Redwood and cedars with dark-colored wood are very difficult to pulp or to bleach by the sulphite process. Consideration of the mechanical processes for these woods is not warranted, owing to their dark color. Their light weight and consequently the low yields obtained discourage consideration of them for the alkaline processes, although very satisfactory pulps for unbleached wrapping paper can be obtained.

In the case of species more or less resinous, it frequently happens that by the mechanical or sulphite-processes pulps of satisfactory strength and color can be obtained, but that the presence of "pitch" gives rise to operating difficulties in the paper mill. The laboratory experimental runs in which the pulps were studied were so short that the degree to which "pitch" troubles would be encountered was not ascertained accurately. It is possible that the difficulties would be decreased or eliminated by a judicious use, on the grinders or in the beaters, of some highly colloidal material such as bentonite. At the suggestion of the laboratory staff bentonite has been used commercially in both sulphite and mechanical pulping operations, with satisfactory results. It may become an important factor in extending the use of resinous pulp woods.

HARDWOODS

The fibers of hardwoods are short and hence not suited to the manufacture of strong, tough papers. They do, however, contribute to the formation of a well-closed, smooth-surfaced sheet of the type that is essential for a satisfactory print paper. In news and similar cheap print papers this characteristic is obtained more economically by the addition of ground wood than by the addition of a short-fibered chemical pulp; hence bleached hardwood chemical pulps find their most extensive use in print papers of the higher grades. The alkaline-cooked pulps, by virtue of their softness, bulk, and opacity, are most favored. The sulphite pulps are harder and less opaque but yield better, bleach whiter, and require less bleach. Their lack of opacity may be overcome by the addition of mineral fillers. A more extensive use of hardwood sulphite pulps in the manufacture of book, envelope, and similar paper may be expected, especially in paper mills that are already equipped for the production of sulphite.

The following hardwoods, with diffuse-porous structure, can be reduced readily by the sulphite process and bleached with small quantities of chemical: Poplars, willows, maples, birches, gums, magnolias, sycamore, and butternut. Of these with ring-porous structure, hackberry, elm, ash, and hickory can be readily or fairly readily pulped and bleached. The pulp usually contains small dark-colored specks, which, however, disappear on bleaching. Of diffuse-porous woods difficult to pulp and bleach to a satisfactory product there were tested basswood, red gum, and Ohio buckeye; of ring-porous woods difficult to pulp and bleach, common catalpa, chestnut, sassafras, slippery elm, red and white oak, and black locust. In both cases the difficulty of pulping is probably due to extractive matter or to structure which prevents penetration of the wood by the cooking liquor.

The hardwoods, in general, are unsuited to the manufacture of mechanical pulp, on account of the high power consumption required and the weakness of the pulp. By the adoption of new principles in grinding, however, it may become practicable to use the lighter colored of the hardwoods, such as the poplars, birches, and gums, for the manufacture of mechanical pulp.

All the hardwoods are capable of reduction by the soda or sulphate processes. The poplars and basswood among the diffuse-porous species are very easily pulped and bleached, and yellow poplar, willows, soft maples, beech, red alder, and balsa fairly easily. The

birches, hard maples, gums magnolias, Ohio buckeye, butternut, and mangrove are rather difficult but are within the realm of profitable utilization. Of the ring-porous woods chestnut, after extraction, and the elms are fairly easily pulped and bleached. Unextracted chestnut, however, yields a pulp which is very inferior and very difficult to bleach. Common catalpa, hackberry, and white ash are rather difficult; sassafras, red and white oak, mockernut hickory, and black locust are very difficult.

BARK DISPOSAL

In considering the availability of various species for paper pulp the question of the utilization of the bark removed in the preparation of the wood naturally occurs. The feasibility of such utilization depends to a very large extent on local conditions, and each species and locality should be studied independently. Attempts to make use of this waste have met with considerable success in a number of cases. The most obvious means of utilization is as fuel, and at many mills it is found that the burning of the bark supplements the fuel supply to an appreciable extent. This is especially true if the bark is obtained from knife barkers or, in case the wood is barked wet in drum barkers, if as much water as possible is removed by means of a press before feeding to the furnaces. The barks from some species, such as hemlock, contain sufficient tannin to justify recovery of the latter by means of water extraction before burning. Extracted hemlock tanbark has also been found a suitable material for use with rags for the manufacture of roofing felt, and considerable quantities have been used for that purpose. Redwood bark is so utilized on a commercial scale.

Experiments with bark from the southern pines indicate that satisfactory roofing felt may be made with it by adding enough sulphate pulp from the same wood to give the required strength for passing through the impregnating bath. Spruce bark has been used as a portion of the furnish in the manufacture of board and cheap wrapping papers, such as car liner. Balsam fir and spruce barks have been used in finely shredded form in the manufacture of heat-insulation material.

SUITABILITY OF INDIVIDUAL SPECIES FOR PULPING

Descriptive summaries dealing with the pulping characteristics of various species under one or more of the various processes are given on pages 25 to 65. These summaries include brief statements about names of species, their range, specific gravity, and fiber length.

The information on names and range is based on the revised "Check List of the Forest Trees of the United States," by George B. Sudworth (United States Department of Agriculture (Miscellaneous Circular 92.)

ESTIMATION OF PULPING VALUE

All statements appearing in the summaries as to yields and quality of pulp and consumption of bleach are to be regarded as estimates of results to be expected under commercial operating conditions. In arriving at such estimates the writers have considered, (1) under the chemical pulp, the results of a limited number of laboratory tests on each species—usually not more than two or three for each pulping process—the data for which are recorded in Tables 6 to 12, and, under

the mechanical pulps, the results published in Department Bulletin No. 343, "Ground-Wood Pulp"; (2) the relation of yield and quality of pulp to particular conditions of pulping and to the characteristics of individual woods; and, (3) limitations affecting the reproduction of laboratory results at the mill. These considerations are briefly discussed in the next three paragraphs.

LABORATORY PULPING TESTS

Although the operation of the tests recorded in Tables 6 to 12 was standardized as far as possible, it was necessary to vary cooking conditions according to the character of the wood pulped. It is fully recognized that, with very little information available beforehand to guide the selection of the conditions, the cooks frequently failed to produce the best results. In such cases conclusions as to practical pulping values must be arrived at largely by a process of deduction based upon later and more exact knowledge of the factors involved. The figures shown in the tables represent, however, results obtained under specific selected conditions of operation. They make up the most comprehensive body of data that has been compiled with regard to the pulping of American species by the various chemical processes. They are presented in this bulletin as a matter of scientific record and for the possible guidance of future research.

CONDITIONS OF PULPING AND CHARACTER OF WOOD

For a number of years the laboratory has conducted special studies of spruce, loblolly pine, jack pine, and aspen in an effort to relate yield and quality of pulp to the conditions of pulping and to the characteristics of the wood itself. The results of these special studies have been published at intervals in Government bulletins or in the trade and technical journals. Many of the most important results have been obtained comparatively recently. Had the information been available at an earlier stage of the general study of American species, the conditions of pulping could have been selected so as to yield pulps in the laboratory more nearly equal, in both quantity and quality, to those now considered possible of realization on a commercial scale. In preparing the descriptive summaries of species, however, the aim has been to interpret the results of the pulping tests in the light of the more recently acquired knowledge and so arrive at reasonably accurate estimates of the practical pulping characteristics of the species studied.

COMMERCIAL ADAPTATION OF EXPERIMENTAL RESULTS

Laboratory equipment is designed to provide accurate control over a relatively wide variety of operating conditions. If it were possible to duplicate laboratory control on a commercial scale, laboratory results could, of course, be duplicated with mathematical accuracy. Such, however, is rarely the case. In mill practice unavoidable variations or irregularities are encountered, among which may be mentioned those in acid concentration, moisture content and quality of wood, temperature rise, pressure and wetness of steam, circulation of digester liquor, and end point of cook. It must be borne in mind also that the data recorded in the tables were obtained on a much smaller scale than obtains at the mill. It is true that wherever

opportunity has offered to carry on cooks in the mill under similar conditions, similar results have been obtained. Nevertheless there is always the possibility of divergence on account of the larger volumes of commercial cooks and the greater ratio of volume of digester to surface.

In estimating the pulping characteristics of the various woods, it has necessarily been assumed that the mill operator will take advantage of the best information available as to methods of operation. Due consideration has been given, however, to variations and irregularities of mill conditions, which militate against the highest yields and quality of pulp.

APPLICATION OF DATA TO OPERATING CONDITIONS

The oven-dry weight of the wood per cubic foot, green volume, given in the summaries, may be used as a factor in converting pulp yield by weight to yield per cord or any other unit of volume. Yields per cord may be determined by multiplying the yield of pulp based on weight by the oven-dry weight of the wood per cubic foot, and the product by the number of cubic feet solid wood obtained from a cord—due attention being given the character of the wood available from the particular species. The yields of pulp to be expected per cord or per thousand board feet are not directly stated as such because it was thought advisable that the reader exercise his own judgment in interpreting the data in this respect. The volume of solid wood per cord is an uncertain figure, which may vary from as little as 50 up to 100 cubic feet, according to the kind, shape, dimensions, soundness, and mechanical condition of the material. Rossed 2-foot spruce bolts of mixed diameters ranging from 6 to 14 inches contain slightly over 100 cubic feet per cord, and 100 cubic feet is assumed in figuring yields. Four-foot rossed bolts run 2 to 3 per cent less, 4-foot peeled bolts about 7 per cent less, and 4-foot rough bolts from 20 to 25 per cent less. The solid cubical content of mill waste varies enormously. Frequently 2 cords of mill waste will be found to yield only as much solid wood as 1 cord of 4-foot round bolts with the bark on.

The yield of oven-dry pulp is given in percentage of the oven-dry weight of the chips. Yields of less than 40 per cent are, in general, too low for profitable production, especially from woods lighter than 22 or 23 pounds to the cubic foot. Bleachability, discussed later, is a factor entering into calculations in this connection.

The physical characteristics of the species under consideration are not dwelt upon, such information being readily available in various works on forestry and on properties and uses of wood. They are, however, of especial importance in so far as they affect the ease with which the wood may be chipped and the bark removed; many species which may be easily pulped are rejected on account of the difficulty in handling them in the wood room.

In considering the suitability of a species in a given locality for pulp-making purposes, account should be taken of its growth habits, since the same species often varies greatly in properties with the latitude, altitude, character of soil, and other conditions of its environment.

Neither the durability of a species (i. e., resistance to decay) nor its susceptibility to insect attack is covered in this report, although

both are of immense importance from a practical standpoint, since it is customary to keep on hand at the mills at least one year's supply of pulp wood, and since much of the wood is in storage for considerably longer periods. Balsam fir, for example, shows admirable pulping qualities by any of the processes and yet is not well regarded by the industry, for the reason that it is very susceptible to both insect attack and decay. Although red alder is a wood excellently adapted to the manufacture of soda pulp, unless methods of handling can be devised whereby loss from its excessive susceptibility to decay may be avoided its use as a pulp wood will remain out of the question. Reference works on the pathological and entomological characteristics of various species are available and should be consulted in any particular case.

The fiber lengths stated are the averages of such measurements, often very limited in number, as have been made by the Forest Service or, where Forest Service measurements are not available, by other investigators. They offer only an indication of what may be expected from the species given. Since many of these measurements were made the significance of a further element, namely, the position of the fibers in the tree with reference to height, has been investigated in considerable detail. It has been found that the fiber length in one tree may vary from 0.8 to 7.65 millimeters⁴ or even from 0.3 to 8.6 millimeters.⁵ The length of the fibers undoubtedly affects the character of the pulp obtainable. The fineness of the fiber is also a very important characteristic.

Physical properties, however, considered alone, may lead to contradictory conclusions. Thus rather poor and tender pulps were obtained from redwood with a fiber length of 5½ millimeters, whereas an extremely tough and durable sheet was obtained from yellow birch sulphate pulp with a fiber length of only 1½ millimeters. The substance forming the fiber is of great importance in this respect and varies with different species as well as with different treatments.

The information on color and quality given in the summaries under the heading "Unbleached pulp" has particular reference to uses in which bleaching is not ordinarily practiced. Sulphite pulp, for instance, is often used without bleaching, as in conjunction with mechanical pulp in the manufacture of newsprint, and for that reason it must be light in color and free from shives. Sulphate pulp for wrapping paper is seldom bleached.

In other large uses, however, bleaching qualities are important. Exceptionally well-operated mills bleach spruce sulphite with as little as 10 per cent of bleaching powder of standard strength, but the average is well over 15 per cent. Some mills are using as much as 25 per cent on pulp obtained from the species available and yet are showing a profit.

Under the characteristics of sulphate pulps from the pines the bleach consumption in two stages is often shown. Tests indicated that in this case the consumption was only half that required in one stage and the color obtained was a purer white. Not all species were so tested, however, and the fact that the bleach requirement for two steps is not mentioned does not mean that better results

⁴ GERRY, E. MICROSCOPY OF PULPWOODS. Paper, Apr. 21, 1920.

⁵ LEE, H. N., and SMITH, E. M. DOUGLAS FIR FIBER, ETC. For. Quart., Dec., 1916,

might not occasionally be obtained by that procedure. It was found, however, that the advantages did not hold for sulphite.

In the soda process, the color of the unbleached pulp is not mentioned, since the pulp is almost invariably bleached before using.

In sulphate pulps from conifers strength is the outstanding requirement, although bleaching qualities are coming into account as the use of the bleached product increases.

With mechanical pulps color is the major consideration and sheet-forming qualities are important. Strength is also a desideratum, since the stronger the pulp the less sulphite is required to manufacture paper of specified strength. Many species otherwise suitable are not economically feasible for mechanical pulp on account of the power required in grinding. Power consumption may therefore be the controlling factor.

The power requirements given in the summaries for the various species apply to the production of ground wood of standard strength. On account of local conditions it may prove advisable to grind coarser or weaker pulps in order to use less power and gain in production and make up for the lower strength of the paper by using more sulphite.

When the establishment of a plant in an area new to the industry is in contemplation it is advisable to obtain pulping and paper-making tests on representative local samples of the species the use of which is intended. It is, of course, obvious that a complete survey of the locality should be made to ascertain the amounts of suitable species available, their rapidity of growth, the distribution and character of stands, etc. There should also be an economic survey of the supply of labor, living conditions, freight rates to centers of consumption, character and quantity of water available, and cost of fuel and power.

SUMMARIES BY SPECIES

Yields in all cases refer to the oven-dry weight of the pulp and are based on the oven-dry weight of the wood. Bleach requirements are expressed as percentages of the oven-dry weight of the pulp.

In the discussion of the coniferous species no mention is made of soda pulp, for the reason that strength and susceptibility to bleach, the most important qualities of the conifers, are better brought out by the sulphate than by the soda process.

1. THE SPRUCES

BLACK SPRUCE (*Picea mariana*)

Other names in use.—Double spruce and spruce pine. In the trade the wood is often mixed with red and white spruce and called eastern spruce.

Range.—Labrador to the MacKenzie River, and northwestward into Alaska; southward through Newfoundland, eastern Canada, Michigan, Wisconsin, Minnesota to central Pennsylvania, and in the northeastern mountains to northern Virginia.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—2.6 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Strong, of fine texture and excellent color, although occasionally somewhat pitchy; bleached easily to excellent white.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

Uses to which pulp is suited: News, wrapping, book, high-grade printing, and bond paper.

By Sulphate Process

Reduces readily.

Unbleached pulp: Strong, of fine texture.

Yields: 45 to 50 per cent of strong pulp.

Bleaching properties probably similar to those of white spruce.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: Comparable to that for white spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

BLUE SPRUCE (*Picea pungens*, FORMERLY *P. parryana*)

Other names in use.—Parry's spruce, white spruce, silver spruce, and Colorado blue spruce.

Range.—Central Rocky Mountain region—Colorado, eastern Utah, southern and northwestern Wyoming, and northern New Mexico and Arizona.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—2.8 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Strong, of fine texture and excellent color; bleaches easily to excellent white.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

Uses to which pulp is suited: News, wrapping, book, high-grade printing, and bond papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Strong, of fine texture.

Yields: 45 to 50 per cent of strong pulp; 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 15 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: Comparable to that for white spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

ENGELMANN SPRUCE (*Picea engelmannii*)

Other names in use.—White spruce, balsam, mountain spruce, and silver spruce.

Range.—From southeastern and northern Arizona and southern New Mexico northward through the Rocky Mountain region to British Columbia, and westward to the eastern slopes of the Cascade Mountains in Oregon and Washington.

Oven-dry weight per cubic foot, green volume.—21 pounds,

Fiber length.—3 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Strong, of fine texture and excellent color; bleaches easily to excellent white.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

Uses to which pulp is suited: News, wrapping, book, high-grade printing, and bond papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Strong, of fine texture.

Yields: 45 to 50 per cent of strong pulp.

Bleaching properties probably similar to those of white spruce.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: Comparable to that for white spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

NORWAY SPRUCE (*Picea abies*, FORMERLY *P. excelsa*)

Other names in use.—Spruce, fir, common spruce, and white fir.

Range.—From the Urals and Lapland to the Pyrenees and Alps. Planted in the eastern United States.

Oven-dry weight per cubic foot, green volume.—30 pounds.

Fiber length.—-----

By Sulphite Process

Reduces readily.

Unbleached pulp: Strong, of fine texture and excellent color; bleaches easily to excellent white.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

Uses to which pulp is suited: News, wrapping, book, high-grade printing, and bond papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Strong, of fine texture.

Yields: 45 to 50 per cent of strong pulp; 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 15 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: Comparable to that for white spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

RED SPRUCE (*Picea rubra*, formerly *P. rubens*)

Other names in use.—Yellow spruce. Trade names of the lumber are eastern spruce, West Virginia spruce, Canadian spruce, and Adirondack spruce.

Range.—Prince Edward Island southward to the coast of Massachusetts and through New England and New York and northern Pennsylvania to North Carolina and Tennessee (high mountains). Range imperfectly known. Over three-fourths of the present stand is in New England and New York.

Oven-dry weight per cubic foot, green volume.—24 pounds.

Fiber length.—3.7 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Strong, of fine texture and excellent color, although occasionally somewhat pitchy; bleaches easily to excellent white.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

Uses to which pulp is suited: News, wrapping, book, high-grade printing, and bond papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Strong, of fine texture.

Yields: 45 to 50 per cent of strong pulp.

Bleaching properties probably similar to those of white spruce.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: Comparable to that for white spruce.

Uses to which pulp is suited: Practically all uses requiring round wood.

SITKA SPRUCE (*Picea sitchensis*)

Other names in use.—Tideland spruce and western spruce. Trade names of the lumber are Sitka spruce, yellow spruce, silver spruce, and west coast spruce.

Range.—Pacific coast region (extending inland about 50 miles) from the east end of Kadiak Island and Alaska to northern California.

Oven-dry weight per cubic foot, green volume.—24 pounds.

Fiber length.—3.5 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Strong and of excellent color, texture not quite so fine as that of white spruce; bleaches easily to excellent white.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

Uses to which pulp is suited: News, wrapping, book, high-grade printing, and bond papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Strong, of fairly fine texture.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 15 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Slightly grayish in color and of standard strength.

Power required: Comparable to that for white spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

WHITE SPRUCE (*Picea glauca*, formerly, *P. canadensis*)

Other names in use.—Single spruce, cat spruce, skunk spruce, and blue spruce. The lumber, mixed with that of red spruce, is sold as eastern spruce.

Range.—Labrador to Hudson Bay and northwestward through Alaska to Bering Strait; southward in the Atlantic region to Maine, New Hampshire, Vermont, northern New York, Michigan, Wisconsin, and Minnesota.

Oven-dry weight per cubic foot, green volume.—24 pounds.

Fiber length.—2.8 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Strong, of fine texture and excellent color, although occasionally somewhat pitchy; bleaches easily to excellent white.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

Uses to which pulp is suited: News, wrapping, book, high-grade printing, and bond papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong, of fine texture.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 15 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: 60 to 80 horsepower-days per ton (in actual commercial practice).

Uses to which pulp is suited: Practically all uses requiring ground wood.

2. THE PINES

LIMBER PINE (*Pinus flexilis*)

Other names in use.—White pine and Rocky Mountain pine.

Range.—Chiefly in Rocky Mountain region from Alberta and Montana to western Texas and New Mexico; westward in mountains of northern Arizona, Utah, Nevada, and California.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—-----

By Sulphite Process

Does not reduce satisfactorily.

By Sulphate Process

Reduces readily.

Unbleached pulp; strong.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: More than 20 per cent in one stage, or 15 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber boards.

By Mechanical Process

Reduces readily.

Pulp: Of good color and standard strength; somewhat pitchy.

Power required: 30 to 40 per cent more than for white spruce.

Uses to which pulp is suited: Limited chiefly by content of pitch.

PIÑON (*Pinus edulis*)

Other names in use.—Nut pine, piñon pine, and scrub pine.

Range.—From central Colorado southward to western Texas and western Oklahoma; westward to eastern Utah, and through New Mexico to northern, central, and southeastern Arizona; mountains of northern Mexico; Lower California.

Oven-dry weight per cubic foot, green volume.—31 pounds.

Fiber length.—2 mm.

By Sulphite Process

Reduces with difficulty. Too much resin for uniform cooking.

Unbleached pulp: Of fair strength and color. Somewhat shivy, often pitchy.

Yields: 40 to 45 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Possibly wrapping papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Fairly strong but somewhat shivy.

Yields: 40 to 45 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Probably too pitchy and knotty for grinding.

SUGAR PINE (*Pinus lambertiana*)

Other names in use.—California sugar pine and big pine.

Range.—Northwestern Oregon to southern and Lower California. The heaviest stands are found from Tulare to Eldorado counties in California.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—4.1 mm.

By Sulphite Process

Reduces readily but unevenly.

Unbleached pulp: Of dull greenish-brown color and fair strength. Shivy and harsh.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Wrapping papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: More than 20 per cent in one stage, or 15 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Probably similar to that of northern white pine.

NORTHERN WHITE PINE (*Pinus strobus*)

Other names in use.—White pine, eastern white pine, Wisconsin white pine, Minnesota white pine, Canadian white pine, and cork pine. The term "white pine" is also often applied in the trade to other species of pine the wood of which more or less resembles northern white pine in appearance and quality.

Range.—From Newfoundland to Lake Winnipeg and southward through the Lake States, the New England States, and the Appalachians as far south as northern Georgia.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—4.1 mm.

By Sulphite Process

Reduces fairly readily but unevenly.

Unbleached pulp: Dull greenish brown in color; shivy and harsh.

Yields: 50 to 55 per cent.

Bleach required: More than 25 per cent.

Uses to which pulp is suited: Limited chiefly by dark color, shiviness, and harshness.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 15 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: of good color and standard strength, but pitchy.

Power required: 30 to 40 per cent more than for white spruce.

Uses to which pulp is suited: Limited chiefly by content of pitch.

JACK PINE (*Pinus banksiana*, formerly, *P. divaricata*)

Other names in use.—Scrub pine, gray pine, banksiana pine, and Hudson Bay pine.

Range.—Nova Scotia to northern New Hampshire and west through the Great Lakes and southern shores of Hudson Bay region to Great Bear Lake, Mackenzie River, and Rocky Mountains; south into northern Maine, northern New Hampshire, and Vermont, northern New York, Michigan, northern Illinois, Wisconsin, and central and southeastern Minnesota.

Oven-dry weight per cubic foot, green volume.—24 pounds.

Fiber length.—2.5 mm.

By Sulphite Process

Reduces readily but unevenly.

Unbleached pulp: Of good color and strength and fine texture, but shivy and pitchy.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Wrapping and printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong and of fine texture.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: More than 20 per cent in one stage, or 15 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces fairly readily.

Pulp: Grayish in color but of standard strength; somewhat pitchy.

Power required: 40 to 50 per cent more than for white spruce.

Uses to which pulp is suited: Limited chiefly by poor color and presence of pitch.

LOBLOLLY PINE (*Pinus taeda*)

Other names in use.—Old-field pine, rosemary pine, sap pine, Virginia pine, and bastard pine. The lumber is usually mixed with that of short-leaf pine and is sold as short leaf or North Carolina pine.

Range.—South Atlantic and Gulf States from New Jersey, southern Delaware, eastern Maryland, and eastern West Virginia to central Florida; west to eastern Texas; northward into southwestern Oklahoma, Arkansas, and southern border of middle and west Tennessee.

Oven-dry weight per cubic foot, green volume.—30 pounds.

Fiber length.—3.0 mm.

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Slightly darker than white spruce sulphite and with a decided reddish-gray tone; of fair strength, with rather coarse fibers; probably pitchy.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Wrapping and printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Of good strength. Fibers long and rather coarse.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 10 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade wrapping papers, fiber board, and book stock.

From 1 to 10 gallons (in case of selected materials) of turpentine per cord of wood cooked may be recovered from the digester relief.

By Mechanical Process

Reduces readily.

Pulp: Coarser and weaker than pulp from the spruces and inclined to be pitchy; color good from wood cut in the fall, poorer from wood cut in the spring.

Power required: 50 to 60 per cent more than for white spruce, to attain same strength of pulp.

Uses to which pulp is suited: Limited chiefly by poor color and presence of pitch.

LOGEPOLE PINE (*Pinus contorta*)⁶

Other names in use.—Scrub pine, knotty pine, Bolander's pine, Henderson's pine, tamarack, prickly pine, white pine, black pine, spruce pine, jack pine, and bird's-eye pine.

Range.—From Alaska (Yukon River) southward in the Pacific coast region to California (Mendocino County) and through interior British Columbia, the mountains of Washington and Oregon to California (Sierra Nevada to San Jacinto Mountains); plateau east of the Rocky Mountains (latitude 56°) and south through the Rocky Mountain Region to New Mexico and northern Arizona.

Oven-dry weight per cubic foot, green volume.—24 pounds.

Fiber length.—2.3 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of excellent color, fine fibered and very strong; probably somewhat pitchy; easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 45 to 50 per cent of strong pulp.

Bleaching characteristics probably similar to those of jack pine.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: 15 to 25 per cent more than for white spruce.

Uses: Practically all uses requiring ground wood.

NOTE.—The properties stated above apply to the lodgepole pine grown in the Rocky Mountain regions, which contains much less pitch than that grown in the lowlands and coastal regions. The pulping properties of the latter are similar to those of jack pine.

LONG-LEAF PINE (*Pinus palustris*)

** Other names in use.*—Long-leaf yellow pine, southern hard pine, southern heart pine, hill pine, Georgia pine, Florida pine, Texas yellow pine, North Carolina pitch pine, long-leaved pine, longstraw pine, southern yellow pine, fat pine. The lumber is usually called "pitch pine" in the export trade.

Range.—Atlantic coast region from southeastern Virginia to southern Florida and westward to eastern Texas; northward in Alabama to the northern part of the State, to northwestern Georgia, central and western Mississippi and western Louisiana almost to the northern border of the State.

Oven-dry weight per cubic foot, green volume.—34 pounds.

Fiber length.—3.7 mm.

By Sulphite Process

Long-leaf pine varies enormously in pitch content, and although selected trees might be used, it would be inadvisable to consider the use of this species on a commercial scale.

By Sulphate Process

Reduces readily.

Unbleached pulp: Strong, rather coarse, and very long fibered; requires special beater treatment to develop maximum strength. Strength is usually sacrificed to secure standard formation of sheet.

Yields: 45 to 50 per cent of strong pulp, 40 to 45 per cent of pulp for bleaching.

⁶ The Rocky Mountain form of this tree, upon which the following tests were made, was formerly and is still designated variously as *Pinus murrayana*, *P. contorta* var. *murrayana*, and *P. contorta* var. *latifolia*, the Pacific coast form being restricted to *P. contorta*. The Rocky Mountain form contains much less pitch than that from the lowlands and coastal regions. The properties of the lowland and coast form are approximately as given for jack pine.

Bleach required: 20 to 30 per cent in one stage, or 15 to 25 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

From 2 to 36 gallons (in the case of selected material) of turpentine and pine oil per cord of wood may be recovered from the digester relief.

By Mechanical Process

Not suitable for mechanical pulp on account of the high pitch content usually encountered.

MONTEREY PINE (*Pinus radiata*, formerly, *P. insignis*)

Other names in use.—Monterey pine is the name universally used for this species.

Range.—Occurs only in a few small areas near the coast of southern California.

Oven-dry weight per cubic foot, green volume.—29 pounds.

Fiber length.—-----

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Strong and of fair color; somewhat coarser than spruce sulphite pulp; fairly easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Wrapping and printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong, difficult to bleach.

Yields: 45 to 55 per cent of strong pulp.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Behavior probably similar to that of jack pine.

NORWAY PINE (*Pinus resinosa*)

Other names in use.—Red pine, hard pine, and northern pine.

Range.—From Nova Scotia to northern Ontario to southern Manitoba; southward through the Northern States to Massachusetts, southeastern Pennsylvania, northeastern Ohio, central Michigan, and northern Wisconsin; southern Wisconsin and northeastern Minnesota.

Oven-dry weight per cubic foot, green volume.—27 pounds.

Fiber length.—3.7 mm.

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Of good color, fairly fine-fibered and fairly strong; probably somewhat pitchy; fairly easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 15 to 25 per cent.

Uses to which pulp is suited: Few. Limited chiefly by content of pitch.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 45 to 55 per cent of strong pulps, 40 to 45 per cent of pulp for bleaching.

Bleach required: 30 to 40 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Behavior probably similar to that of jack pine.

PITCH PINE (*Pinus rigida*)

Other names in use.—Hard pine, yellow pine, and sap pine.

Range.—From the coast of Maine to eastern Ontario, and southward in the Atlantic coast region to southern Virginia and along the mountains to northern Georgia; west to western New York, northeastern and northwestern Pennsylvania, eastern Ohio and Kentucky, and eastern Tennessee.

Oven-dry weight per cubic foot, green volume.—29 pounds.

Fiber length.—-----

By Sulphite Process

Reduces with difficulty.

Unbleached pulp: Too pitchy for commercial production; bleaches with some difficulty to a fairly satisfactory quality.

Yields: 45 to 50 per cent.

Bleach required: 30 to 40 per cent.

Uses to which pulp is suited: Limited chiefly by content of pitch.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong; fibers longer and coarser than spruce.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach: 20 to 30 per cent in one stage, or 15 to 25 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers, fiber board, and book stock.

Turpentine may be recovered from the digester relief in quantities warranting consideration.

By Mechanical Process

Probably too resinous for successful grinding.

POND PINE (*Pinus rigida serotina*, formerly, *P. serotina*)

Other names in use.—Spruce pine, bastard pine, pocoson pine, bay pine, black pine, marsh pine, and meadow pine.

Range.—Atlantic coast region from southern New Jersey and southeastern Virginia to east-central Florida and probably farther south; on the west coast of Florida from Pensacola to Citrus County and probably much farther south. Range imperfectly known.

Oven-dry weight per cubic foot, green volume.—31 pounds.

Fiber length.—-----

By Sulphite Process

Reduces readily.

Unbleached pulp: Of a reddish-gray tone, about the same color as hemlock sulphite, but fibers somewhat coarser. Probably somewhat pitchy. Bleaches easily.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

Uses to which pulp is suited: Wrapping and printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Of good strength. Fibers are longer but coarser than those of spruce.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 10 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers, fiber board, and book stock.

From 1 to 10 gallons (in the case of selected material) of turpentine per cord of wood cooked may be recovered from the digester relief.

By Mechanical Process

Behavior probably similar to that of loblolly pine.

SAND PINE (*Pinus clausa*)

Other names in use.—Old-field pine, Florida spruce pine, scrub pine, and upland spruce pine.

Range.—Coast of Alabama and western Florida; east coast of Florida from St. Augustine to New River.

Oven-dry weight per cubic foot, green volume.—29 pounds.

Fiber length.—-----

By Sulphite Process

Reduces readily.

Unbleached pulp: Of good color; rather weak, with fibers of average fineness; probably somewhat pitchy; easily bleached.

Yields: 25 to 35 per cent (figures subject to modification by further investigation).

Bleach required: 10 to 20 per cent.

Uses to which the pulp is suited: Wrapping and printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Of fair strength.

Yields: 40 to 45 per cent.

Bleach required: Probably more than 20 per cent.

Uses to which the pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Behavior probably similar to that of jack pine.

SCOTCH PINE (*Pinus sylvestris*)

Other names in use.—Northern pine, Scots pine (Scotland), and Scotch fir (England).

Range.—Europe, northern Asia up to 700 feet above sea-level in the far north, 6,500 feet in southern Europe. Planted in eastern United States.

Oven-dry weight per cubic foot, green volume.—37 pounds (data from English sources).

Fiber length.—-----

By Sulphite Process

Reduces with difficulty and very unevenly.

Unbleached pulp: Of fair color but shivy; probably somewhat pitchy.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Few. Limited chiefly by content of pitch and shives.

By Sulphate Process

Reduces readily.

Unbleached pulp: Of good strength.

Yields: 40 to 45 per cent of strong pulp, 35 to 40 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, 10 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

Turpentine may probably be recovered from the digester relief in quantities sufficient to warrant consideration.

By Mechanical Process

Behavior probably similar to that of jack pine.

VIRGINIA PINE (*Pinus virginiana*)

Other names in use.—Scrub pine, Jersey pine, and spruce pine. The lumber is often sold as North Carolina pine.

Range.—Mainly from central and southern New Jersey and central, southern, and western Pennsylvania to Georgia and northern Alabama; west into Ohio, southern Indiana, northeastern Mississippi, and middle Tennessee.

Oven-dry weight per cubic foot, green volume.—26 pounds.

Fiber length.—2.8 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of about the same color as hemlock sulphite, but with somewhat coarser fibers: probably pitchy.

Yields: Probably 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Wrapping and printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Of good strength; fibers longer and coarser than those of spruce.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 10 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers, fiber board, and book stock.

From 1 to 10 gallons (in the case of selected material) of turpentine per cord of wood may be recovered from the digester relief.

By Mechanical Process

Reduces readily.

Pulp: Coarser than spruce pulp, and pitchy.

Power required: 50 to 60 per cent more than for white spruce, to obtain the same strength of product.

Uses to which pulp is suited: Limited chiefly by content of pitch.

SHORT-LEAF PINE (*Pinus echinata*)

Other names in use.—Yellow pine, short-leaved pine, spruce pine, and bull pine. The lumber frequently goes under the name of North Carolina pine.

Range.—From southeastern New York to western Florida, and westward into West Virginia, southern Illinois, southern Missouri, eastern Oklahoma, and eastern Texas.

Oven-dry weight per cubic foot, green volume.—31 pounds.

Fiber length.—3.7 mm.

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Fairly strong; of the same color as hemlock sulphite, but with somewhat coarser fibers; probably pitchy.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Wrapping papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Fairly strong; fibers longer and coarser than those of spruce.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 10 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers, fiber board, and book stock.

From 1 to 10 gallons (in the case of selected materials) of turpentine per cord of wood may be recovered from the digester relief.

By Mechanical Process

Behavior similar to that of scrub pine.

Pulps obtained from wood cut in the fall have good color, those from wood cut in the spring considerably poorer color.

Uses to which pulp is suited: Limited chiefly by content of pitch.

SLASH PINE (*Pinus caribaea*, formerly, *P. cubensis* and *P. heterophylla*).

Other names in use.—Swamp pine, bastard pine, meadow pine, pitch pine, spruce pine, and saltwater pine.

Range.—Atlantic coast region (60 to 100 miles inland) from South Carolina to southern Florida; westward in the coast region of the Gulf States to eastern Louisiana.

Oven-dry weight per cubic foot, green volume.—37 pounds.

Fiber length.—-----

By Sulphite Process

Probably too resinous for consideration.

By Sulphate Process

Reduces readily.

Unbleached pulp: Strong; fibers rather long and coarse.

Yields: 45 to 50 per cent of strong pulp.

Bleach required: 20 to 30 per cent in one stage, or 10 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

From 2 to 30 gallons of turpentine and pine oil per cord of wood may be recovered from the digester relief.

On account of its rapid growth, the high quality of lumber obtained from it, its large yields of rosin, turpentine, and pine oil, and the ease with which it reduces to an easy-bleaching pulp, slash pine is worthy of consideration for replanting areas with a view to establishing a group of industries related to each other and dependent on a self-perpetuating supply of wood.

By Mechanical Process

Probably too resinous for consideration.

WESTERN YELLOW PINE (*Pinus ponderosa*)

Other names in use.—Yellow pine and bull pine. The lumber is sold under various trade names, including western pine, western soft pine, western white pine, California white pine, Oregon white pine, Washington white pine, Montana pine, Arizona soft pine, Arizona white pine, New Mexico white pine, Mexican white pine, British Columbia white pine, and ponderosa pine.

Range.—From British Columbia and the Black Hills of South Dakota southward in the Pacific and Rocky Mountain region to western Texas, northwestern Nebraska, and Mexico.

Oven-dry weight per cubic foot, green volume.—24 pounds.

Fiber length.—3.6 mm.

By Sulphite Process

Reduces fairly readily but unevenly.

Unbleached pulp: Dark in color, and shivvy.

Yields: 45 to 50 per cent.

Bleach required: Probably more than 20 per cent.

Uses to which pulp is suited: Limited chiefly by dark color and content of pitch and shives.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong, the long, fine fibers having exceptionally good felting properties.

Yields: 45 to 50 per cent.

Bleach: Probably more than 25 per cent.

Probably enough turpentine may be recovered from the digester relief to warrant consideration.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces fairly readily.

Pulp: Of satisfactory color and soft texture, but coarser than spruce pulp; probably pitchy.

Power required: 40 to 50 per cent more than for spruce, to obtain pulp of the same strength.

Uses to which pulp is suited: Limited by coarseness and pitchiness.

PEHUEN (*Araucaria aurocana*, formerly, *A. imbricata*)

Other names in use.—Native names for this species are pehuen and piño piñon. In English-speaking countries it is commonly referred to as Araucaria pine and monkey-puzzle.

Range.—Southern Brazil, Argentina, Chile.

Oven-dry weight per cubic foot, green volume.—33 pounds.

Fiber length.—-----

By Sulphite Process

Reduces readily.

Unbleached pulp: Light brown in color and of fair strength.

Yields: 45 to 55 per cent.

Bleach required: Probably more than 20 per cent.

Uses to which pulp is suited: Wrapping papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Of good strength, but somewhat softer than spruce sulphate.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent in one stage, or 10 to 20 per cent in two stages.

Uses to which pulp is suited: Kraft wrapping papers and fiber board.

By Mechanical Process

Probably yields a fair grade of pulp of about the color of jack pine ground wood, with reasonable consumption of power.

3. THE FIRS

ALPINE FIR (*Abies lasiocarpa*)

Other names in use.—Sub-alpine fir, balsam, white fir, white balsam, Oregon balsam-tree, pumpkin tree, mountain balsam, black balsam, and balsam fir.

Range.—Rocky Mountain region from northern Arizona; southwestern New Mexico to Montana and Idaho, and westward through the mountains of Oregon and Washington and northward to Alaska: high ranges of British Columbia and Alberta.

Oven-dry weight per cubic foot, green volume.—21 pounds.

Fiber length.—-----

By Sulphite Process

Reduces readily.

Unbleached pulp: Of excellent color and strength, easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 10 to 15 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 45 to 50 per cent of strong pulp, 40 to 45 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: 15 to 25 per cent more than for spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

BALSAM FIR (*Abies balsamea*)

Other names in use.—Balsam, Canada balsam, Balm of Gilead fir, blister pine, fir pine, firtree, single spruce, silver pine, and she-balsam. The lumber is frequently called eastern fir in the market.

Range.—From Newfoundland and Labrador to Hudson Bay and northwestward to the Great Slave Lake region, and south to Pennsylvania (and along high mountains to Virginia), Michigan, Minnesota, and northeastern Iowa.

Oven-dry weight per cubic foot, green volume.—21 pounds.

Fiber length.—2.7 mm.

By Sulphite Process

Reduces readily under slightly milder conditions than are required for spruce.

Unbleached pulp: Of good color and excellent strength, but slighter softer, as a rule, than spruce sulphite; fairly easily bleached.

Yields: 45 to 50 per cent.

Bleached required: 15 to 25 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: very strong.

Yields: 45 to 50 per cent of strong pulp, 40 to 45 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength. On account of the susceptibility of this species to insect attack and decay, inferior pulps are often obtained which are not characteristic of the sound wood.

Power required: 15 to 25 per cent more than for white spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

LOWLAND WHITE FIR (*Abies grandis*)

Other names in use.—White fir, silver fir, yellow fir, Oregon white fir, western white fir, great silver fir, and balsam fir.

Range.—Pacific coast region from Vancouver Island to western California and from Washington and Oregon to northern Idaho and Montana.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—3.2 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of excellent color and strength; fibers somewhat coarser than spruce fibers; fairly easily bleached.

Yields: 45 to 55 per cent.

Bleach required: 15 to 25 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 45 to 50 per cent of strong pulp, 35 to 45 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color.

Power required: 15 to 25 per cent more than for white spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

NOBLE FIR (*Abies nobilis*)

Other names in use.—Red fir, larch, noble fir, and bigtree.

Range.—Western Washington and Oregon and northern California.

Oven-dry weight per cubic foot, green volume.—22 pounds.

Fiber length.—-----

By Sulphite Process

Reduces readily.

Unbleached pulp: Of excellent color and strength; fibers fine and tough; easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 10 to 15 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduces readily.

Yields: 45 to 50 per cent of strong pulp, 40 to 45 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: 20 per cent less than for spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

RED FIR (*Abies magnifica*)

Other names in use.—California red-bark fir and California red fir.

Range.—California (Sierra Nevada Mountains) and northward in the Cascade Mountains of southern Oregon.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—-----

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Very strong, darker than spruce sulphite but lighter than hemlock sulphite; fibers fairly fine; fairly easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 15 to 25 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: More than 30 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Color slightly reddish; of standard strength.

Power required: 15 to 25 per cent more than for spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood, except as limited by dark color.

SILVER FIR (*Abies amabilis*)

Other names in use.—Red fir, red silver fir, fir, and larch.

Range.—From southeastern Alaska to Vancouver Island and British Columbia and southward in the Cascade Mountains to northern Oregon; also in the coast mountains of Washington and Oregon.

Oven-dry weight per cubic foot, green volume.—22 pounds.

Fiber length.—-----

By Sulphite Process

Reduces readily.

Unbleached pulp: Of excellent color and strength; fairly easily bleached.

Yields: 45 to 50 per cent.

Bleached required: 20 to 30 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduced readily.

Unbleached pulp: Very strong, long fibered.

Yields: 48 to 53 per cent of strong pulp.

Bleaching properties probably similar to those of noble fir.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Behavior similar to that of white spruce.

WHITE FIR (*Abies concolor*)

Other names in use.—Balsam fir, silver fir, white balsam, bastard pine, and blue fir.

Range.—Southwestern Oregon to southern California; northern Arizona and New Mexico to Colorado and northern Utah.

Oven-dry weight per cubic foot, green volume.—22 pounds.

Fiber length.—3.5 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of excellent color and strength; fibers larger and somewhat coarser than spruce fibers; easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 10 to 15 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 48 to 53 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength. Pulps from young trees are usually of better quality than from old trees on account of the susceptibility of this species to heart rot.

Power required: 15 to 20 per cent more than for white spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

DOUGLAS FIR (*Pseudotsuga taxifolia*)

Other names in use.—Red fir, yellow fir, Oregon pine, Douglas spruce, red pine, Puget Sound pine, Santiam quality fir, and red spruce.

Range.—From the Rocky Mountain region (in the United States) and northward to central British Columbia; westward to the Pacific coast and southward into northern Mexico and the mountains of western Texas. Over one-half of the present stand is in western Washington and Oregon.

Oven-dry weight per cubic foot, green volume.—28 pounds.

Fiber length.—4.4 mm.

By Sulphite Process

Reduces with difficulty on account of the pitchy character of the wood.

Unbleached pulp: Of fair strength and poor color; probably somewhat pitchy.

Yields: 45 to 50 per cent.

Bleach required: 20 to 25 per cent.

Uses to which the pulp is suited: Limited chiefly by poor color and content of pitch.

By Sulphate Process

Reduces readily.

Unbleached pulp: Fairly strong.

Yields: 45 to 50 per cent.

Probably enough turpentine can be recovered from the digester relief to warrant consideration.

Uses to which pulp is suited: Kraft wrapping papers and fiber board which do not require maximum strength.

By Mechanical Process

Too resinous for grinding.

4. HEMLOCKS AND OTHER CONIFERS

CAROLINA HEMLOCK (*Tsuga caroliniana*)

Other names in use.—Spruce pine, hemlock, and hemlock spruce.

Range.—Mountains of southwestern Virginia and western North Carolina to northern Georgia; very local.

Oven-dry weight per cubic foot, green volume.—30 pounds.

Fiber length.—-----

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Slightly lighter in color than eastern hemlock sulphite, but otherwise similar; fairly easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Same as for eastern hemlock.

By Sulphate Process

Reduces readily.

Unbleached pulp: Strong.

Yields: 45 to 50 per cent of strong pulp, 35 to 40 per cent of pulp for blenching.

Bleach: More than 30 per cent.

Uses to which pulp is suited: Same as for eastern hemlock.

By Mechanical Process

Behavior probably similar to that of eastern hemlock.

EASTERN HEMLOCK (*Tsuga canadensis*)

Other names in use.—Hemlock, hemlock spruce, and spruce pine.

Range.—Nova Scotia to eastern Minnesota, to southwestern Wisconsin, southern Michigan, and Indiana; southward in the Atlantic coast region to Delaware and Maryland, and southward along the mountains to northern Alabama and Georgia.

Oven-dry weight per cubic foot, green volume.—24 pounds.

Fiber length.—3 mm.

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Very strong, as compared with spruce sulphite; darker in color and with a decided reddish-gray tone; fibers somewhat coarser and more readily hydrated in the beater; fairly easily bleached.

Yields: 40 to 45 per cent.

Bleach required: 15 to 25 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 45 to 50 per cent of strong pulp, 40 to 45 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent in one stage, or 10 to 20 per cent in two stages.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces fairly readily.

Pulp: Slightly reddish in color, somewhat brittle.

Power required: 50 to 60 per cent more than for white spruce, to obtain standard strength.

Uses to which pulp is suited: As partial substitute for white spruce ground wood.

WESTERN HEMLOCK (*Tsuga heterophylla*)

Other names in use.—Hemlock, western hemlock, hemlock spruce, and Alaska pine. In the lumber trade the wood is often called West coast and Pacific hemlock. In England it is largely known as western hemlock fir and Prince Albert's fir.

Range.—From southeastern Alaska to northern Idaho and northwestern Montana, and southward in Washington and western Oregon to northwestern California. The best stands are found in the coast region and through the Cascade Mountains at an elevation of 1,500 to 3,500 feet.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—2.7 mm.

By Sulphite Process

Reduces readily, more like spruce than eastern hemlock.

Unbleached pulp: Tough and strong; much lighter in color and finer in texture than eastern hemlock.

Yield: 45 to 50 per cent.

Bleach required: 15 to 25 per cent.

Uses to which pulp is suited: News, wrapping, book, and high-grade printing papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong and tough.

Yields 45 to 50 per cent of strong pulp.

Bleaching properties probably similar to those of eastern hemlock.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Of excellent color and standard strength.

Power required: 10 to 15 per cent more than for spruce.

Uses to which pulp is suited: Practically all uses requiring ground wood.

TAMARACK (*Larix laricina* FORMERLY *L. americana*)

Other names in use.—Larch, hackmatack, and American larch.

Range.—From Newfoundland and Labrador northward, through the Hudson Bay region, to the Mackenzie River and reappearing in Alaska between Cook Inlet and the Yukon River; southward in the East to northern and eastern Pennsylvania, western Maryland, northeastern West Virginia, northern Ohio, Indiana, and Illinois, and northeastern Minnesota; in western Canada extending southward along the eastern base of the Rockies.

Oven-dry weight per cubic foot, green volume.—31 pounds.

Fiber length.—2.6 mm.

By Sulphite Process

Reduces with difficulty.

Unbleached pulp: Brash, shivy, and dark in color; fairly easily bleached to satisfactory product.

Yields: 40 to 45 per cent.

Bleach required: 15 to 25 per cent.

Uses to which pulp is suited: Low-grade wrapping papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong and tough.

Yields: 45 to 50 per cent of strong pulp, 35 to 40 per cent of pulp for bleaching.

Bleach required: 25 to 30 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces readily.

Pulp: Light grayish green in color.

Power required: 40 to 50 per cent more than for white spruce to obtain standard strength.

Uses to which pulp is suited: Practically all uses requiring ground wood.

WESTERN LARCH (*Larix occidentalis*)

Other names in use.—Larch, tamarack, hackmatack, red American larch, and western tamarack. The lumber is variously called western larch, Montana larch, Oregon larch, and British Columbia tamarack.

Range.—Southern British Columbia and south in the Cascade Mountains to the Columbia River, and to western Montana; also in southeastern Washington, northeastern Oregon, and northern Idaho.

Oven-dry weight per cubic foot, green volume.—28 pounds.

Fiber length.—2.6 mm.

By Sulphite Process

Reduces with difficulty and very unevenly.

Unbleached pulp: Brash, shivv, and dark in color; bleaches to fairly satisfactory product.

Yields: 40 to 45 per cent of pulp for bleaching.

Bleach required: 15 to 25 per cent.

Uses to which pulp is suited: Low-grade wrapping papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Very strong.

Yields: 45 to 50 per cent of strong pulp.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Reduces with difficulty.

Pulp: Rather coarse, decidedly brown in color.

Power required: Two and half times more than for white spruce, to obtain standard strength.

Uses to which pulp is suited: Limited by poor color and coarseness.

INCENSE CEDAR (*Libocedrus decurrens*)

Other names in use.—Cedar, post cedar, bastard cedar, and California post cedar.

Range.—From northwestern Oregon southward through California into Mexico and Lower California. The commercial range is confined largely to the mountains of northern California and southern Oregon.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—2 mm.

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Very dark in color; bleaches with difficulty.

Yields: 40 to 45 per cent.

Bleach required: More than 35 per cent.

Uses to which pulp is suited: Limited chiefly by poor color.

By Sulphate Process

Reduces readily. Best results obtained at cooking temperatures corresponding to steam pressures below 80 pounds per square inch.

Unbleached pulp: Fine fibered and very strong, but strength easily impaired by too high temperatures during cooking.

Yields: 40 to 45 per cent of strong pulp, 35 to 40 per cent of pulp for bleaching.

Bleach required: More than 30 per cent.

Uses to which pulp is suited: Kraft wrapping papers and fiber board.

By Mechanical Process

Pulp too dark for ordinary ground-wood uses.

PORT ORFORD CEDAR (*Chamaecyparis lawsoniana*)

Other names in use.—Lawson's cypress, Oregon cedar, ginger pine, and white cedar.

Range.—Pacific coast region from southwestern Oregon to northwestern California, extending inland about 40 miles. The bulk of the timber of commercial importance is confined to a strip 20 to 25 miles wide along the Pacific coast in Coos and Curry Counties, Oreg.

Oven-dry weight per cubic foot, green volume.—26 pounds.

Fiber length.—2.6 mm.

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Strong, fine fibered; rather difficult to bleach.

Yields: 45 to 55 per cent.

Bleach required: 25 to 30 per cent.

Uses to which pulp is suited: Wrapping papers and some print papers.

By Sulphate Process

Reduces readily. Best results obtained at cooking temperatures corresponding to steam pressures below 80 pounds per square inch.

Unbleached pulp: Very strong, but strength easily impaired by too high temperatures during cooking.

Yields: Not fully determined; possibly 40 to 45 per cent.

Bleach required: 25 to 30 per cent.

Uses to which pulp is suited: Kraft wrapping papers and fiber board.

By Mechanical Process

Probably unsuited to grinding because of color and nature of the wood.

SOUTHERN WHITE CEDAR (*Chamaecyparis thyoides*)

Other names in use.—White cedar, swamp cedar, post cedar, and juniper.

Range.—Atlantic coast region from southern Maine to northern Florida westward to Mississippi (Pearl River).

Oven-dry weight per cubic foot, green volume.—20 pounds.

Fiber length.—2.1 mm.

By Sulphite Process

Pulping characteristics probably similar to those of Port Orford cedar.

By Sulphate Process

Reduces readily. Best results obtained at cooking temperatures corresponding to pressures below 80 pounds per square inch.

Unbleached pulp: Very strong, but strength easily impaired by too high temperatures during cooking.

Yields: 45 to 50 per cent of strong pulp, 38 to 43 per cent of pulp for bleaching.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Probably reduces readily to satisfactory pulps with reasonable power consumption.

EASTERN RED CEDAR (*Juniperus virginiana*)

Other names in use.—Cedar, juniper, and savin. Trade names for the wood are eastern red cedar and Tennessee red cedar.

Range.—Nova Scotia and New Brunswick to Georgia (coast), southern Alabama and Mississippi; west in Ontario (Georgian Bay) to eastern North and South Dakota, southern Michigan, eastern Nebraska and Kansas, southeastern Oklahoma, southwestern Arkansas, and eastern Texas.

Oven-dry weight per cubic foot, green volume.—27 pounds.

Fiber length.—2.8 mm.

By Sulphite Process

Wood too oily for reduction to satisfactory pulp.

By Sulphate Process

Reduces readily. Cooking temperatures corresponding to 80 pounds steam pressure should not be exceeded. The knotty character of the wood and the smallness of the average bolt would offer difficulties in the wood room.

Unbleached pulp: Strength easily impaired by too high cooking temperatures; practically impossible to bleach.

Yields: 40 to 45 per cent.

From 5 to 10 gallons of cedar oil per cord of wood may be recovered from the digester relief.

Uses to which pulp is suited: Kraft wrapping papers.

By Mechanical Process

Wood too dark in color, too oily, and too knotty for the production of satisfactory pulp.

WESTERN RED CEDAR (*Thuja plicata*)

Other names in use.—Red cedar, canoe cedar, arborvitae, shinglewood, gigantic, cedar, Pacific red cedar, and western cedar.

Range.—From the coast of southern Alaska to northern California; eastward through British Columbia and northern Washington to northern Idaho and Montana.

Oven-dry weight per cubic foot, green volume.—19 pounds.

Fiber length.—3.8 mm.

By Sulphite Process

Pulp: Dark in color, shivy, and practically impossible to bleach.

Uses to which pulp is suited: Limited chiefly by poor color and shiviness.

By Sulphate Process

Reduces readily. It is probable that the digester pressure during cooking should not exceed 90 pounds per square inch.

Unbleached pulp: Very strong.

Yields: 40 to 45 per cent.

Uses to which pulp is suited: High-grade kraft wrapping papers and fiber board.

By Mechanical Process

Wood too dark for production of satisfactory pulp.

SOUTHERN CYPRESS (*Taxodium distichum*)

Other names in use.—Cypress, bald cypress, red cypress, black cypress, white cypress, yellow cypress, and Gulf cypress.

Range.—From southern Delaware southward in the Atlantic coast region to southern Florida; westward in the Gulf Coast region to western Texas, and northward through Louisiana to Oklahoma, Arkansas, northern and western Mississippi and Tennessee, southeastern Missouri, western Kentucky, southern Illinois, and southwestern Indiana. The greater part of the supply of this timber is in Louisiana and Florida.

Oven-dry weight per cubic foot, green volume.—27 pounds.

Fiber length.—3.3 mm.

By Sulphite Process

Reduces with difficulty.

Unbleached pulp: Fairly strong but very dark in color; difficult to bleach.

Yields: 45 to 50 per cent.

Bleach required: 25 to 35 per cent.

Uses to which pulp is suited: Limited chiefly by poor color.

By Sulphate Process

Reduces readily.

Unbleached pulp: Soft and long fibered; required careful beating to develop satisfactory strength.

Yields: 50 to 55 per cent of strong pulp, 35 to 40 per cent of pulp for bleaching.

Bleach required: More than 25 per cent.

Uses to which pulp is suited: Kraft wrapping papers and fiber board.

By Mechanical Process

Not suited to ground-wood production because of color.

REDWOOD (*Sequoia sempervirens*)

Other names in use.—Sequoia, California redwood, and coast redwood.

Range.—From the southern borders of Oregon southward in the Pacific coast region 20 to 30 miles inland) to about 100 miles south of San Francisco.

Oven-dry weight of the wood per cubic foot, green volume.—23 pounds.

Fiber length.—5.5 mm.

By Sulphite Process

Reduces readily but unevenly.

Unbleached pulp: Fairly strong but brash, shivy, dark in color, and practically impossible to bleach.

Yields: About 50 per cent.

Uses to which pulp is suited: Low-grade wrapping papers.

By Sulphate Process

Reduces readily.

Unbleached pulp: Fairly strong; fibers very long but soft and tender. Best results are obtained when chips are leached before cooking and 10 to 20 per cent of their weight extracted as a tanninlike dark red coloring substance.

Yields: 35 to 40 per cent.

Bleach required: More than 30 per cent, even when yield is reduced to 30 per cent.

Uses to which pulp is suited: No. 2 kraft wrapping paper; with very careful beating, possibly No. 1 kraft.

Both the specific gravity of the wood and the percentage yield by weight are low and combine to reduce the yield per cord below that of the coniferous woods generally pulped.

By Mechanical Process

Wood too dark for production of satisfactory pulp.

5. HARDWOODS—DIFFUSE-POROUS

Possible uses: Reference is directed to page 20 for a discussion of the uses of hardwood pulps as a group. Individual species differ as to the ease or difficulty with which pulps of satisfactory quality can be produced rather than as to specific uses for which they may be suited. Therefore no discussion of specific uses of pulps from the individual species will be attempted in the summaries.

Sulphate process: Practically all American hardwoods can be pulped by the sulphate process as readily as by the soda process. The sulphate pulps usually bleach with less bleaching powder than soda pulps; otherwise the two classes show practically no difference in quality. The soda process, however, since it was established earlier than the sulphate and operates with greater freedom from offensive odors, has remained almost without challenge for the pulping of hardwoods. Therefore the sulphate process will be referred to only incidentally in this section.

ASPEN (*Populus tremuloides*)

Other names in use.—Quaking asp, American aspen, aspen leaf, white poplar, trembling poplar, American poplar, poplar, popple, trembling aspen, and quaking aspen.

Range.—Southern Labrador to Hudson Bay (southern shores) and northward to the Mackenzie River (near mouth); southward through Northeastern

United States and in the mountains to southern Kentucky, to northern Ohio, Indiana and Illinois, eastern and central Iowa and northern Missouri.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—1 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of excellent color; usually contains small black specks, which, however, disappear on bleaching: easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 10 to 15 per cent.

By Soda Process

Reduces fairly readily.

Unbleached pulp: Bleaches easily.

Yields: 45 to 50 per cent.

Bleach required: 10 to 15 per cent.⁷

By Mechanical Process

Aspen is readily reduced to mechanical pulp, yielding 85 to 86 per cent of standard strength with approximately three times as much power as is required for spruce. Upon the introduction of the ground-wood process aspen came to be used to a considerable extent on account of the light color of the pulp. Spruce has now supplanted it because much less power is required and pulp of greater strength and better felting properties is obtained.

BALSAM POPLAR (*Populus balsamifera*)

Other names in use.—Balsam, balm of Gilead, cottonwood, and faca mahac.

Range.—Coast of Alaska and valley of Mackenzie River to Hudson Bay and Labrador; southward to northern New England and New York, central Michigan and Minnesota, northern North Dakota, western South Dakota, northwestern Nebraska, Colorado, northern Montana, Idaho, Oregon, and Nevada.

Oven-dry weight per cubic foot, green volume.—26 pounds.

Fiber length.—1 mm.

By Sulphite Process

Reduces with exceptional ease.

Unbleached pulp: Of excellent color; not contaminated with black specks characteristic of aspen; very easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 5 to 10 per cent.

By Soda Process

Reduces readily.

Unbleached pulp: Fairly easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 15 to 20 per cent.

By Mechanical Process

Behavior probably similar to that of aspen.

COTTONWOOD

Other names in use.—For the purposes of this bulletin both eastern cottonwood (*Populus deltoides*) and southern cottonwood (*P. deltoides virginiana*) are included under the name "cottonwood."

Range.—The range of eastern cottonwood is commonly recognized as northwestern Vermont, through western New York, eastern border of Pennsylvania, and central Maryland; central-eastern Mississippi. The complete range is imperfectly known. Southern cottonwood ranges from Quebec and Lake Champlain southward through western New-England to Florida; westward to southern Minnesota, the Dakotas, eastern Nebraska, Kansas, Oklahoma, and Texas.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—1.3 mm.

⁷About 7 to 12 per cent when cooked by sulphate process to yields indicated.

By Sulphite Process

Pulping properties probably similar to those of aspen, but pulp less contaminated with black specks.

*By Soda Process*⁸

Reduces readily.

Unbleached pulp: Fibers longer than those from aspen; fairly easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 15 to 20 per cent.

By Mechanical Process

Behavior similar to that of aspen.

LARGETOOTH ASPEN (*Populus grandidentata*)

Other names in use.—Poplar, largetoothed poplar, large poplar, white poplar, popple, and large American aspen.

Range.—Nova Scotia, New Brunswick, southern Quebec, and Ontario to northern Minnesota, and northeastern North Dakota; southward to Pennsylvania, Ohio, and Iowa, and along the Alleghany Mountains to North Carolina, central Kentucky and Tennessee.

Oven-dry weight per cubic foot, green volume.—22 pounds.

Fiber length.—1.1 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of excellent color; bleaches fairly readily.

Yields: 45 to 50 per cent.

Bleach required: 15 to 20 per cent.

By Soda Process

Reduces readily.

Unbleached pulp: Bleaches fairly readily.

Yields: 40 to 45 per cent.

Bleach required: 15 to 20 per cent.

By Mechanical Process

Behavior probably similar to that of aspen.

YELLOW POPLAR (*Liriodendron tulipifera*)

Other names in use.—Tulip poplar, tulip-tree, whitewood, poplar, white poplar, blue poplar, and hickory poplar.

Range.—From Rhode Island to southwestern Vermont and west to Lake Michigan; south to northern Florida, southern Alabama and Mississippi; west of Mississippi River in northeastern Louisiana, southeastern Missouri, and northeastern Arkansas.

Oven-dry weight per cubic foot, green volume.—26 pounds.

Fiber length.—1.8 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of poor color, though less contaminated with black specks than is aspen sulphite; difficult to bleach.

Yields: 45 to 50 per cent.

Bleach required: 20 to 25 per cent.

By Soda Process

Reduces fairly readily.

Unbleached pulp: Stronger than aspen pulp; fairly easily bleached.

Yields: 40 to 45 per cent.

Bleach required: 15 to 20 per cent.⁹

⁸ Tests were also made on Norway poplar (*Populus canadensis eugenei*, a hybrid) which behaves like cottonwood. Norway poplar is believed to be a cross between *P. deltoides* and *P. nigra italica*—a European species—and the resultant hybrid has been planted extensively in this country.

⁹ About 12 to 18 per cent when cooked by sulphate process to yields indicated.

By Mechanical Process

Behavior probably similar to that of aspen, but slightly less power required for pulp of standard strength.

BASSWOOD (*Tilia glabra*, formerly *Tilia Americana*)

Other names in use.—American linden, linn, lime tree, and whitewood.

Range.—New Brunswick to Lake Superior (eastern shores) and to Lake Winnipeg (southern shores) and the Assiniboine River; south to Pennsylvania, Ohio, through Michigan, Indiana, and Illinois and eastern Nebraska to Missouri.

Oven-dry weight per cubic foot, green volume.—21 pounds.

Fiber length.—1.1 mm.

By Sulphite Process

Unbleached pulp: Very shivy, incapable of satisfactory bleaching.

By Soda Process

Reduces readily.

Unbleached pulp: Fairly easy to bleach.

Yields: 45 to 50 per cent.

Bleach required: 20 to 25 per cent.¹⁰

By Mechanical Process

Behavior probably similar to that of aspen.

BLACK WILLOW (*Salix nigra*)

Other names in use.—Swamp willow and willow. The lumber is usually called willow.

Range.—Southern New Brunswick, Quebec and Ontario to Georgia and central Alabama; west to southeastern North Dakota, eastern South Dakota, Nebraska, Kansas, Oklahoma, southwestern Arkansas, western Texas.

Oven-dry weight per cubic foot, green volume.—21 pounds.

Fiber length.—0.8 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of excellent color, somewhat contaminated with black specks; fairly easily bleached.

Yields: 50 to 55 per cent.

Bleach required: 15 to 20 per cent.

By Soda Process

Reduces readily.

Unbleached pulp: Fairly easy to bleach.

Yields: 45 to 50 per cent.

Bleach required: 15 to 20 per cent.

By Mechanical Process

Behavior probably similar to that of aspen.

SANDBAR WILLOW (*Salix longifolia*, formerly, in part, *S. fluviatilis*)

Other names in use.—Long-leaved willow, narrow-leaved willow, and river-bank willow.

Range.—Quebec to Athabasca and southward through western New England to Virginia; westward to Colorado and southern Texas.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—0.7 mm.

By Sulphite Process

Reduces easily.

Unbleached pulp: Of poor color; bleaches easily.

Yields: 45 to 50 per cent.

Bleach required: 5 to 10 per cent.

¹⁰ About 10 to 13 per cent when cooked by sulphate process to yields indicated.

By Soda Process

Reduces readily.
 Unbleached pulp: Bleaches with difficulty.
 Yields: 40 to 45 per cent.
 Bleach required: 25 to 30 per cent.

By Mechanical Process

Behavior probably similar to that of aspen.

RED ALDER (*Alnus rubra*)

Other names in use.—Alder and western alder.
Range.—From southeastern Alaska to southern California.
Oven-dry weight per cubic foot, green volume.—23 pounds.
Fiber length.—1.2 mm.

By Sulphite Process

Not determined.

By Soda Process

Reduces readily.
 Unbleached pulp: Fairly easy to bleach.
 Yields: 40 to 45 per cent.
 Bleach required: 20 to 25 per cent.¹¹
 Red alder is much more susceptible to decay than ordinary pulp woods.

By Mechanical Process

Behavior probably similar to that of aspen.

BALSA (*Ochroma lagopus*)

Other names in use.—Balsa and balsa wood are the English and the commoner trade names for the wood. Common native names are lanero and lanillo in Cuba, bombast mahoe in Jamaica, and guano in Spanish Honduras.
Range.—Tropical America, Cuba, Jamaica, and Porto Rico.
Oven-dry weight per cubic foot, green volume.—7 pounds.
Fiber length.—1.33 mm.

By Sulphite Process

Not determined.

By Sulphate Process

Reduces readily.
 Unbleached pulp: Fairly easily bleached.
 Yield: 55 to 60 per cent. The lightness of the wood makes the yield on the volume basis extremely low.
 Bleach required: 25 to 30 per cent.
 Uses to which pulp is suited: Balsa is probably of no commercial value as a pulp wood because of the extremely low yield per unit of volume.

By Mechanical Process

Not determined.

BOX ELDER (*Acer negundo*)

Other names in use.—Ash-leaved maple and three-leaved maple.
Range.—From central New York and western New England, southward to central Florida; westward to Minnesota, Iowa, eastern Kansas, Missouri, southeastern Oklahoma, and southwestern Arkansas, northern Alabama, western Louisiana, and eastern Texas.
Oven-dry weight per cubic foot, green volume.—30 pounds.
Fiber length.-----

By Sulphite Process

Behavior probably similar to that of red maple.

¹¹ About 15 to 20 per cent when cooked by sulphate process to yields stated.

By Soda Process

Reduces readily.

Unbleached pulp: Rather difficult to bleach.

Yields: 35 to 40 per cent.

Bleach required: 25 to 30 per cent.¹²

By Mechanical Process

Behavior probably similar to that of black gum.

RED MAPLE (*Acer rubrum*)

Other names in use.—Swamp maple, soft maple, and water maple. The trade name of the lumber, mixed with that of silver maple, is soft maple.

Range.—From Newfoundland to southern Florida and westward to western Wisconsin, northwestern Minnesota, southeastern Iowa, eastern Oklahoma, southwestern Oklahoma, southwestern Arkansas, and eastern Texas.

Oven-dry weight per cubic foot, green volume.—30 pounds.

Fiber length.—0.8 mm.

By Sulphite Process

Reduces very easily.

Unbleached pulp: Of rather poor color; usually contains small black specks, which disappear upon bleaching; easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 5 to 15 per cent.

By Soda Process

Reduces vary easily.

Unbleached pulp: Fairly easy to bleach.

Yields: 40 to 45 per cent.

Bleach required: 15 to 20 per cent.

By Mechanical Process

Behavior probably similar to that of black gum.

SUGAR MAPLE (*Acer saccharum*)

Other names in use.—Hard maple, sugar-tree, and rock maple. The lumber is called hard maple and white maple by the trade.

Range.—From southern Newfoundland and Nova Scotia (along the St. Lawrence and Saguenay Rivers, Lake St. John, and the northern borders of the Great Lakes) to Lake of the Woods, Ontario, Minnesota, northeastern South Dakota, Iowa, eastern Kansas, central and southeastern Oklahoma, southwestern Arkansas, and eastern Louisiana; south (through the Northern States and on the Allegheny Mountains) to northern Georgia; west to eastern Nebraska, eastern Kansas, and eastern Texas.

Oven-dry weight per cubic foot, green volume.—35 pounds.

Fiber length.—-----

By Sulphite Process

Reduces very easily.

Unbleached pulp: Of excellent color; bleaches easily.

Yields: 45 to 50 per cent.

Bleach required: 10 to 20 per cent.

By Soda Process

Reduces with some difficulty.

Unbleached pulp: Rather difficult to bleach.

Yields: 40 to 45 per cent.

Bleach required: 25 to 30 per cent.¹³

By Mechanical Process

Behavior probably similar to that of black gum.

¹² About 15 to 20 per cent when cooked by sulphate process to yields stated.

¹³ About 20 to 27 per cent when cooked by sulphate process to yields stated.

PAPER BIRCH (*Betula papyrifera*)

Other names in use.—Canoe birch and white birch.

Range.—From Labrador to Hudson Bay (southern shores); southward to New York (Long Island) and northern Pennsylvania, central Michigan, northern Wisconsin, North Dakota, South Dakota (Black Hills), eastern Nebraska, and Wyoming. The best stands occur in the central portion of Maine, in a strip extending from the coast to the White Mountains of New Hampshire.

Oven-dry weight per cubic foot, green volume.—34 pounds.

Fiber length.—1.2 mm.

By Sulphite Process

Reduces easily.

Unbleached pulp: Of poor color; fairly easy to bleach.

Yields: 45 to 50 per cent.

Bleached required: 10 to 20 per cent.

By Soda Process

Reduces with some difficulty.

Unbleached pulp: Fairly easy to bleach.

Yields: 35 to 40 per cent.

Bleached required: 15 to 20 per cent.

By Mechanical Process

Characteristics similar to those of aspen except that the pulp, though light colored, has a pinkish tinge.

YELLOW BIRCH (*Betula lutea*)

Other names in use.—Gray birch, swamp birch, and silver birch. The lumber is sold as birch.

Range.—From Newfoundland and along the northern shores of St. Lawrence Gulf to Abitibi Lake and Rainy River; southward through northern Minnesota to central Iowa, and through the Northern States to eastern Tennessee, western North Carolina, northern Georgia, and Delaware. Wisconsin, Michigan, and New York have the largest stands.

Oven-dry weight per cubic foot, green volume.—34 pounds.

Fiber length.—1.5 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of good color; fairly easily bleached.

Yields: 45 to 50 per cent.

Bleached required: 15 to 20 per cent

By Soda Process

Reduces with some difficulty.

Unbleached pulp: Fairly easy to bleach.

Yields: 40 to 45 per cent.

Bleach required: 15 to 20 per cent.

By Mechanical Process

Behavior probably similar to that of paper birch.

BEECH (*Fagus grandifolia*, formerly, *F. atropunicea*)

Other names in use.—Red beech and white beech.

Range.—New Brunswick to Lake Huron (northern shores) and Minnesota; south to western Florida and west to Missouri and Texas (Trinity River).

Oven-dry weight per cubic foot, green volume.—36 pounds.

Fiber length.—1.1 mm.

By Sulphite Process

Not determined.

By Soda Process

Reduces with slightly more difficulty than aspen.
 Unbleached pulp: Easy to bleach.
 Yields: 45 to 50 per cent.
 Bleached required: 10 to 15 per cent.

By Mechanical Process

Not determined.

BLACK GUM (*Nyssa sylvatica*)

Other names in use.—Tupelo and pepperidge.

Range.—From Maine (Kennebec River) to northern Florida; west to southern Ontario, southern Michigan, southeastern Missouri, Oklahoma, southwestern Arkansas, and eastern Texas.

Oven-dry weight per cubic foot, green volume.—30 pounds.

Fiber length.—1.7 mm.

By Sulphite Process

Reduces readily.
 Unbleached pulp: Fairly easy to bleach.
 Yields: 45 to 50 per cent.
 Bleach required: 15 to 20 per cent.

By Soda Process

Reduces readily.
 Unbleached pulp: Slightly stronger than aspen pulp; rather difficult to bleach.
 Yields: 35 to 40 per cent.
 Bleach required: 20 to 30 per cent.¹⁴

By Mechanical Process

A pulp of standard strength, very light colored and fine fibered, is produced with a consumption of approximately three times as much power as is required for spruce.

TUPELO GUM (*Nyssa aquatica*)

Other names in use.—Sour gum, bay poplar, cotton gum, large tupelo, swamp poplar, and hickory poplar. The lumber usually goes under the names tupelo and sap gum in the market.

Range.—Atlantic coast region from southern Virginia to northern Florida, and through the Gulf States to central Texas; northward through Arkansas, west Tennessee, and Kentucky, southern and southeastern Missouri to southern Illinois.

Oven-dry weight per cubic foot, green volume.—29 pounds.

Fiber length.—1.6 mm.

By Sulphite Process

Reduces readily.
 Unbleached pulp: Of fair color; fairly easily bleached.
 Yields: 45 to 50 per cent.
 Bleach required: 15 to 25 per cent.

By Soda Process

Reduces readily.
 Unbleached pulp: Slightly stronger than aspen pulp; rather difficult to bleach.
 Yields: 35 to 40 per cent.
 Bleach required: 25 to 30 per cent.¹⁵

By Mechanical Process

Behavior probably similar to that of black gum.

¹⁴About 15 to 25 per cent when cooked by sulphate process to yields stated.

¹⁵About 20 to 27 per cent when cooked by sulphate process to yields stated.

RED GUM (*Liquidambar styraciflua*)

Other names in use.—Gum, sweet gum, liquidambar, and star-leaved gum. In the lumber markets red gum is the name applied to the heartwood and sap gum to the sapwood of the tree. In foreign markets the heartwood is called satin walnut and the sapwood, hazel pine.

Range.—From southwestern Connecticut to southeastern Missouri, Arkansas and Oklahoma, south to central Florida and eastern Texas. The commercial range is largely confined to the moist lands of the lower Ohio and Mississippi basins and the lowlands of the southeastern coast.

Oven-dry weight per cubic foot, green volume.—27 pounds.

Fiber length.—1.6 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Dark colored and rather difficult to bleach, differing in this respect from pulps from the true gums (*Nyssa*).

Yields: 45 to 50 per cent.

Bleach required: 35 to 40 per cent.

Uses to which pulp is suited: Limited chiefly by resistance to bleach.

By Soda Process

Reduces fairly readily.

Unbleached pulp: Rather difficult to bleach.

Yields: 35 to 40 per cent.

Bleach required: 15 to 20 per cent.

By Mechanical Process

Behavior probably similar to that of black gum.

CUCUMBER MAGNOLIA (*Magnolia acuminata*)

Other names in use.—Cucumber tree, cucumber, and mountain magnolia. The lumber is usually sold as yellow poplar.

Range.—From western New York through southern Ontario and south to southern Illinois and Indiana, and south in the Appalachian Mountains to southern Georgia, southern Alabama, and northeastern Mississippi, central Kentucky and Tennessee, northeastern, southern, and southwestern Arkansas, and eastern Oklahoma, and southwestern Missouri.

Oven-dry weight per cubic foot, green volume.—27 pounds.

Fiber length.—1.3 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Dark colored, rather difficult to bleach.

Yields: 45 to 50 per cent.

Bleach required: 25 to 30 per cent.

Uses to which pulp is suited: Limited chiefly by resistance to bleach.

By Soda Process

Reduces easily.

Unbleached pulp: Rather difficult to bleach.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

By Mechanical Process

Behavior probably similar to that of black gum.

SWEET BAY (*Magnolia virginiana australis*, formerly included as a form of *M. glauca*)

Other names in use.—White bay, swamp laurel, and swamp magnolia.

Range.—From southeastern North Carolina (vicinity of Wilmington) and southward in the coast region of South Carolina and Georgia (to Randolph and Carroll Counties), throughout Florida, and westward in the Gulf States to eastern

Texas (Nueces River, San Augustine County); in Alabama, extending to Macon and Dallas Counties, and also to Sand and Lookout Mountains, in Mississippi, to the northeast corner of the State, and in western Louisiana, to Winn and Natchitoches Parishes.

Oven-dry weight per cubic foot, green volume.—29 pounds.

Fiber length.—1.3 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of poor color; easily bleached.

Yields: 40 to 45 per cent.

Bleach required: 10 to 15 per cent.

By Soda Process

Reduces readily.

Unbleached pulp: Rather difficult to bleach.

Yields: 35 to 40 per cent.

Bleach required: 25 to 30 per cent.¹⁶

By Mechanical Process

Behavior probably similar to that of black gum.

SYCAMORE (*Platanus occidentalis*)

Other names in use.—Button-wood, buttonball-tree, and plane-tree.

Range.—Southwestern Maine to northern Vermont, southern Ontario and Michigan, central and southern Iowa, southeastern Nebraska, eastern Kansas, Oklahoma, and southwestern Arkansas, south to western Florida, central Alabama, and Mississippi, to western Texas.

Oven-dry weight per cubic foot, green volume.—29 pounds.

Fiber length.—1.7 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Easily to bleach.

Yields: 45 to 50 per cent.

Bleach required: 10 to 15 per cent.

By Soda Process

Reduces readily.¹⁷

Unbleached pulp: Fairly easy to bleach.

Yields: 45 to 50 per cent.

Bleach required: 15 to 20 per cent.

By Mechanical Process

Not determined.

BUTTERNUT (*Juglans cinerea*)

Other names in use.—White walnut and oil nut.

Range.—Southern New Brunswick to Delaware and in the Appalachian Mountains to Georgia and Alabama, westward through Ontario to eastern South Dakota, eastern Iowa, southeastern Nebraska, central Kansas, southern Missouri, and northern Arkansas.

Oven-dry weight per cubic foot, green volume.—22 pounds.

Fiber length.—1.2 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of poor color; fairly easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 15 to 20 per cent.

By Soda Process

Reduces readily.

Unbleached pulp: Very difficult to bleach.

Yields: 45 to 50 per cent.

¹⁶ 20 to 25 per cent when cooked by sulphate process to yields stated.

¹⁷ The wood is difficult to chip if it is allowed to dry out, presumably on account of the numerous and broad medullary rays.

By Mechanical Process

Not determined.

OHIO BUCKEYE (*Aesculus glabra*)

Other names in use.—Buckeye, American horse chestnut, and stinking buckeye.

Range.—From Pennsylvania (western slopes of the Allegheny Mountains) to northern Alabama, and west to southern Iowa, northeastern Kansas, Missouri, and southeastern Nebraska.

Oven-dry weight per cubic foot, green volume.—21 pounds.

Fiber length.—-----

By Sulphite Process

Reduces readily.

Unbleached pulp: Silver-gray in color; rather difficult to bleach.

Yields: 45 to 50 per cent.

Bleach required: 20 to 25 per cent.

By Soda Process

Reduces fairly readily.

Unbleached pulp: Rather difficult to bleach.

Yields: 40 to 45 per cent.

Bleach required 25 to 30 per cent.

By Mechanical Process

Not determined.

MANGROVE (*Rhizophora mangle*)

Other names in use.—This species is known only as mangrove.

Range.—Southern coast of Florida.

Oven-dry weight per cubic foot, green volume.—56 pounds.

Fiber length.—-----

By Sulphite Process

Not determined.

By Soda Process

Reduces readily.

Unbleached pulp: Short fibered, rather difficult to bleach.

Yields: 40 to 45 per cent.

Bleach required: 25 to 30 per cent.

On account of its exceptionally large yield on the volume basis as a result of its high density, this wood is worthy of consideration as a pulp material, provided means can be devised for harvesting at reasonable cost.

By Mechanical Process

Not determined.

6. HARDWOODS—RING-POROUS

Possible uses: Reference is directed to page 20 for a discussion of the uses of hardwood pulps as a group. Individual species differ as to the ease or difficulty with which pulps of satisfactory quality can be produced rather than as to specific uses for which they may be suited. Therefore no discussion of specific uses of pulps from the individual species will be attempted in the summaries.

Sulphate process: Practically all American hardwoods can be pulped by the sulphate process as readily as by the soda process. The sulphate pulps usually bleach with less bleaching powder than soda pulps; otherwise the two classes show practically no difference in quality. The soda process, however, since it was established earlier than the sulphate and operates with greater freedom from offensive odors, has remained almost without challenge for the pulping of hardwoods. Therefore the sulphate process will be referred to only incidentally in this section.

COMMON CATALPA (*Catalpa bignonioides*, formerly *C. catalpa*)

Other names in use.—Indian bean, bean-tree, common catalpa, catawba, and cigar-tree.

Range.—Believed to be indigenous only in southwestern Georgia, western Florida, central Alabama, Mississippi, and southwestern Missouri. It is widely

cultivated for ornament, however, and is naturalized elsewhere in the eastern United States as far north as southern New York, and also in Europe.

Oven-dry weight per cubic foot, green volume.—31 pounds.

Fiber length.—-----

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Decidedly pinkish in color, frequently specky; very difficult to bleach.

Yields: 45 to 50 per cent.

Bleach required: 35 to 40 per cent.

By Soda Process

Reduces readily.

Unbleached pulp: Fairly easy to bleach.

Yields: 40 to 45 per cent.

Bleach required: 15 to 20 per cent.

By Mechanical Process

Not determined.

CHESTNUT (*Castanea dentata*)

Other names in use.—Chestnut is one of the few trees of commercial importance that has but one name.

Range.—The entire stand of chestnut in the United States is being rapidly depleted by a fungous disease known as the "chestnut blight." Before it was attacked by the blight, chestnut grew in commercial quantities from New Hampshire and Vermont southward and westward in Connecticut, Massachusetts, New York, Pennsylvania, and along the Appalachian Mountains to northern Georgia. The commercial supply has been greatly diminished by the blight in the northern part of this region, and the best remaining stands are located in the southern Appalachians.

Oven-dry weight per cubic foot, green volume.—25 pounds.

Fiber length.—1 mm.

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Olive-brown in color; very difficult to bleach.

Yields: 40 to 45 per cent.

Bleach required: 35 to 40 per cent.

By Soda Process

Does not reduce satisfactorily. When extracted, however, for the tannin content, chestnut chips reduce readily. The following statements apply to pulp made from extracted chips:

Unbleached pulp: Bleaches easily.

Yields: 35 to 40 per cent.

Bleach required: 10 to 15 per cent.

By Mechanical Process

Not determined.

HACKBERRY (*Celtis occidentalis*)

Other names in use.—Sugarberry and nettle-tree.

Range.—From New England to Virginia and westward to eastern North Dakota, Iowa, southwestern Missouri, and western Kansas.

Oven-dry weight per cubic foot, green volume.—30 pounds.

Fiber length.—1.1 mm.

By Sulphite Process

Reduced readily.

Unbleached pulp: Exceptionally light colored; easily bleached.

The color of the bleached pulp is better than that obtained with any other wood pulp, comparing favorably with that of the finest bleached cotton.

Yield: 40 to 45 per cent.

Bleached required: 10 to 15 per cent.

By Soda Process

Reduces readily.

Unbleached pulp: Rather difficult to bleach; differs from soda pulps of most other species on account of being noticeably less opaque.

Yields: 35 to 40 per cent.

Bleached required: 20 to 30 per cent.

By Mechanical Process

Not determined.

SASSAFRAS (*Sassafras variifolium*, formerly *S. sassafras*)

Other names in use.—Sassafras is the universal name for this species.

Range.—From southern Maine and eastern Massachusetts through southern Vermont, southern Ontario, and central Michigan, southeastern Iowa to eastern Kansas, Arkansas, and Oklahoma; south to central Florida, and eastern Texas.

Oven-dry weight per cubic foot, green volume.—26 pounds.

Fiber length.—0.9 mm.

By Sulphite Process

Not successfully reduced.

By Soda Process

Reduces readily.

Unbleached pulp: Very difficult to bleach except where yields are too low for commercial consideration.

Yields: 30 to 35 per cent.

Bleach required: 30 to 35 per cent.

By Mechanical Process

Not determined.

ROCK ELM (*Ulmus racemosa*)

Other names in use.—Cork elm and hickory elm. Rock elm is the usual name applied to the lumber.

Range.—From Quebec (eastern townships) through Ontario, and south through northwestern New Hampshire to southern Vermont, and to northern New Jersey; westward through northern New York, southern Michigan, and central Wisconsin; southwestern Minnesota to northeastern Nebraska, western Missouri, eastern Kansas, and middle Tennessee.

Oven-dry weight per cubic foot, green volume.—36 pounds.

Fiber length.—1.3 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of poor color; easily bleached.

Yields: 45 to 50 per cent.

Bleach required: 10 to 15 per cent.

By Soda Process

Reduces readily.

Unbleached pulp: Fairly easy to bleach.

Yields: 45 to 50 per cent.

Bleach required: 20 to 25 per cent.

By Mechanical Process

Not determined.

SLIPPERY ELM (*Ulmus fuiva*, FORMERLY *U. pubescens*)

Other names in use.—This species is also commonly known as red elm and moose elm. The lumber is often sold as "gray elm."

Range.—From the lower St. Lawrence River through Ontario to South Dakota and eastern Nebraska, southeastern Kansas, southwestern Arkansas, and Oklahoma; south to western Florida, central Alabama, and Mississippi, western Louisiana, and central Texas.

Oven-dry weight per cubic foot, green volume.—30 pounds.

Fiber length.—1.7 mm.

By Sulphite Process

Reduces very imperfectly.

Unbleached pulp: Specky and dark.

Yields: 45 to 50 per cent.

Uses to which pulp is suited: Limited chiefly by imperfect reduction.

By Soda Process

Reduces readily.

Unbleached pulp: Difficult to bleach.

Yields: 35 to 40 per cent.

Bleach required: 30 to 40 per cent.¹⁸

By Mechanical Process

Not determined.

AMERICAN ELM (*Ulmus americana*)

Other names in use.—White elm, water elm, and elm. The lumber is known variously as soft elm, gray elm, and hard gray elm.

Range.—From southern Newfoundland to Lake Superior and to the eastern base of the Rocky Mountains, south to southern Florida, west to North Dakota, South Dakota, western Nebraska, central Kansas, Oklahoma, southwestern Arkansas, and west central Texas.

Oven-dry weight per cubic foot, green volume.—27 pounds.

Fiber length.—1.6 mm.

By Sulphite Process

Behavior probably similar to that of rock elm.

By Soda Process

Readily reduced.

Unbleached pulp: Fairly easy to bleach.

Yields: 40 to 45 per cent.

Bleach required: 25 to 30 per cent.¹⁹

By Mechanical Process

Not determined.

WHITE ASH (*Fraxinus americana*)

Other names in use.—Lumber of the several ashes is usually sold as "ash," and the term "white ash" is generally used to indicate heavy, strong material of high quality from which the lighter wood is excluded. Pumpkin ash is a term frequently employed to designate soft and brittle ash wood.

Range.—White ash is found over nearly all the eastern half of the United States. It occurs from Nova Scotia and New Brunswick to Florida and westward through southern Quebec and Ontario to eastern Minnesota, eastern Nebraska and Kansas, Oklahoma, southwestern Arkansas, and eastern Texas.

Oven-dry weight per cubic foot, green volume.—34 pounds.

Fiber length.—1.2 mm.

By Sulphite Process

Reduces fairly readily.

Unbleached pulp: Of poor color, specky; rather difficult to bleach.

Yields: 45 to 50 per cent.

Bleach required: 20 to 30 per cent.

Uses to which pulp is suited: Few.

By Soda Process

Reduces readily.

Unbleached pulp: Rather difficult to bleach.

Yields: 40 to 45 per cent.

Bleach required: 25 to 30 per cent.

Uses to which pulp is suited: Few.

By Mechanical Process

Not determined.

¹⁸ From 15 to 20 per cent when cooked by sulphate process to yields stated.

¹⁹ About 18 to 24 per cent when cooked by sulphate process to yields stated.

RED OAK (*Quercus borealis maxima*, FORMERLY *Q. rubra*)

Other names in use.—Black oak, spotted oak, mountain oak, and Spanish oak. The term "red oak" is used commercially to indicate the wood of a number of species included in the red-oak group, which is one of the two groups (namely "red" and "white") into which the oaks are divided commercially in the trade.

Range.—The northern range is not fully determined. Red oak occurs from western New York and Pennsylvania westward through Ohio and southern Michigan and southward to Georgia, Tennessee, Alabama, and Mississippi to Arkansas and Oklahoma; westward to eastern Nebraska and central Kansas.

Oven-dry weight per cubic foot, green volume.—35 pounds.

Fiber length.—1.5 mm.

By Sulphite Process

Reduces readily.

Unbleached pulp: Of fair color, but specky; rather difficult to bleach.

Yields: 45 to 50 per cent.

Bleach required: 20 to 25 per cent.

Uses to which pulp is suited: Limited chiefly by speckiness.

By Sulphate Process

Reduces readily.

Unbleached pulp: Rather difficult to bleach.

Yields: 35 to 40 per cent.

Bleach required: 15 to 25 per cent.

Uses to which pulp is suited: When undercooked, high yields are obtained of a pulp suitable for the manufacture of wrapping paper of fair strength; otherwise possible uses are few.

By Mechanical Process

Not determined.

WHITE OAK (*Quercus alba*)

Other names in use.—"West Virginia soft white oak," stave oak, and "forked-leaf white oak" are trade names. Lumber of several other species of the white oak group is classed as "white oak".

Range.—From southern Maine to southwestern Quebec and through southern Ontario, Lower Peninsula of Michigan, and southern Minnesota, eastern Iowa, southeastern Nebraska, and eastern Kansas, Arkansas, and Oklahoma; south to western Florida and eastern Texas.

Oven-dry weight per cubic foot, green volume.—37 pounds.

Fiber length.—1.5 mm.

By Sulphite Process

Reduces with some difficulty.

Unbleached pulp: Specky; difficult to bleach.

Yields: 45 to 50 per cent.

Bleach required: 30 to 35 per cent.

By Soda Process

Reduces readily.

Unbleached pulp: Very difficult to bleach.

Yields: 35 to 40 per cent.

Bleach required: 35 to 40 per cent.²⁰

By Mechanical Process

Not determined.

MOCKERNUT HICKORY (*Hicoria alba*)

Other names in use.—Mockernut hickory, mockernut, and white heart hickory. The lumber is generally sold as hickory, a name under which several hickories are included.

Range.—Southwestern Ontario to Florida and west to southeastern Iowa, Missouri, eastern Oklahoma, and southwestern Arkansas, and in the Gulf States to eastern Texas.

Oven-dry weight per cubic foot, green volume.—40 pounds.

Fiber length.—1.4 mm.

²⁰ About 22 to 25 per cent when cooked by sulphate process to yields stated.

By Sulphite Process

Reduces readily.
 Unbleached pulp: Specky; rather difficult to bleach.
 Yields: 40 to 45 per cent.
 Bleach required: 15 to 20 per cent.

By Soda Process

Reduces readily.
 Unbleached pulp: Very difficult to bleach.
 Yields: 30 to 35 per cent.
 Bleach required: More than 35 per cent.²¹

By Mechanical Process

Not determined.

BLACK LOCUST (*Robinia pseudoacacia*)

Other names in use.—Locust and yellow locust.

Range.—From Pennsylvania to northern Georgia, also southern Illinois and southwestern Indiana. Widely naturalized through cultivation and other agencies throughout the United States east of the Rocky Mountains.

Oven-dry weight per cubic foot, green volume.—41 pounds.

Fiber length.—-----

By Sulphite Process

Reduces with difficulty and very unevenly.
 Unbleached pulp: Not satisfactory.

By Soda Process

Reduces fairly readily.
 Unbleached pulp: Does not bleach satisfactorily.
 Yields: 40 to 45 per cent.

By Mechanical Process

Not determined.

ALANTHUS (*Ailanthus altissima*, FORMERLY *A. glandulosa*)

Other names in use.—Tree of Heaven and Chinese sumac.

Range.—Native of China; but has been widely naturalized in the eastern United States.

Oven-dry weight per cubic foot, green volume.—24 pounds.

Fiber length.—1.2 mm.

By Sulphite Process

Not determined.

By Soda Process

Reduces readily.
 Unbleached pulp: Very easy to bleach.
 Yields: 45 to 50 per cent.
 Bleach required: 5 to 10 per cent.

By Mechanical Process

Not determined.

7. MISCELLANEOUS SPECIES

SOAPWEED (*Yucca elata*, formerly *Y. radiosa*)

Other names in use.—Spanish bayonet and Spanish dagger.

Range.—Southwestern Texas to southern Arizona; northern Mexico.

Oven-dry weight per cubic foot, green volume.—18 pounds.

Fiber length.—-----

Sulphite Pulp

Not determined.

Soda Pulp

Soapweed is readily reduced by the soda process, yielding a pulp containing 20 to 30 per cent of rather short fibers. The remainder is pithy material, the

²¹ Bleach requirement greatly reduced when cooked by sulphate process.

cells of which are very little longer than their diameter. A few special uses might be developed for this material, but it could hardly be used for standard pulp products on account of the probable cost of collection, nonuniformity of the pulp obtained, low yields, and the difficulty in completely removing soil and other foreign matter from the material before cooking.

Mechanical Pulp

Not determined.

CABBAGE PALMETTO (*Sabal palmetto*)

Other names in use.—Palmetto and cabbage tree.

Range.—Coast region from North Carolina to southern Florida, and on the Gulf coast to western Florida.

Oven-dry weight per cubic foot, green volume.—23 pounds.

Fiber length.—-----

Sulphite Pulp

Cabbage palmetto under the sulphite process yields 35 to 40 per cent of dark, raw, and brash pulp not suited for any of the common uses.

Sulphate Pulp

Cabbage palmetto can be reduced by the sulphate process under low steam pressure to satisfactory pulp fairly easy to bleach. The pulp is stronger than aspen soda pulp, and may be used in the manufacture of book, magazine, and other similar papers, preferably in combination with 20 to 40 per cent of bleached pulp from coniferous woods. The pulp consists of a mixture of fairly long fibers and pithy material. The proportion of pithy material, however, does not seriously affect the character of the sheet except in so far as it makes it weaker than would be the case with the long-fibered portion alone. Yields of 40 to 45 per cent are obtained, requiring 25 to 30 per cent of standard bleaching powder.

Soda Pulp

Cabbage palmetto when cooked by the soda process yields 35 per cent of coarse, tender fiber difficult to bleach and not suited for any of the common uses.

Mechanical Pulp

Not determined.

CANE (*Arundinaria macrosperma*)

Other names in use.—Large cane and giant cane.

Range.—River bottoms from Virginia to Florida, westward to Louisiana and along the Mississippi and its tributaries as far north as Kentucky, Tennessee, and Missouri.

Oven-dry weight per cubic foot, green volume (in piles).—10 pounds.²²

Fiber length.—-----

Sulphite Pulp

Not determined.

Soda Pulp

Cane reduces readily by the soda process to an easily bleached pulp having greater average fiber length than aspen soda pulp and capable of use in the manufacture of book, magazine, and similar papers. It could probably be used without admixture of longer-fibered pulps from coniferous woods. The fiber is soft, opaque, and contains much less pith than is usual for this sort of material. Yields of 33 to 42 per cent are obtained, requiring 15 to 18 per cent of standard bleaching powder.

Mechanical Pulp

Not determined.

²² When chopped for the digester, the material occupies 1 cubic foot for each 14 pounds of oven-dry material, in comparison with 10 pounds to the cubic foot of space occupied by spruce chips.)

8. CHILEAN WOODS²³

OLIVILLO

Description.—The bark is light ash-gray, about one-half inch thick, compact, comparatively smooth, and is not broken into fissures nor can it be readily separated into scales. The wood does not resemble any commercial native wood. It has a very open structure and contains one-quarter by volume of wood fibers having walls of moderate thickness, the rest being made up of parenchyma or vascular tissue.

Oven-dry weight per cubic foot, green volume.—-----

Fiber lengths.—Average, 2.15 mm.; maximum, 2.62 mm.; minimum, 1.34 mm.

Soda Pulp

Olivillo yields a pulp with a longer fiber than has been obtained from any North American hardwoods, which would render it suitable for use unbleached in the manufacture of wrapping paper of considerable strength. Although it is rather difficult to bleach, with bleaching in two stages economical means of operation might possibly be evolved. Yields of 35 to 40 per cent are obtained, requiring 30 to 40 per cent of standard bleaching powder.

LAUREL (*Laurelia aromatica*)

Range.—Laurel grows from 34° south latitude to Llanquihue, Chile.

Description.—The bark is dark reddish brown, about one-half inch thick, is not broken into fissures but can be readily separated into scales. The wood resembles that of silver maple (*Acer saccharinum*). Fiber walls are moderately thick.

Oven-dry weight per cubic foot, green volume.—-----

Fiber lengths.—Average, 0.86 mm.; maximum, 1.02 mm.; minimum, 0.7 mm.

Soda Pulp

The action of the caustic soda in cooking is slower than with most species, and the same is true with the solutions in bleaching. The pulp is similar to aspen soda pulp. Yields of 40 per cent are obtained, requiring 30 to 35 per cent of standard bleaching powder.

COIGUE (*Nothofagus dombeyi*)

Range.—Grows abundantly throughout Chile.

Description.—The bark is grayish, one-half inch thick, and separated into low flat ridges. The inner bark is very fibrous. The wood strongly resembles red gum (*Liquidambar styraciflua*), with about the same proportion of vascular and woody tissue and fairly thick-walled fibers, although the pores are slightly larger.

Oven-dry weight per cubic foot, green volume.—-----

Fiber lengths.—Average 0.85 mm.; maximum, 1.02 mm.; minimum, 0.7 mm.

Soda Pulp

Coigue is readily reduced by the soda process to fairly easily bleached pulp similar to aspen soda pulp. Yields of 40 to 45 per cent are obtained, requiring 15 to 20 per cent of standard bleaching powder.

LINGUE (*Persea lingue*)

Range.—From Aconcagua to Llanquihue, Chile.

Description.—The bark is deep reddish brown about one-half inch thick and strongly resembles that of hemlock. It is separated by narrow fissures into broad flat plates. The wood strongly resembles butternut (*Juglans cinerea*), and has large pores. The fibers are moderately thin-walled with comparatively large lumen.

Oven-dry weight per cubic foot, green volume.—-----

Fiber lengths.—Average, 1.11 mm.; maximum, 1.6 mm.; minimum, 0.61 mm.

Soda Pulp

Yields of 40 to 45 per cent are obtained, requiring 20 to 30 per cent of standard bleaching powder.

²³ These woods were submitted by Senor Alejandro Rosselot, member of Congress, Santiago, Chile.

ROBLE PELLIN (*Nothofagus obliqua*)

Range.—From 33° south latitude to Llanquihue, Chile.

Description.—The bark is reddish brown with light-gray particles. It is one-half inch thick, not ridged, and readily separated into thin, broad, flat scales. The wood closely resembles coigue.

Oven-dry weight per cubic foot, green volume.—-----

Fiber lengths.—Average, 1.45 mm.; maximum, 1.76 mm.; minimum, 1.12 mm.

Soda Pulp

Roble pellin is readily reduced by the soda process, but the pulp is very difficult to bleach. Yields of 30 to 35 per cent are obtained, requiring 35 to 40 per cent of standard bleaching powder.

There is little likelihood of this species being considered for pulp, on account of its great durability and consequently higher value for railroad ties and structural timber.

QUILLAI (CHILEAN CANE) (*Quillaja saponaria*)

Description.—Resembles cane, except that it is solid and much stronger.

Oven-dry weight per cubic foot, green volume.—-----

Fiber lengths.—Average, 2.2 mm.; maximum, 2.66 mm.; minimum, 1.34 mm.

Soda Pulp

Quillai reduces readily by the soda process, yielding 40 to 45 per cent of pulp of very good fiber length and capable of use in the manufacture of papers of moderate strength.

On account of the light color of the pulp it might be considered for use unbleached in the manufacture of newsprint.

TABLES OF COOKING AND STRENGTH DATA

Tables 6 to 18 give for most of the woods included the results of a majority of the test cooks made. They cover cooking conditions, yields, and strength of the resulting pulps. For reasons already stated, the data are not in all cases representative of what are, according to the final conclusions, the practical pulping characteristics of the species. They may be considered, however, as illustrative of possible operating conditions, which in some cases are to be avoided rather than imitated.

The column headings in the tables are, in general, self-explanatory. In the tables of sulphite cooks the columns showing the composition of the cooking liquor give the percentage of SO₂ in the liquor as free, combined, and total, with the commonly accepted understanding that the free is the excess over that required to combine with the base and form normal sulphite, even though the latter does not exist as such. "Duration of cook" is the total time of cooking, from turning on steam to blowing. The steam pressures shown refer in all cases to pressures above atmospheric. It is to be noted that these are partial pressures as distinguished from total pressures shown on the gauge. The quantity of bleach required was found by methods already described in "Experimental procedure."

In the strength data the strength factor is obtained by dividing the Mullen test value by the weight per ream of the paper tested. The average stretch and average breaking length are the average of those values in each direction as determined on the Schopper tensile strength tester for paper. The number of double folds was obtained on the standard Schopper folding tester. In the cases of both the folding and the tearing tests due allowance must be made for the weight of the sheet, since the values have not been converted to a standard or unit weight basis for want of any known conversion factor. Strength tests are shown for relatively few of the cooks of hardwoods, since, on account of their short fibers, hardwoods are not often used in papers where strength is of major importance.

Some of the raw cooks listed in the tables were worked into paper by a special beater treatment. This would indicate possibilities of combining chemical with mechanical disintegration of the chips and of producing paper of moderate strength from unbleached pulps at yields between 70 and 80 per cent. Work with caustic soda and caustic soda and sulphur has recently demonstrated this to be possible. Light-colored sulphite pulps with yields of over 70 per cent have been made, but additional work is necessary to perfect the details. The bearing of these developments on the utilization of mill waste or of southern woods for newsprint is apparent. The exceptional strength of pulp so obtained from the hardwoods is also of interest.

TABLE 6.—Cooking and strength data: *The spruces—Sulphite process*

Species	Ship- ment No.	Cook No.	Date	Quantity of wood used		Cooking liquor				Cooking period				
				Moist weight	Oven- dry weight	Composition			Per 100 pounds chips	Time to maxi- mum tem- per- ature	Dura- tion of cook- ing	Maxi- mum tem- per- ature	Maxi- mum pres- sure per square inch	Gas pres- sure at blow per square inch
						Total	Free	Com- bined						
				Pounds	Pounds	Per cent	Per cent	Per cent	Gallons	Per cent	Hours	° C.	Pounds	Pounds
Black spruce (<i>Picea mariana</i>)	{	565	Apr. 11, 1921	75.4	66.0	4.97	3.76	1.21	80.8	4.75	8.00	153	100	10
		561	Mar. 30, 1921	73.8	63.5	5.28	4.13	1.15	82.7	4.00	8.00	153	100	4
		574	Apr. 25, 1921	70.0	62.5	5.02	3.74	1.28	93.3	4.70	8.00	150	98	5
		501	Dec. 10, 1920	77.9	65.0	5.26	4.08	1.18	---	5.25	8.00	154	97	8
Blue spruce (<i>Picea pungens</i>)	{	490	July 16, 1917	74.6	64.0	5.68	4.44	1.24	---	2.75	8.75	155	98	10
		502	Apr. 23, 1908	13.2	12.7	4.12	3.07	1.05	---	7.00	10.00	158	---	---
		447	Aug. 16, 1920	70.6	61.4	5.45	4.36	1.09	90.2	4.40	8.00	153	100	4
		477	Oct. 13, 1920	70.9	62.5	5.47	4.28	1.19	96.8	4.00	8.00	158	100	8
Engelmann spruce (<i>Picea engelmannii</i>)	{	572	Apr. 21, 1921	58.3	51.5	5.37	4.12	1.25	112.7	3.50	8.00	153	100	10
		575	Apr. 26, 1921	59.2	51.6	5.72	4.02	1.10	112.5	3.50	8.00	153	100	10
		348	Oct. 12, 1917	73.0	63.6	5.50	4.13	1.37	---	8.00	2.75	152	90	6
		358	Nov. 4, 1917	68.7	59.6	5.49	4.36	1.13	99.5	7.25	8.00	153	100	6
Sitka spruce (<i>Picea sitchensis</i>)	{	390	Aug. 15, 1919	63.3	59.7	5.38	4.24	1.14	---	8.00	5.50	153	100	10
		399	Oct. 30, 1919	63.3	63.7	4.26	3.11	1.15	89.5	3.50	10.50	153	100	8
		334	Mar. 21, 1917	85.0	74.4	5.70	4.50	1.20	---	9.00	9.00	150	100	12
		336	July 10, 1917	96.1	84.5	5.86	4.56	1.30	32.9	2.25	3.00	153	100	10
White spruce (<i>Picea glauca</i>)	{	347	Oct. 11, 1917	85.1	75.7	5.80	4.17	1.63	---	7.25	3.50	150	100	10
		469	Oct. 1, 1920	74.8	64.8	4.96	3.95	1.01	190.2	3.50	0.00	161	75	0
		536	Feb. 17, 1921	66.1	55.8	5.42	4.30	1.12	106.0	3.75	8.00	152	100	4
		537	Feb. 18, 1921	72.7	59.2	5.39	4.30	1.09	103.0	8.00	8.00	153	100	4
		636	Mar. 7, 1922	115.6	88.3	5.60	4.46	1.14	70.3	3.50	15.00	137	65	32

Species	Cooking data—Continued					Strength data							Conditions during test				
	Ship-ment No.	Cook No.	Date	Yields based on oven-dry weight of chips charged		Bleach available per cent	Calendered 24 x 36—500	Weight per ream, 500	Thick-ness .0001 in.	Mullen test per square inch	Strength factor pound per ream	Aver-age break-ing length	Aver-age double folds	Aver-age Elmen-dorf tearing test	Rela-tive humid-ity	Tem-pera-ture	° F.
				Crude pulp	Screen-ings												
Black spruce (<i>Picea mariana</i>).	501	565	Apr. 11, 1921	Per cent	44.5	8	Yes---	Pounds	0.001 in.	Pounds	Points	Meters	Grams	Per cent	65	79	
		561	Mar. 30, 1921	Per cent	44.0	.66	Yes---	48.1	3.0	38.2	.80	6, 040	1,079	121	65	76	
		574	Apr. 25, 1921	Per cent	46.4	.66	Yes---	57.5	3.9	54.3	.94	6, 966	1,766	158	65	88	
Blue spruce (<i>Picea pungens</i>)	792	504	Dec. 10, 1920	Per cent	46.3	1.20	Yes---	39.5	2.8	38.8	.98	7, 572	634	---	66	70	
Engelmann spruce (<i>Picea engelmannii</i>)	490	339	July 16, 1917	Per cent	49.7	.23	Yes---	41.5	3.8	34.1	.82	5, 870	1, 990	---	67	88	
Do	502	4	Apr. 23, 1908	Per cent	46.2	.50	Yes---	49.0	3.4	37.3	.76	7, 310	744	---	65	80	
Norway spruce (<i>Picea abies</i>).	226	447	Aug. 16, 1920	Per cent	48.6	1.63	Yes---	52.9	3.4	33.0	.62	5, 228	284	---	66	84	
		477	Oct. 13, 1920	Per cent	40.1	.69	Yes---	65.1	3.3	48.5	1.06	6, 791	1, 618	115	65	87	
		572	Apr. 21, 1921	Per cent	51.0	.59	Yes---	65.1	4.2	67.2	1.03	8, 054	2, 400	182	64	78	
Red spruce (<i>Picea rubra</i>)	504	575	Apr. 26, 1921	Per cent	47.2	.43	Yes---	51.9	5.0	40.2	.79	3, 38	746	---	64	73	
		348	Oct. 12, 1917	Per cent	58.9	.14	Yes---	51.9	4.1	48.3	.93	6, 690	1, 336	---	65	75	
		358	Nov. 4, 1917	Per cent	52.0	.33	Yes---	37.7	3.8	22.3	.59	3, 70	718	---	66	---	
		390	Aug. 15, 1919	Per cent	51.6	---	No---	38.5	2.7	18.8	.49	2, 582	533	---	65	73	
Sitka spruce (<i>Picea sitchensis</i>).	399	Oct. 30, 1919	Per cent	51.5	.10	Yes---	46.0	4.1	46.7	1.02	5, 930	580	---	65	71		
	334	Mar. 21, 1917	Per cent	48.6	.35	Yes---	43.5	3.8	32.0	.74	7, 040	880	---	65	94		
	336	July 10, 1917	Per cent	47.1	.37	Yes---	45.5	4.2	37.2	.82	5, 880	785	---	64	75		
	347	Oct. 11, 1917	Per cent	47.8	---	Yes---	50.9	3.6	37.1	.73	6, 580	1, 182	---	64	88		
	469	Oct. 1, 1920	Per cent	57.5	.43	N. B.	53.8	4.0	39.7	.74	7, 068	967	---	66	74		
	536	Feb. 17, 1921	Per cent	45.8	.40	Yes---	49.0	4.0	30.6	.62	1, 79	153	---	64	73		
White spruce (<i>Picea glauca</i>).	537	Feb. 18, 1921	Per cent	45.6	.20	Yes---	49.0	4.0	30.6	.62	1, 79	153	---	64	73		
	636	Mar. 7, 1922	Per cent	48.4	.13	Yes---	53.8	4.5	37.1	.69	6, 600	4 555	80	65	71		

¹ Impregnation used.² 2,300 c. c. H₂SO₄, 1.13 sp. gr., added.³ Pulp of excellent strength and quality. Not run into paper.⁴ Ball mill tests gave 1,240 folds.

TABLE 7.—Cooking and strength data: The spruces—Soda or sulphate process

Species	Shipment No.	Cook No.	Date	Quantity of wood used		Cooking data										Black liquor ratio com- bined to total alkali				
				Moist weight	Oven-dry weight	Before penetration				After penetration				Penetration			Cooking liquor			
						Concentration		Volume	Concentration		Volume	Concentration		Duration	Pressure per square inch		Temperature	Concentration		Per 100 pounds bone-dry chips
						NaOH	Na ₂ S		NaOH	Na ₂ S		NaOH	Na ₂ S					NaOH	Na ₂ S	
Black spruce (<i>Picea mariana</i>)	501	187	Oct. 11, 1917	Lbs. 61.9	Lbs. 51.9	Grams per liter	Gal- lons	Grams per liter	Gal- lons	Grams per liter	Gal- lons	Grams per liter	Gal- lons	Lbs. 72.4	Lbs. 15.5	Lbs. 8.0	Lbs. 25.7	Per cent 42.0		
		194	Oct. 23, 1917	67.2	55.9	56.3	50.0	40.0	37.9	39.8	49.0	37.9	29.0	29.0	12.8	6.4	26.3	60.0		
		238	May 6, 1918	65.0	57.8	44.2	50.0	30.0	36.6	37.0	29.3	29.3	78.6	12.0	18.0	4.8	44.7			
		244	July 19, 1918	65.0	64.2	44.2	50.0	30.0	36.6	37.0	29.3	29.3	45.0	25.0	18.8	6.2	30.0	80.2		
Blue spruce (<i>Picea pungens</i>)	792	706	Nov. 23, 1920	77.2	64.2									75.2	25.0	18.8	6.2	30.0	88.5	
		707	Nov. 29, 1920	71.3	59.7									100.0	25.0	18.8	6.2	30.0	83.5	
		715	Dec. 17, 1920	52.2	46.4									64.6	21.5	15.0	5.0	27.8	78.2	
		130	May 2, 1917	72.3	55.1	56.0	50.0	32.0	38.3	48.4	31.4	15	105	53	68.6	14.3	6.0	25.0	61.0	
Engelmann spruce (<i>Picea engelmannii</i>)	490	132	May 8, 1917	66.0	51.2	56.0	50.0	31.3	39.2	46.6	30.1	10	105	26	77.2	30.5	6.2	24.6	65.0	
		221	Dec. 11, 1917	69.5	61.7	90.0	50.0		36.2	82.4		20	97	52	104.9	20.9		24.0	75.0	
		273	Sept. 15, 1920	83.6	73.7										79.9	20.0	5.0	30.0	81.3	
		274	Sept. 16, 1920	78.1	66.9										77.0	19.2	4.0	25.0	84.2	
Norway spruce (<i>Picea abies</i>)	795	275	Sept. 17, 1920	71.0	63.2									111.5	26.1	26.1	28.1	73.2		
		68	Aug. 4, 1916	74.0	64.3	55.3	49.0	40.0	35.4	44.0	37.3	20	110	65	78.0	44.6	8.6	23.0		
		71	Aug. 9, 1916	74.0	65.3	57.5	50.0	45.0	36.8	44.7	43.5	15	55	41	86.5	45.9	15.8	8.4	21.8	
		72	Aug. 10, 1916	74.0	65.1	57.5	50.0	45.0	38.3	43.2	42.5	25	55	39	89.4	45.2	15.7	7.9	21.9	
Red spruce (<i>Picea rubra</i>)	226	217	Oct. 4, 1917	57.3	49.9	90.0	50.0	50.0	37.9	84.0		17	97	51	101.2	22.0	22.0	26.0		
		191	Oct. 18, 1917	66.9	59.5	49.2	50.0	35.0	35.8	36.1		10	100	52	77.4	16.2	6.5	25.0	53.0	
		232	Apr. 25, 1918	70.4	61.6										27.0	48.0	9.0	16.0	40.0	
		235	May 3, 1918	69.5	59.4										36.0	30.0	12.0	10.0	40.0	
Sitka spruce (<i>Picea sitchensis</i>)	504	233	Apr. 26, 1918	66.9	60.2									41.9	18.0	14.0	6.0	40.0		
		239	May 7, 1918	67.6	60.0										45.1	12.0	15.0	4.0	40.0	
		237	June 8, 1921	68.2	60.4										45.0	12.0	15.0	4.0	40.0	
		777	June 9, 1921	69.2	60.6										48.1	6.0	16.0	2.0	40.0	
White spruce (<i>Picea glauca</i>)	225	2	Jan. 17, 1916	97.2	84.1	65.2	43.0	45.6	34.6	40.2	40.6	30	100	136.0	25.0	21.7	5.0	30.0	81.8	
		4	Jan. 23, 1916	95.1	83.7	80.0	49.2	45.6	31.2	64.4	23.6	14	100	136.0	25.0	21.7	5.0	30.0	81.0	
		9	July 8, 1916	147.5	73.0	70.6	44.7	35.1	52.9	35.2					99.7	23.4	19.3	4.5	23.5	91.0
		109	Dec. 7, 1916	82.0	71.9	84.2	50.0		31.6	74.0		25	110	83	78.0	20.3	20.3	8.2	27.4	75.0
		223	Dec. 17, 1917	100.0	85.0									83.4	23.2	6.0	32.6	75.0		

Cooking data—Continued										Strength data													
Species	Shipment No.	Cook No.	Date	Steam				Yields based on oven-dry weight of chips charged			Bleach required (35 per cent available chlorine) per 100 pounds oven-dry pulp	Strength data					Average Elmiendorf tearing	Conditions during test					
				Maximum pressure per square inch	Pressure increased	Duration at maximum pressure	Crude pulp	Screenings	Oil per ton bone-dry chips	Calendered		Weight per ream 24 x 36—500	Thickness	Mullen test per square inch	Strength factor per pound	Average stretch			Average breaking length	Average double folds			
Black spruce (<i>Picea mariana</i>)	501	187	Oct. 11, 1917	100	25	125	46.4	Per cent	Gal-	Lbs.	No.	Yes	37.0	3.6	45.2	1.22	3.20	7,020	2,355	Average double folds	Gms.	Relative humidity	Temperature
		194	Oct. 23, 1917	100	20	125	46.8	cent	tons		No.	Yes	38.0	3.8	55.1	1.45	3.70	7,110	1,473				
		238	May 6, 1918	100	40	300	41.9				No.	Yes	42.5	3.2	42.9	1.01	2.13	7,455	488				
		244	July 19, 1918	100	20	210	44.8				No.	Yes	42.5	3.2	42.9	1.01	2.13	7,455	488				
Blue spruce (<i>Picea pungens</i>)	792	706	Nov. 23, 1920	100	60	300	38.7			24		Yes	42.5	3.2	42.9	1.01	2.13	7,455	488	Average double folds	Gms.	Relative humidity	Temperature
		707	Nov. 29, 1920	99	100	300	38.0			26		Yes	42.5	3.2	42.9	1.01	2.13	7,455	488				
		715	Dec. 17, 1920	95	90	345	34.9				No.	Yes	42.5	3.2	42.9	1.01	2.13	7,455	488				
		132	May 2, 1917	80	15	155	53.6				No.	Yes	42.5	3.2	42.9	1.01	2.13	7,455	488				
Engelmann spruce (<i>Picea engelmannii</i>)	490	132	May 8, 1917	80	15	180	55.2					No.	42.5	3.8	72.2	1.70	4.80	8,470	1,846	Average double folds	Gms.	Relative humidity	Temperature
		221	Dec. 11, 1917	90	20	240	51.5				No.	Yes	43.5	3.9	51.8	1.19	3.45	9,010	896				
		273	Sept. 15, 1920	100	75	330	40.0			30		Yes	38.0	2.9	28.9	.76	1.50	4,762	778				
		274	Sept. 16, 1920	100	120	340	41.8			42		Yes	38.0	2.9	28.9	.76	1.50	4,762	778				
Norway spruce (<i>Picea abies</i>)	795	275	Sept. 17, 1920	100	75	300	40.2					Yes	34.0	2.9	41.1	1.21	4.05	6,995	1,417	Average double folds	Gms.	Relative humidity	Temperature
		68	Aug. 4, 1916	125	25	125	49.0			.76		Yes	38.5	3.5	47.0	1.22	4.20	7,038	1,923				
		71	Aug. 9, 1916	100	20	120	48.1			.35		No.	33.0	4.3	42.6	1.29	4.10	7,674	1,133				
		72	Aug. 10, 1916	80	15	180	50.4			.43		No.	40.5	3.7	49.4	1.22	2.90	8,150	859				
Red spruce (<i>Picea rubra</i>)	226	1217	Oct. 4, 1917	100	25	245	49.5			.13		No.	36.0	3.2	36.0	1.00	3.80	6,520	1,915	Average double folds	Gms.	Relative humidity	Temperature
		191	Oct. 18, 1917	102	20	120	49.4			.60		No.	40.5	3.8	44.4	1.10	3.10	6,500	1,515				
		232	Apr. 25, 1918	100	25	180	48.0			.13		No.	44.5	3.7	50.4	1.13	3.20	6,500	1,515				
		235	May 3, 1918	100	25	180	47.6			.20		No.	44.5	3.7	50.4	1.13	3.20	6,500	1,515				
Sitka spruce (<i>Picea sitchensis</i>)	504	236	May 3, 1918	100	25	180	47.7			.25		No.	29.0	2.6	29.2	1.01	3.40	6,060	1,314	Average double folds	Gms.	Relative humidity	Temperature
		233	Apr. 26, 1918	100	25	180	46.0			.23		No.	33.8	4.9	48.2	.90	3.20	5,680	2,900				
		239	May 7, 1918	100	25	180	44.6			.25		No.	37.5	3.3	36.0	1.04	3.20	6,850	1,888				
		237	June 8, 1921	100	25	180	61.6			8.24		No.	27.5	2.5	28.5	1.04	3.20	6,850	1,888				
White spruce (<i>Picea glauca</i>)	225	776	June 9, 1921	100	70	345	38.2			.07		Yes	48.5	4.0	35.8	.84	2.68	5,149	636	Average double folds	Gms.	Relative humidity	Temperature
		777	Jan. 17, 1916	80	10	80	49.7			4.69		Yes	40.5	3.4	34.0	.84	2.68	5,149	636				
		2	Jan. 23, 1916	110	45	150	45.8			.50		No.	45.0	4.1	72.4	1.59	3.18	10,850	893				
		4	July 8, 1916	135	30	60	47.0			.50		Yes	49.0	3.8	52.4	1.31	2.55	9,900	853				
White spruce (<i>Picea glauca</i>)	225	109	Dec. 7, 1916	100	35	135	50.2			.36		Yes	49.0	3.8	52.4	1.31	2.55	9,900	853	Average double folds	Gms.	Relative humidity	Temperature
		223	Dec. 17, 1917	95	45	300	39.2			1.26		No.	42.5	3.8	58.7	1.38	2.50	10,850	1,149				
		223	Dec. 17, 1917	95	45	300	39.2			1.26		No.	40.0	4.5	28.4	.72	1.97	5,490	707				
		223	Dec. 17, 1917	100	90	210	39.0				18	Yes	40.0	4.5	28.4	.72	1.97	5,490	707				

TABLE 8.—Cooking and strength data: *The pines—Sulphite process*

Species	Ship-ment No.	Cook No.	Date	Quantity of wood used		Composition			Cooking liquor		Cooking period				
				Moist weight	Oven-dry weight	Per 100 pounds chips			Volume	SO ₂	Time to maximum temperature	Dura-tion of cook	Maxi-mum tem-perature per square inch	Maxi-mum pres-sure per square inch	Gas pres-sure at blow per square inch
				Pounds	Pounds	Total	Free	Com-bined			Hours	Hours	° C.	Pounds	Pounds
Lumber pine (<i>Pinus flexilis</i>)	465	548	Mar. 10, 1921	86.0	72.3	5.12	3.57	1.55	75.3	—	7.50	3.50	158	100	10
Pinon (<i>Pinus edulis</i>)	792	506	Dec. 14, 1920	86.0	75.8	5.20	3.84	1.36	78.0	—	8.00	4.00	154	100	10
Sugar pine (<i>Pinus lambertiana</i>)	—	357	Nov. 13, 1917	59.6	52.1	5.46	4.22	1.24	—	—	7.75	4.00	152	100	10
—	—	360	Nov. 27, 1917	60.8	53.4	4.84	3.73	1.11	—	—	7.75	4.00	150	100	10
Northern white pine (<i>Pinus strobus</i>)	501	368	Dec. 4, 1917	55.7	48.6	5.49	4.28	1.21	—	—	8.00	3.25	153	102	8
—	—	369	Dec. 7, 1917	68.5	58.6	5.54	4.32	1.22	—	—	8.00	4.00	153	100	8
Jack pine (<i>Pinus banksiana</i>)	798	434	Mar. 29, 1920	68.8	60.4	5.68	4.32	1.36	100.0	49.4	7.75	4.50	160	100	2
—	—	437	Apr. 2, 1920	71.2	66.3	5.48	4.38	1.10	94.0	44.6	8.00	4.00	153	100	4
Loblolly pine (<i>Pinus taeda</i>)	801	500	Nov. 21, 1920	60.0	52.9	5.41	4.40	1.01	122.2	—	8.00	4.00	153	100	10
Lodgepole pine (<i>Pinus contorta</i>)	323	422	Mar. 10, 1920	69.8	62.1	5.43	4.11	1.32	101.0	47.5	8.25	4.25	153	100	6
Longleaf pine (<i>Pinus palustris</i>)	259	343	Aug. 13, 1917	77.9	68.2	5.90	4.26	1.64	156.0	—	7.75	4.25	156	100	14
Monterey pine (<i>Pinus radiata</i>)	811	431	Mar. 18, 1921	52.1	45.4	5.40	4.04	1.36	144.8	—	7.25	4.00	156	98	8
—	—	438	Aug. 13, 1917	52.1	45.4	5.70	3.98	1.72	—	—	8.00	3.00	158	100	4
Norway pine (<i>Pinus resinosa</i>)	501	508	Dec. 16, 1920	114.2	88.0	5.62	4.38	1.24	78.0	38.1	8.00	2.75	136	120	—
—	—	428	Mar. 19, 1921	86.1	73.6	5.38	4.07	1.31	99.6	46.4	8.00	4.25	153	100	9
Pitch pine (<i>Pinus rigida</i>)	818	433	Mar. 26, 1920	76.4	68.0	5.58	3.76	1.82	84.3	—	7.50	4.50	160	100	10
—	—	443	May 3, 1920	76.8	68.6	5.52	4.30	1.22	87.5	41.7	8.00	4.00	153	100	5
Pond pine (<i>Pinus rigida serotina</i>)	821	591	June 13, 1921	124.2	94.5	4.95	3.81	1.14	63.2	37.9	7.25	3.50	155	100	20
—	—	593	June 13, 1921	109.6	83.5	5.12	3.86	1.26	71.1	—	11.00	5.25	148	100	10
Sand pine (<i>Pinus clausa</i>)	178	403	Nov. 6, 1919	48.0	39.4	5.42	4.28	1.14	167.3	54.6	8.00	5.00	153	100	10
—	—	406	Sept. 9, 1920	86.1	72.3	3.90	2.90	1.00	84.8	—	8.00	5.00	148	80	29
Scotch pine (<i>Pinus sylvestris</i>)	795	456	Mar. 24, 1921	78.0	66.8	5.47	4.97	0.50	89.5	—	8.00	2.75	153	100	10
—	—	558	Jan. 23, 1907	44.4	37.3	4.35	2.84	1.51	121.0	44.0	6.20	5.20	153	90	—
Virginia pine (<i>Pinus virginiana</i>)	—	3	Mar. 4, 1907	25.0	22.2	4.26	2.87	1.39	202.0	72.0	5.00	8.50	150	100	—
Shortleaf pine (<i>Pinus echinata</i>)	342	432	Mar. 25, 1920	80.4	70.7	4.40	4.12	1.28	87.4	40.8	8.00	4.00	161	100	4
Western yellow pine (<i>Pinus ponderosa</i>)	—	528	Feb. 12, 1921	57.4	49.6	4.70	3.69	1.01	120.8	—	8.00	2.50	150	100	4
—	—	333	Mar. 28, 1917	85.0	60.9	5.61	4.31	1.30	—	—	8.00	3.00	149	96	13
Pelican (Monkey-puzzle) (<i>Araucaria araucana</i>)	455	373	Mar. 28, 1917	102.2	75.8	5.56	4.26	1.30	—	—	8.00	3.50	152	100	12
—	—	376	June 4, 1918	113.9	80.9	5.64	4.40	1.24	—	—	5.50	2.75	155	100	14
—	—	—	June 7, 1918	—	—	4.59	3.50	1.09	—	—	3.50	3.50	152	100	10

Species			Ship- ment No.	Cook No.	Date	Cooking data—Continued			Strength data										Conditions during test	
						Yields based on oven-dry weight of chips effused		Bleach required (55 per cent available chlo- rine) per 100 pounds oven-dry pulp	Calen- dered	Weight per ream 24 by 36—500	Thick- ness per square inch	Mullen test per square inch	Strength factor per pound per ream	Aver- age break- ing length	Aver- age double folds	Aver- age Elmen- dorf tearing test	Rela- tive humid- ity	Tem- pera- ture		
						Crude pulp	Screen- ings													
Lumber pine (<i>Pinus flexilis</i>)	465	548	Mar. 10, 1921	43.1	1.87	24	Yes	42.5	3.1	26.7	.63	1.62	4,144	162	65	70				
Pinon (<i>Pinus edulis</i>)	792	506	Dec. 14, 1920	50.3	.69	27	Yes	40.5	3.6	31.4	.77	2.40	5,758	74	64	76				
Sugar pine (<i>Pinus lambertiana</i>)		357	Nov. 13, 1917	50.4	.05	31	Yes	41.5	3.7	28.8	.69	2.30	6,925	444	60	69				
Northern white pine (<i>Pinus strobus</i>)	501	368	Dec. 7, 1917	56.5	1.02	46	Yes	48.1	4.0	32.7	.79	2.10	5,710	456	61	64				
		369	Dec. 7, 1917	55.6	.50		Yes	48.1	5.0	30.7	.64	2.12	5,145	433	61	64				
Jack pine (<i>Pinus banksiana</i>)	798	434	Mar. 29, 1920	50.3	6.08	34	Yes	38.0	2.7	18.6	.49	2.14	4,082	167	65	72				
		437	Apr. 4, 1920	47.1	2.42	33	Yes	38.5	2.7	21.5	.56	1.17	5,403	150	65	75				
		500	Nov. 21, 1920	46.9	.40		Yes	59.5	4.1	42.5	.72	2.53	4,472	258	66	71				
Loblolly pine (<i>Pinus taeda</i>)	801	422	Mar. 10, 1920	50.6	1.82	33	Yes	55.2	4.6	28.4	.51	2.40	4,667	453	67	70				
Lodgepole pine (<i>Pinus contorta</i>)	323	554	Mar. 18, 1921	43.5	.84	12	Yes	70.8	5.1	30.8	.44	2.09	4,056	204	68	78				
		343	Aug. 13, 1917	48.6	1.01	24	Yes	45.5	3.7	36.7	.81	4.61	6,815	1,055	68	78				
Longleaf pine (<i>Pinus palustris</i>)		533	Mar. 17, 1921	44.1	.44	12	Yes	48.1	3.5	35.6	.74	2.34	6,290	939	65	78				
Monterey pine (<i>Pinus radiata</i>)	259	301	Oct. 18, 1916	54.7		20	(⁹)	47.0	4.1	22.9	.49	2.42	4,156	262	64	68				
Norway pine (<i>Pinus resinosa</i>)	501	508	Dec. 10, 1920	49.9	2.82	24	Yes	45.5	3.5	26.6	.58	1.35	5,000	134	64	72				
		428	Mar. 19, 1920	50.1	.44	35	Yes	33.0	2.6	16.8	.51	1.97	5,889	305	67	70				
Pitch pine (<i>Pinus rigida</i>)	818	433	Mar. 14, 1921	44.9	.92	18	Yes	78.4	2.1	35.1	.45	2.18	3,417	202	65	78				
Pond pine (<i>Pinus rigida serotina</i>)	821	443	Mar. 26, 1920	49.1	5.42	32	Yes	33.0	2.5	12.2	.37	1.97	4,622	76	65	71				
		591	May 3, 1921	45.6	4.96	30	Yes	43.5	3.0	23.9	.55	2.75	4,778	120	64	77				
		503	June 8, 1921	44.2	3.50	14	Yes	51.0	3.9	23.9	.47	3.18	3,213	38	66	92				
Sand pine (<i>Pinus clausa</i>)	178	403	Nov. 6, 1919	44.2	3.50	17	Yes	48.0	3.5	20.1	.42	1.93	3,256	38	66	93				
		20	Sept. —, 1912	23.1	.40		Yes	41.5	2.9	18.4	.44	1.80	4,175	225	64	78				
Scotch pine (<i>Pinus sylvestris</i>)	795	456	Sept. 9, 1920	49.9	12.20	30	Yes	38.5	3.2	26.3	.68	1.54	4,716	265	64	83				
Virginia pine (<i>Pinus virginiana</i>)	19-21	568	Mar. 21, 1907	36.8	1.10	120	Yes	48.0	3.8	19.2	.40	2.03	3,827	25	64	75				
		3	Jan. 23, 1907			728														
Shortleaf pine (<i>Pinus echinata</i>)	342	432	Mar. 25, 1920	48.0			Yes	39.5	3.0	17.4	.44	1.84	4,949	145	64	69				
Western yellow pine (<i>Pinus ponderosa</i>)	455	528	Feb. 2, 1921	44.0	4.88	627	Yes	60.4	5.4	19.1	.32	.88	2,811	33	62	73				
		333	Mar. 16, 1917	58.0		(⁹)	Yes	56.0	3.4	31.2	.56	2.40	3,620	143	65	79				
Peluen (Monkey-puzzle) (<i>Arbutus aucuparia</i>)		373	Mar. 28, 1917	47.6	.46		Yes	49.0	4.4	22.8	.47	2.60	4,510	47	66	71				
		376	June 3, 1918	53.1	.70		Yes	47.0	3.7	21.0	.44	2.55	3,560	66	68	81				
		376	June 7, 1918	51.5	.30		Yes	53.0	4.0	23.3	.44	3.07	3,457	156	63	83				

¹ Pulp extremely raw. Not run into paper.² Unbleached pulp of very good color.³ Unbleached pulp of very good color. Paper exceptionally free from shives.⁴ Pulp badly burned. Not run into paper.⁵ Ratio lime to magnesia, 17:10.⁶ Pulp evidently burned.⁷ Pulp of excellent strength and quality. Not run into paper.

TABLE 9.—Cooking and strength data: The pines—soda or sulphate process

Species	Shipment No.	Cook No.	Date	Quantity of wood used		Cooking data										Black liquor ratio combined to total alkali				
				Moist weight	Oven-dry weight	Impregnating liquor				Penetration		Cooking liquor								
						Before penetration		After penetration		Duration	Pressure per square inch	° C.	Concentration		Per 100 pounds bone-dry chips					
Gal- lons	Grams per liter	Grams per liter	Gal- lons	Grams per liter	Grams per liter	Grams per liter	Min- utes	Lbs.	Lbs.	Grams per liter	Grams per liter	NaOH	Na ₂ S	NaOH	Na ₂ S	Volume	Gal- lons			
Lbs.	Lbs.																		Per cent	
Lumber pine (<i>Pinus flexilis</i>)	465	189	Oct. 15, 1917	64.2	57.0	50.0	56.4	40.0	35.5	48.8	41.0	15	100	62	70.7	34.0	15.9	7.7	27.0	61.9
		193	Oct. 23, 1917	64.2	57.0	50.0	56.4	40.0	35.5	48.8	41.0	15	100	62	70.7	34.0	15.9	7.7	27.0	61.9
		717	Jan. 4, 1921	80.9	62.5	48.8	50.5	31.5	35.9	43.8	31.3	15	100	48	100.0	20.0	25.0	5.0	30.0	80.4
		718	Jan. 6, 1921	95.4	62.5	48.8	50.5	31.5	35.9	43.8	31.3	15	100	48	100.0	20.0	25.0	5.0	30.0	80.4
		726	Jan. 24, 1921	44.4	31.1	50.0	56.4	40.0	35.5	48.8	41.0	20	105	78	57.7	24.9	14.3	6.2	29.9	75.4
Piñon (<i>Pinus edulis</i>)	792	727	Feb. 3, 1921	34.6	28.8	50.0	56.4	40.0	35.5	48.8	41.0	20	105	78	57.7	24.9	14.3	6.2	29.9	75.4
		728	Feb. 16, 1921	32.4	27.4	50.0	56.4	40.0	35.5	48.8	41.0	20	105	78	57.7	24.9	14.3	6.2	29.9	75.4
		127	Apr. 27, 1917	64.4	56.4	50.0	56.4	40.0	35.5	48.8	41.0	20	105	78	57.7	24.9	14.3	6.2	29.9	75.4
		199	Oct. 30, 1917	68.9	60.5	50.0	56.4	40.0	35.5	48.8	41.0	20	105	78	57.7	24.9	14.3	6.2	29.9	75.4
		229	Jan. 11, 1918	65.0	58.5	50.0	56.4	40.0	35.5	48.8	41.0	20	105	78	57.7	24.9	14.3	6.2	29.9	75.4
Sugar pine (<i>Pinus lambertiana</i>)	455	723	Jan. 19, 1921	66.1	59.6	50.0	56.4	40.0	35.5	48.8	41.0	20	115	55	101.4	33.5	12.5	7.6	23.8	84.8
		139	June 5, 1917	90.4	52.2	50.0	56.4	40.0	35.5	48.8	41.0	20	115	55	101.4	33.5	12.5	7.6	23.8	84.8
		195	Oct. 24, 1917	64.1	56.1	49.7	51.1	31.7	36.9	44.8	31.9	10	110	44	64.3	27.6	15.6	6.1	22.6	64.0
		729	Feb. 17, 1921	64.2	56.2	50.0	56.4	40.0	35.5	48.8	41.0	10	102	43	63.0	28.9	12.9	5.9	24.6	74.0
		730	Feb. 18, 1921	62.0	55.0	45.0	51.1	31.7	36.9	44.8	31.9	10	102	43	60.7	17.8	15.1	4.4	29.9	86.0
Northern white pine (<i>Pinus strobus</i>)	501	730	Feb. 18, 1921	62.0	55.0	45.0	51.1	31.7	36.9	44.8	31.9	10	102	43	60.7	17.8	15.1	4.4	29.9	86.0
		21	Apr. 11, 1916	120.0	71.3	45.0	70.0	40.0	36.2	51.9	35.3	20	100	85	87.3	30.6	15.0	5.3	20.6	76.2
		22	Apr. 13, 1916	120.0	70.1	44.0	82.5	50.0	36.2	61.3	46.0	20	100	84	102.0	38.6	16.8	6.4	19.7	84.8
		24	Apr. 17, 1916	120.0	73.4	45.0	60.0	35.0	33.8	44.7	31.8	20	100	85	70.6	29.6	15.5	5.2	22.9	74.0
		77	Aug. 18, 1916	82.0	66.8	50.0	60.0	35.0	38.2	48.1	35.0	15	100	84	85.3	30.6	14.5	5.2	20.4	86.0
Jack pine (<i>Pinus banksiana</i>)	431	85	Sept. 6, 1916	56.8	50.1	50.0	60.0	35.0	38.2	48.1	35.0	15	100	84	76.5	26.0	16.2	5.5	25.4	93.4
		89	Sept. 13, 1916	51.2	44.8	50.0	60.0	35.0	38.2	48.1	35.0	15	100	84	76.5	26.0	16.2	5.5	25.4	93.4
		90	Sept. 15, 1916	82.0	71.6	50.0	60.0	35.0	38.2	48.1	35.0	15	100	84	76.5	26.0	16.2	5.5	25.4	93.4
		92	Sept. 30, 1916	82.1	72.2	52.0	43.1	21.4	39.4	45.1	21.4	25	100	70	63.2	19.5	10.9	3.1	19.1	91.2
		100	Oct. 5, 1916	58.0	48.7	50.0	43.1	21.4	39.4	45.1	21.4	25	100	70	57.2	18.0	12.6	3.9	26.2	92.2
Jack pine (<i>Pinus banksiana</i>)	431	222	Oct. 12, 1917	74.1	58.0	50.0	43.1	21.4	39.4	45.1	21.4	25	100	70	57.2	18.0	12.6	3.9	26.2	92.2
		247	July 8, 1919	71.6	49.9	50.0	43.1	21.4	39.4	45.1	21.4	25	100	70	57.2	18.0	12.6	3.9	26.2	92.2
		249	July 10, 1919	80.4	54.0	50.0	43.1	21.4	39.4	45.1	21.4	25	100	70	57.2	18.0	12.6	3.9	26.2	92.2
		251	July 14, 1919	73.6	50.8	50.0	43.1	21.4	39.4	45.1	21.4	25	100	70	57.2	18.0	12.6	3.9	26.2	92.2
		836	Mar. 8, 1922	170.0	100.0	61.0	107.8	43.0	43.0	97.2	97.2	30	105	24	90.0	42.3	15.8	2.0	44.7	80.3

TABLE 9.—Cooking and strength data: The pines—soda or sulphate process—Continued

Species	Cooking data																		
	Shipment No.	Cook No.	Date	Quantity of wood used		Impregnating liquor				Penetration		Cooking liquor				Black liquor ratio combined to total alkali			
						Before penetration		After penetration				Concentration		Per 100 pounds bone-dry chips					
				Moist weight	Oven-dry weight	Volume	Concentration		Volume	Concentration		Duration	Pressure per square inch	Temperature	Concentration		Per 100 pounds bone-dry chips		
							NaOH	Na ₂ S		NaOH	Na ₂ S				NaOH		Na ₂ S	NaOH	Na ₂ S
Virginia pine (<i>Pinus virginiana</i>).	818 513 207	17 16 207	Nov. 24, 1920 Nov. 22, 1920 Nov. 19, 1917	168.3 167.5 112.2	88.5 85.8 83.8	51.6 50.0 50.0	38.4 50.0 35.0	43.8 40.9 40.3	43.3 39.5 39.5	40.2 32.2 32.2	Grams per liter	Grams per liter	Grams per liter	Grams per liter	NaOH	Na ₂ S	Volume		
Shortleaf pine (<i>Pinus echinata</i>).	342 703 704	122 703 704	Nov. 15, 1920 Nov. 17, 1920 Aug. 5, 1920	86.7 88.0 133.9	85.2 76.7 106.0	78.4 88.0 64.7	76.7 88.0 57.5	50.0 49.0 62.0	43.8 40.9 62.9	39.5 39.5 55.9	40.3 40.3 26.9	43.3 39.5 55.9	32.2 32.2 45.0	103.0 87.7 92.6	28.4 24.1 25.0	15.3 43.1 25.0	12.3 12.0 18.8	6.1 3.1 6.3	33.0 30.0 30.0
Slash pine (<i>Pinus caribaea</i>).	752 297 298 299	297 297 298 299	Sept. 8, 1920 Sept. 9, 1920 Feb. 2, 1916 Feb. 21, 1917	64.7 62.0 70.7 76.0	57.5 55.8 62.9 57.4	57.5 55.8 50.0 50.0	57.5 55.8 40.0 30.0	57.5 55.0 35.0 35.0	57.5 55.0 41.1 26.2	57.5 55.0 41.1 26.2	57.5 55.0 41.1 26.2	57.5 55.0 41.1 26.2	57.5 55.0 41.1 26.2	67.7 53.7 92.6 110.0	15.3 13.4 25.0 110.0	19.6 13.4 16.8 13.8	4.4 5.0 7.8 12.4	34.8 80.8 20.3 13.6	30.0 80.0 72.0 93.0
Western yellow pine (<i>Pinus ponderosa</i>).	455 71 170 781	115 117 118 170	Feb. 26, 1917 Mar. 8, 1917 Aug. 4, 1917 June 15, 1921	76.0 76.0 60.6 64.3	52.8 55.1 53.8 58.5	57.4 55.1 50.0 58.5	57.4 55.1 50.0 58.5	57.4 55.1 50.0 58.5	57.4 55.1 50.0 58.5	57.4 55.1 50.0 58.5	57.4 55.1 50.0 58.5	57.4 55.1 50.0 58.5	57.4 55.1 50.0 58.5	106.0 77.5 74.8 90.0	43.4 35.0 24.8 24.8	43.4 35.0 18.8 18.8	15.0 12.0 6.2 6.2	13.6 13.6 9.8 9.8	93.0 88.0 26.0 29.9
Pehuén (Monkey-puzzle) (<i>Araucaria arucana</i>).	241 242 243	241 242 243	May 29, 1918 June 5, 1918 June 10, 1918	131.3 112.0 115.1	89.7 75.0 91.0	24.9 75.0 91.0	24.9 75.0 91.0	24.9 75.0 91.0	24.9 75.0 91.0	24.9 75.0 91.0	24.9 75.0 91.0	24.9 75.0 91.0	24.9 75.0 91.0	59.6 80.0 59.5	26.5 21.9 24.0	14.1 6.3 12.4	35.0 33.0 5.0	46.6 28.4 12.4	82.9 83.3 83.3

Cooking data—Continued										Strength data											
Species	Shipment No.	Cook No.	Date	Steam			Yields based on oven-dry weight of chips charged			Bleach required (35 per cent available chlorine) per 100 pounds oven-dry pulp	Calendered	Weight per ream 24 x 36—500	Thickness	Mullen test per square inch	Strength factor per pound per ream	Average stretch	Average breaking length	Average double folds	Average Elmhendorf tearing test	Conditions during test	
				Maximum pressure per square inch	Pressure increased	Duration at maximum pressure	Crude pulp	Screenings	Oil per ton bone-dry chips											Relative humidity	Temperature
Lumber pine (<i>Pinus flexilis</i>)	465	189	Oct. 15, 1917	100	20	135	47.0	.36			No.	41.5	3.7	46.4	1.12	2.48	6,980	1,323			
		193	Oct. 23, 1917	100	25	120	48.4	.43			No.	46.5	4.6	58.6	1.26	4.1	6,770	1,540			
		717	Jan. 4, 1921	100	60	300	42.7	.23			No.										
		718	Jan. 6, 1921	100	60	360	36.2	.36			No.										
		726	Jan. 24, 1921	95	60	320	36.3	2.09			Yes										
Piñon (<i>Pinus edulis</i>)	792	727	Feb. 3, 1921	100	60	375	37.9				Yes	46.0	5.6	24.9	.54	2.48	3,810	368			
		728	Feb. 16, 1921	100	45	360	34.5				Yes	56.6	4.9	39.6	.70	2.77	5,010	1,200			
		1127	Apr. 27, 1917	90	10	150	50.4	.11			N. B.	51.9	4.4	33.9	.65	2.54	576	510			
		1128	Oct. 30, 1917	100	15	150	47.4	.03	.05		No.	43.5	4.4	54.6	1.20	3.00	7,450	1,189			
		1129	Jan. 11, 1918	105	20	300	44.0	.06			No.	42.5	3.7	48.4	1.14	3.50	7,110	2,638			
Sugar pine (<i>Pinus lambertiana</i>)	455	723	Jan. 19, 1921	100	60	300	35.2				No.	39.5	3.2	35.6	.90	3.60	6,850	1,042			
		1139	June 5, 1917	90	15	155	51.4	.10			Yes	43.5	3.9	58.0	1.33	3.90	4,025	1,320			
		1195	Oct. 24, 1917	100	25	150	48.8	.04			No.	41.5	3.9	55.3	1.33	4.10	7,100	1,836			
		729	Feb. 17, 1921	100	60	300	38.0	.10			Yes	49.1	3.7	41.8	.85	2.92	6,457	703			
		730	Feb. 18, 1921	100	60	375	37.1				Yes	54.8	4.1	45.3	.83	3.05	7,212	514			
Northern white pine (<i>Pinus strobus</i>)	501	21	Apr. 11, 1916	80	15	180	48.6	.76	1.20		No.	47.0	4.8	54.0	1.15	3.86	7,090	1,613			
		22	Apr. 13, 1916	75	15	180	45.0	.35	.80		No.	49.0	4.1	52.9	1.08	3.75	7,220	1,312			
		24	Apr. 17, 1916	80	15	180	47.9	.80	1.10		No.	44.0	4.4	66.8	1.52	4.53	7,800	2,178			
		77	Aug. 18, 1916	120	40	90	51.4	10.90			No.	39.0	3.9	46.9	1.20	4.65	6,620	1,298			
		85	Sept. 6, 1916	80	35	180	48.6	3.20			No.	43.5	4.4	63.5	1.46	3.70	6,370	1,410			
Jack pine (<i>Pinus banksiana</i>)	431	89	Sept. 13, 1916	100	35	185	55.2	11.00			No.	42.5	4.8	49.3	1.16	2.90	6,250	704			
		90	Sept. 15, 1916	100	45	130	48.7	2.25			No.	40.5	3.8	50.2	1.24	4.10	7,570	1,280			
		92	Sept. 20, 1916	100	45	140	56.5	19.35			No.	59.0	3.8	57.8	1.98	2.30	4,705	1,868			
		100	Oct. 5, 1916	100	35	210	49.6	2.98			No.	40.0	4.1	50.8	1.27	4.10	6,960	1,383			
		222	Dec. 12, 1917	95	30	45	96.4				No.										
		247	July 8, 1919	100	60	180	42.1				No.	41.5	3.4	34.0	.82	4.19	7,130	1,147			
		249	July 10, 1919	100	60	180	50.9				No.	38.0	4.0	29.0	.76	3.28	5,778	207			
		251	July 14, 1919	100	60	180	54.4				No.	41.5	4.2	34.5	.83	4.56	5,735	629			
		836	Mar. 8, 1922	100	50	240	37.0				No.										

Footnotes at end of table.

TABLE 9.—Cooking and strength data: The pines—soda or sulphate process—Continued

Species	Cooking data—Continued				Strength data														Conditions during test	
	Shipment No.	Cook No.	Date	Steam		Yields based on oven-dry weight of chips charged			Calendered	Weight per ream 24 x 36—500	Thickness	Mullen test per square inch	Strength factor per pound	Average stretch	Average breaking length	Average double folds	Average Elmendorf tearing	Relative humidity		Temperature
				Maximum pressure per square inch	Pressure increased	Duration at maximum pressure	Crude pulp	Screenings												
Loblolly pine (<i>Pinus taeda</i>)	801	231	Jan. 15, 1918	100	20	305	50.2	.34		Lbs.	No.	Lbs.	0.001 in.	Lbs.	Points	Per cent	Meters	Gms.	Per cent	° F
		239	Apr. 7, 1920	100	180	60	39.8	.06		65		55.7	6.1	35.6	.64	3.30	4,650	448	69	72
		260	Apr. 8, 1920	100	135	315	35.5	.02		24										
		263	Apr. 13, 1920	106	120	360	38.5			20										
		264	Apr. 15, 1920	103	105	360	35.0	.20		25										
	323	780	June 14, 1921	100	75	240	41.5			35	Yes	55.7	5.7	42.4	.76	3.60	4,943	553	66	91
		824	June 27, 1922	106	60	360	39.9			N.B.	Yes	44.4	3.9	23.6	.53	2.30	1,707	67	66	84
		54	Aug. 11, 1916	80	30	180	48.5	1.66		Yes	42.5	3.7	53.1	1.25	4.10	6,510	1,398	65		
		55	Aug. 12, 1916	100	30	120	46.6	1.26		Yes	39.5	3.6	54.1	1.37	3.70	7,280	1,535	62		
		1216	Dec. 3, 1917	100	25	245	47.4	.33		No.	47.2	4.9	48.6	1.03	2.99	6,870	748	61	68	
Lodgepole pine (<i>Pinus contorta</i>)	323	5	Apr. 20, 1909	110	30	600	39.2	.20	41	(1)	36.0	4.6	21.4	.59	2.00	3,980	139	66		
		201	Oct. 7, 1915	80	45	105	54.2	2.87	2.0	No.	40.5	3.9	37.6	.93	3.15	6,525	1,452			
		209	Oct. 1, 1915	90	35	190	42.7			Yes	48.0	4.4	42.3	.88	3.04	6,400	1,467			
		210	Oct. 6, 1915	60	25	180	48.3			No.	46.5	4.8	44.8	.96	2.62	6,720	943			
		212	Oct. 15, 1915	80	40	190	49.1			Yes	38.5	3.8	37.9	.98	3.49	5,930	1,038			
	259	215	Oct. 25, 1915	100	30	120	44.9	3.76		No.	38.5	4.0	38.5	1.00	2.34	6,740	410			
		216	Oct. 26, 1915	100	40	140	44.2	1.25		No.	56.5	5.7	65.0	1.15	2.77	6,985	707			
		223	Nov. 19, 1915	110	75	35	60.5			Yes	49.0	6.0	21.8	.44	1.00	3,640	51			
		232	Dec. 10, 1915	80	40	180	41.1	.15	1.64	30	No.	47.0	4.6	36.4	.78	2.00	7,250	142		
		176	236	Dec. 21, 1915	90	60	160	46.6	.72	12.62	No.	46.0	4.4	46.3	1.01	3.44	7,765	759		
Longleaf pine (<i>Pinus palustris</i>)	181	241	Jan. 13, 1916	80	45	150	40.4	.44		No.	40.0	4.2	38.4	.96	2.41	7,950	601	62		
		242	Feb. 3, 1916	80	25	180	42.7	.26		Yes	43.5	4.0	33.7	.77	3.06	6,240	569	76		
		243	Apr. 27, 1916	80	10	180	52.5	7.05		Yes	38.0	3.2	25.0	.66	3.83	5,355	714			
		244	do.	80	10	180	24.9			No.	38.5	4.0	26.6	.69	3.30	4,995	447	65		
		251	Oct. 20, 1916	80	25	180	36.4	1.20	2.30	No.	38.5	4.0	26.6	.69	3.30	4,995	447	65		
	126	254	Oct. 25, 1916	80	25	210	33.2	2.02	6.70	No.	38.5	4.2	23.9	.62	2.85	4,720	363	68		
		255	Oct. 27, 1917	100	10	145	47.8			No.	42.5	4.6	37.0	.87	3.80	5,850	608	65	70	

Monterey pine (<i>Pinus radiata</i>).	Oct. 31, 1917	100	15	150	52.3	.07			No.	48.1	4.7	49.5	1.03	3.60	5,670	2,191	75
	Jan. 10, 1921	100	105	360	43.2	.34	N. B.		N. B.	78.2	10.4	48.0	.61	2.04	3,537	422	65
	Jan. 12, 1921	91	75	360	40.9		N. B.		N. B.	78.2							87
	June 1, 1917	90	20	165	53.8	.13			Yes	54.0	4.6	65.4	1.21	4.10	7,365	1,375	66
	June 13, 1917	100	15	180	50.8	.00	60		No	113.0	9.6	76.9	.68	4.80	4,810	1,906	72
	June 18, 1917	100	15	180	50.8	.00	60		No	113.0	9.6	76.9	.68	4.80	4,810	1,906	66
	July 27, 1917	110	25	120	48.3	1.96	.05		No	46.5	4.1	59.3	1.08	4.30	6,880	1,170	88
	July 27, 1917	100	70	300	36.7		24		Yes	60.4	4.2	20.0	.43	3.87	4,186	41	51
	July 27, 1917	100	70	300	40.7		N. B.		Yes	38.0	3.2	16.5	.43	2.10	3,700	104	66
	June 2, 1921	100	70	360	40.7				No	51.0	4.4	55.1	1.08	4.60	6,960	1,236	93
	June 27, 1917	102	15	175	48.9	.13	.32		Yes	51.9	4.0	29.2	.56	1.94	4,144	38	66
	Nov. 8, 1920	100	45	360	38.6		24		Yes	51.9							72
	Nov. 12, 1920	100	90	360	36.9		27										
	Nov. 12, 1920	100	90	360	42.7		N. B.										
	Apr. 12, 1923	100	75	300	40.6		30		Yes	131.8	13.0	96.7	.73	3.64	4,889	4,890	597
	Apr. 13, 1923	100	75	300	40.6		30		Yes	131.8							65
	Apr. 16, 1923	100	75	180	48.6		N. B.		(19)								72
	Nov. 14, 1912	100	60	480	40.1	1.00	13 21		Yes	49.0	3.7	37.4	.76	2.32	5,788	608	66
	Sept. 10, 1920	100	70	270	34.5				Yes	49.0							72
	Sept. 13, 1920	100	75	240	41.7		36										
	Sept. 14, 1920	115	95	300	36.1		22										
	Nov. 22, 1920	100	120	330	33.6		16										
	Nov. 22, 1920	100	25	175	47.4	.11	.40		No	52.9	4.4	48.7	.92	5.00	6,390	1,413	63
	Nov. 19, 1917	100	15	165	50.9	.03			No	49.0	5.1	40.2	.82	4.00	5,480	458	65
	Mar. 20, 1917	90	15	165	50.9	.03			No	49.0							
	Nov. 15, 1920	100	120	270	41.7		30		Yes	42.5	2.9	18.6	.44	1.78	3,771	31	65
	Nov. 17, 1920	100	75	360	37.1		N. B.		Yes	42.5	3.9	25.7	.63	2.25	5,155	921	66
	Aug. 5, 1920	100	75	360	37.9		18 28		Yes	40.5							87
	Sept. 8, 1920	100	90	240	48.7		17 30		Yes	40.5							73
	Sept. 9, 1920	117	70	300	37.0		N. B.										
	Feb. 2, 1916	80	45	180	43.4	.10			No	44.0	3.9	73.5	1.67	3.05	10,750	497	
	Feb. 21, 1917	100	20	120	46.2				No	42.5	4.1	43.0	1.01	3.60	6,780	1,378	
	Feb. 26, 1917	80	20	180	54.1	.30			No	49.0	4.2	57.8	1.18	4.60	7,660	681	66
	Mar. 8, 1917	100	25	135	53.6	.44			No	35.8	4.1	47.3	1.32	3.00	7,840	778	65
	June 4, 1917	90	10	170	44.0	.24			No	38.5	3.4	32.0	.83	3.40	6,080	770	67
	Aug. 15, 1921	100	90	300	36.3		N. B.		No	38.5	6.8	54.1	.73	2.77	4,800	2,738	85
	May 3, 1911	70	60	480	54.0	.07			Yes	15.0	1.1	17.7	1.18	2.93	4,862	240	92
	May 29, 1918	100	70	180	46.5	.10	27		Yes	43.5	3.4	22.8	.52	2.88	4,575	462	83
	June 5, 1918	100	40	300	43.5	.10	44		No	58.5	5.2	31.6	.54	2.88	4,575	462	66
	June 10, 1918	100	40	170	49.0	.37			No	36.0	3.9	26.9	.75	3.20	5,040	517	82

1 Recook of pulp from soda cook with 45 per cent yield.

2 23.3 g. p. l. N22 Co in cooking liquor.

3 11.1 g. p. l. N22 Co in cooking liquor.

4 11.1 g. p. l. N22 Co in cooking liquor.

5 Water-soaked chips.

6 Equal parts water-soaked and air-dry chips mixed.

7 Unbarked wood; 96 per cent wood, 4 per cent bark.

8 Bark only; pulp shivvy and unscreenable.

9 Yaryan process shivvy chips retained on 12-mesh screen (70 per cent).

10 Unextracted chips retained on screen (64 per cent).

11 Pulp of good quality. Not run into paper.

12 2.2 gallons distilled during pressure increase period.

13 12 per cent bleach in two steps.

14 Paper of fair strength; no strength tests recorded.

15 18 per cent bleach in two steps.

16 Paper made from bleached pulp.

17 16 per cent bleach in two steps.

18 Waterleaf sheet of pulp.

Species	Cooking data—Continued				Strength data										Conditions during test	
	Ship-ment No.	Cook No.	Date	Yields based on oven-dry weight of chips charged		Bleach-able per cent (35 chlorine per 100 pounds oven-dry pulp)	Weight per ream 24 x 36—500	Thick-ness 0.001 in.	Mullen test per square inch	Strength factor per pound per ream	Aver- age stretch	Aver- age break- ing length	Aver- age double- fold	Aver- age Elmen- dorf tearing test	Rela- tive humid- ity	Tem- perature
				Crude pulp	Screen- ings	Pounds	Pounds	0.001 in.	Pounds	Points	Per cent	Meters		Grams	Per cent	° F.
Alpine fir (<i>Abies lasiocarpa</i>)	271-3	487	Oct. 28, 1920	49.2		16	Yes	30.0	3.3	45.6	.31	7.039	683	---	63	77
		494	Nov. 12, 1920	43.5		10	Yes	47.0	3.5	37.7	.80	6.625	693	---	65	70
		497	Nov. 17, 1920	49.0		26	Yes	51.0	3.8	40.8	.75	6.902	1,291	---	65	69
Balsam fir (<i>Abies balsamea</i>)	501	345	Oct. 1, 1917	44.5	.28	20	Yes	38.4	2.8	29.6	.75	6.655	1,192	---	64	62
		349	Oct. 18, 1917	48.1	.12	30	Yes	39.0	3.5	35.0	.92	6.677	1,109	---	65	77
		354	Nov. 8, 1917	48.0	.10	26	Yes	44.5	4.1	45.0	1.01	7.008	918	---	63	77
		337	July 12, 1917	43.4	1.30	24	Yes	43.5	4.0	21.1	.49	2.65	220	---	---	---
		338	July 13, 1917	48.5	.22	17	Yes	45.5	4.3	30.0	.67	2.52	5,500	---	65	95
Lowland white fir (<i>Abies grandis</i>)	490	341	July 18, 1917	49.6	.44	24	Yes	42.5	4.1	30.1	.71	2.65	740	---	66	96
		498	Nov. 18, 1920	55.1	.70	30	Yes	53.8	3.9	42.9	.80	2.43	6,098	---	65	70
		507	Dec. 15, 1920	48.8		22	Yes	38.5	3.0	28.0	.73	1.53	6,639	---	60	70
		304	Nov. 10, 1916	55.8	.66	45	Yes	47.5	4.2	32.9	.69	1.75	6,160	---	65	94
Noble fir (<i>Abies nobilis</i>)	271-1	594	June 14, 1921	46.4	.16	10	Yes	43.5	3.1	34.8	.80	2.05	5,262	---	65	---
Red fir (<i>Abies magnifica</i>)	---	326	Jan. 4, 1917	51.1	1.11	335	Yes	41.5	3.7	47.5	1.14	1.82	7,250	---	65	---
		524	Jan. 26, 1921	48.2	.25	20	Yes	42.5	3.7	55.5	1.30	1.75	8,206	---	65	70
Silver fir (<i>Abies amabilis</i>)	271-2	353	Oct. 24, 1917	48.7	.13	30	Yes	42.5	3.8	29.3	.69	2.62	5,800	---	64	74
		356	Nov. 12, 1917	50.8	.13	27	Yes	40.5	3.7	34.8	.86	2.41	730	---	64	75
		8	Mar. 3, 1908	42.1	.70	13	(^c)	---	---	---	---	---	---	---	---	---
White fir (<i>Abies concolor</i>)	35-37	525	Jan. 27, 1921	49.3	.35	925	Yes	45.5	3.4	39.5	.86	2.20	6,510	75	65	72
	455	429	Mar. 22, 1920	59.2	5.18	(^e)	Yes	41.5	3.6	15.3	.37	1.41	4,156	71	65	72
Douglas fir (<i>Pseudotsuga taxifolia</i>)	338	439	Apr. 8, 1920	48.8	.82	---	Yes	46.0	3.6	23.2	.50	1.80	3,806	80	66	76
		557	Mar. 23, 1921	42.6	4.14	22	Yes	48.1	3.6	18.3	.38	1.58	3,781	161	66	74

^a Pulp apparently of excellent strength; not run into paper.

^b Unbleached pulp of excellent color and quality.

^c Unbleached pulp decidedly yellow.

¹ Gas pressure held 1½ hours on account of stopped relief valve.

² Gas pressure held 2 hours.

³ Pulp very shivvy.

TABLE 11.—Cooking and strength data: The fir—Soda or sulphate process

Species	Shipment No.	Cook No.	Date	Cooking data										Cooking liquor				Black liquor ratio com- bined to total alkali	
				Quantity of wood used		Impregnating liquor						Penetration		Concentration			Per 100 pounds bone-dry chips		
						Before penetration		After penetration		Duration	Pressure per square inch	Temperature	NaOH	Naz	NaOH	Naz			
				Volume	Concentration		Volume	Concentration											
					Gal- tons	Grams per liter		Gal- tons	Grams per liter	Grams per liter	Grams per liter	Grams per liter	Grams per liter						
				Lbs.	Lbs.	Lbs.	Lbs.	Min- utes	Lbs.	° C.	Gal- tons	Lbs.	Per cent						
Alpine fir (<i>Abies lasiocarpa</i>)	271-3	42	June 15, 1916	74.0	62.6	50.0	57.5	35.0	38.4	31.7	15	35	34	33.3	12.5	5.8	20.7	77.4	
		43	June 16, 1916	74.0	61.0	50.0	69.8	28.0	36.4	27.2	15	35	34	85.5	26.8	5.6	24.8	77.4	
		44	June 19, 1916	166.8	145.9	46.0	70.0	41.0	39.4	34.6	15	60	30	70.5	25.8	6.7	31.0	77.4	
		705	Nov. 9, 1920	77.7	68.2									81.4	20.2	5.0	29.7	77.4	
		702	Nov. 19, 1920	46.4	41.4									98.6	24.6	23.9	77.8	66.5	
Balsam fir (<i>Abies balsamea</i>)	501	183	Jan. 21, 1916	50.2	45.1	37.6	66.8	40.0	29.9	54.8	30	110	96	104.0	40.3	6.2	18.5	58.0	
		284	Oct. 5, 1920	46.0	41.3	50.0	60.0	35.0	36.6	53.9	24.9	25	107	60	72.9	32.0	14.7	24.2	75.3
		128	Apr. 30, 1917	95.6	54.6	50.0	57.5	33.0	40.9	49.2	30.9	22	105	80	61.8	27.5	13.4	26.0	55.0
		197	Oct. 26, 1917	64.6	54.4	50.0	49.0	35.0	37.2	40.3	32.8	20	100	46	68.4	38.3	14.3	25.1	82.4
		710	Dec. 2, 1920	91.3	53.8									100.8	20.5	24.4	28.6	82.4	
Noble fir (<i>Abies nobilis</i>)	271-1	30	May 11, 1916	66.9	58.6	49.0	62.4	36.8	32.3	55.8	36.6	20	100	78	74.3	36.9	17.7	8.8	24.4
		40	June 13, 1916	68.0	59.7	52.0	57.5	25.1	37.1	50.1	25.3	30	25	30	71.5	23.1	15.9	5.2	26.6
		778	June 10, 1921	69.1	61.8									100.0	25.0	18.8	6.3	30.0	76.0
		779	June 13, 1921	64.9	58.1	50.0	56.0	32.0	35.7	48.5	31.2	20	110	48	70.3	32.2	16.9	7.7	28.7
		134	May 22, 1917	60.0	52.9									80.0	18.4	20.0	4.6	29.3	73.2
Silver fir (<i>Abies amabilis</i>)	271-2	712	Dec. 9, 1920	55.3	49.0								99.0	24.2	20.0	8.1	29.4	62.0	
		713	Dec. 13, 1920	57.8	50.6									33.0	19.1	8.1	29.4	62.0	
		34	June 2, 1916	68.0	57.7	52.0	65.0	38.0	36.3	56.7	41.5	20	100	30	76.1	33.0	17.5	7.9	27.6
		35	June 5, 1916	68.0	58.4	52.0	57.5	33.0	37.0	47.9	31.4	20	100	30	75.5	34.2	13.3	6.8	23.9
		196	Oct. 25, 1917	84.8	50.7	50.0	49.1	35.0	42.0	39.3	31.9	20	100	51	108.9	34.0	21.9	24.3	75.4
White fir (<i>Abies concolor</i>)	455	253	Jan. 28, 1920	45.0	40.2									90.2	30.0	16.1	5.3	21.4	68.7
		119	Mar. 9, 1917	60.0	52.8	52.1	57.6	33.4	40.3	44.6	35.0	20	105	66	68.8	37.5	15.0	8.2	26.2
		201	Nov. 1, 1917	61.1	52.3	51.9	55.0	40.0	39.2	45.6	27.9	20	102	35	99.8	21.1	25.0	3.0	30.0
		714	Dec. 15, 1920	72.3	64.3									99.8	34.6	17.2	6.1	21.3	75.8
		716	Dec. 20, 1920	61.8	54.5									137.0	41.1	15.5	5.6	16.4	80.9
Douglas fir (<i>Pseudo tsuga taxifolia</i>)	338	14	Feb. 25, 1916	90.0	78.0	45.4	73.2	38.0	30.3	56.5	38.1	35	100	95	97.5	34.6	17.2	6.1	21.3
		338	Mar. 1, 1916	90.0	78.2	45.4	68.6	39.2	34.0	48.8	36.6	35	100	88	113.0	41.1	15.5	5.6	16.4
		796	Oct. 3, 1921	70.3	62.6									100.0	41.1	15.5	5.6	16.4	85.1
		338	Mar. 1, 1916	90.0	78.0	45.4	73.2	38.0	30.3	56.5	38.1	35	100	95	97.5	34.6	17.2	6.1	21.3
		796	Oct. 3, 1921	70.3	62.6									100.0	41.1	15.5	5.6	16.4	85.1

Cooking data—Continued										Strength data											
Species	Shipment No.	Cook No.	Date	Steam			Yields based on oven-dry weight of chips charged			Bleach required (35 per cent oven-dry pulp)	Calendered	Weight per ream 24 x 36—500	Thickness	Mullen test per square inch	Strength factor per pound per ream	Average stretch	Average breaking length	Average double folds	Average Elmdorff tearing test	Conditions during tests	
				Maximum pressure per square inch	Pressure increased	Duration at maximum pressure	Crude pulp	Screenings	Oil per ton bone-dry chips											Lbs.	Per cent
Alpine fir (<i>Abies lasiocarpa</i>)	271-3	42	June 15, 1916	80	30	195	51.5	22.40	(1)	N.B.	No.	41.5	3.7	43.6	1.05	3.57	7,020	628	1,015	64	64
		43	June 16, 1916	80	15	180	50.6	1.13		N.B.	No.	42.5	3.4	42.1	.99	4.56	7,240	1,015	1,015	69	69
		44	June 19, 1916	80	30	180	49.5	.75		N.B.	No.	38.0	3.2	48.6	1.28	4.41	8,000	1,058		67	67
		701	Nov. 9, 1920	100	60	300	41.2		(2)	N.B.	No.										
		705	Nov. 19, 1920	100	75	360	43.2			N.B.	No.										
Balsam fir (<i>Abies balsamea</i>)	501	702	Nov. 10, 1920	100	75	240	27.3	6.70		N.B.	No.	40.5	3.6	62.0	1.53	2.86	10,220	778			
		183	Jan. 21, 1916	90	30	150	45.8	1.26		N.B.	No.	38.0	3.7	49.8	1.31	3.15	7,550	729			
		284	Oct. 5, 1920	100	60	300	41.2	1.26		N.B.	No.										
		128	Apr. 30, 1917	100	20	120	51.1	.17		N.B.	No.	47.6	5.0	53.8	1.13	3.50	7,230	1,057			
		197	Oct. 26, 1917	100	25	165	49.7	.04		N.B.	No.	38.0	3.8	42.2	1.11	3.50	7,230	1,083			
Lowland white fir (<i>Abies grandis</i>)	490	710	Dec. 7, 1920	90	60	360	35.3			N.B.	No.	40.5	3.2	38.7	.80	3.68	6,570	1,241			
		711	Dec. 7, 1920	95	85	360	35.0			N.B.	No.	40.5	3.2	38.7	.80	3.92	6,150	1,116			
		30	May 11, 1916	80	15	180	49.5	.17		N.B.	No.	40.5	3.2	38.7	.80	3.92	6,150	1,116			
		40	June 13, 1916	80	15	180	53.1	.44		N.B.	No.	40.5	3.2	38.7	.80	3.92	6,150	1,116			
		778	June 10, 1921	100	65	300	40.9			N.B.	Yes	61.4	5.4	53.2	.87	3.09	4,817	1,830			
Noble fir (<i>Abies nobilis</i>)	271-1	779	June 13, 1921	100	70	360	40.6			N.B.	Yes	61.4	5.4	53.2	.87	3.09	4,817	1,830			
		134	May 22, 1917	90	20	155	51.5	.00		N.B.	No.	38.0	3.5	43.7	1.13	3.50	7,570	1,464			
		712	Dec. 9, 1920	100	90	300	39.2			N.B.	No.										
		713	Dec. 13, 1920	97	60	360	40.0			N.B.	No.	43.5	3.9	37.0	.85	3.03	6,140	1,112			
		34	June 2, 1916	100	30	140	46.6	.30		N.B.	No.	39.5	3.4	41.1	1.04	3.92	6,820	1,712			
Silver fir (<i>Abies amabilis</i>)	271-2	35	June 5, 1916	80	10	180	49.9	.64		N.B.	No.	41.5	3.4	47.8	1.15	3.59	6,930	1,663			
		196	Oct. 25, 1917	100	20	150	52.2	.04		N.B.	No.	35.0	3.0	22.1	.63	2.37	5,490	495			
		253	Jan. 28, 1920	82	60	360	47.3			N.B.	No.	36.0	3.0	25.9	.72	2.80	8,110	1,072			
		119	Mar. 9, 1917	90	25	150	51.8	.25		N.B.	No.	41.5	3.9	50.7	1.22	4.50	6,700	1,256			
		201	Nov. 9, 1917	97	20	165	50.0	.07		N.B.	No.										
White fir (<i>Abies concolor</i>)	455	714	Dec. 15, 1920	100	90	285	38.9			N.B.	No.	51.5	5.15	52.6	1.02	2.31	7,750	711			
		716	Dec. 25, 1920	100	60	360	35.4			N.B.	No.	47.0	4.62	53.1	1.13	2.73	8,560	488			
		15	Feb. 25, 1916	100	30	180	42.5	.60		N.B.	No.	70.0	7.60	26.4	1.38	2.00	3,290	345			
		338	Mar. 1, 1916	90	20	180	48.0	5.10		N.B.	No.										
		796	Oct. 3, 1921	100	70	360	37.9	.12		N.B.	No.										
Douglas fir (<i>Pseudotsuga taxifolia</i>)	338																				

1 Relief gases had pleasant ketone-like odor. Condensate gave iodoform reaction.

2 Chips thoroughly soaked with water.

3 Waterleaf sheet of pulp.

Waterleaf sheet of pulp.

Chips thoroughly soaked with water.

Condensate gave iodoform reaction.

Relief gases had pleasant ketone-like odor.

Species	Cooking data—Continued					Strength data										Conditions during test	
	Shipment No.	Cook No.	Date	Yields based on oven-dry weight of chips charged		Bleach required (35 per cent available chlorine per 100 oven-dry pulp)	Calendered 24x36—500 pounds	Weight per ream 24x36—500	Thickness .001 in.	Mullen test per square inch	Strength factor per pound per ream	Average stretch	Average breaking length	Average double folds	Average Elmen-dorf tearing test	Relative humidity	Temperature
				Crude pulp	Screenings							Per cent	Meters	Grams			
				Per cent	Per cent	Pounds		Pounds		Pounds	Points	Per cent				Per cent	° F.
Carolina hemlock (Tsuga caroliniana).	822	531	Feb. 7, 1921	42.9	0.57	21	Yes	43.5	3.4	30.6	0.70	2.31	5,742	370	---	65	70
		532	Feb. 8, 1921	38.2	.45	22	Yes	55.7	4.3	45.7	.82	2.47	6,244	637	---	64	72
Eastern hemlock (Tsuga canadensis).	---	535	Feb. 15, 1921	43.0	.70	27	Yes	44.5	3.1	24.4	.55	1.77	5,146	320	140	66	72
	---	600	Sept. 21, 1921	42.2	.81	24	Yes	53.8	4.0	41.2	.77	3.01	6,762	535	228	64	69
	---	604	Sept. 27, 1921	42.8	---	28	Yes	---	---	---	---	---	---	---	---	---	---
	910-A	632	Aug. 20, 1922	48.6	4.4	---	(1)	---	---	---	.92	---	---	---	---	---	---
Western hemlock (Tsuga heterophylla).	---	404	Nov. 7, 1919	49.7	.57	17	Yes	43.5	3.1	32.6	.75	2.76	7,015	1,286	---	65	73
	325	406	Nov. 14, 1919	49.7	.10	26	Yes	55.0	4.0	46.0	.84	3.01	7,100	1,488	---	67	69
	---	412	Nov. 29, 1919	43.4	4.52	17	Yes	39.6	2.9	24.6	.62	2.98	6,055	589	---	64	71
Tamarack (Larix laricina).	---	381	July 31, 1919	38.4	.30	30	Yes	63.0	4.3	18.1	.29	1.91	3,390	990	---	65	71
	26-3	576	Apr. 27, 1921	42.2	.61	16	Yes	60.5	4.2	31.7	.52	2.48	4,087	371	---	66	65
Western larch (Larix occidentalis).	---	482	Oct. 20, 1920	43.7	14.10	33	Yes	41.5	2.9	28.6	.50	1.32	4,196	775	---	65	81
Incense cedar (Libocedrus decurrens).	277	555	Mar. 21, 1921	40.6	3.86	18	Yes	58.0	4.8	28.6	.49	1.82	4,265	114	---	67	75
Port Orford cedar (Chamaecyparis lawsoniana).	803	459	Sept. 15, 1920	40.7	1.14	42	Yes	38.0	2.6	27.3	.72	2.08	6,295	597	---	64	82
	---	461	Sept. 21, 1920	44.8	4.00	42	Yes	49.1	3.0	35.8	.73	2.60	6,091	390	---	66	74
	---	417	Feb. 20, 1920	43.3	1.55	30	Yes	36.2	2.5	18.0	---	2.58	6,091	390	---	67	79
Eastern red cedar (Juniperus virginiana).	---	523	Jan. 23, 1921	49.7	.80	28	Yes	39.5	3.1	45.3	1.15	1.90	8,014	879	---	66	70
Western red cedar (Thuja plicata).	813	521	Jan. 20, 1921	56.3	---	N.B. ³	Yes	47.0	4.9	18.4	.39	.95	3,332	8	---	65	71
Southern cypress (Taxodium distichum).	812	533	Feb. 9, 1921	43.5	.69	N.B.	Yes	37.0	2.6	25.9	.70	1.33	7,031	340	---	65	73
Redwood (Sequoia sempervirens).	368	379	July 29, 1919	47.8	.73	32	Yes	55.7	4.1	25.1	.45	3.03	4,285	185	---	66	82
	---	544	Mar. 2, 1921	41.6	1.60	24	Yes	47.0	4.0	21.4	.46	1.61	4,132	111	138	64	70
	---	435	Mar. 31, 1920	50.6	1.78	N.B.	Yes	64.0	6.1	64.0	1.00	2.34	6,675	602	---	64	76
	520	441	Apr. 16, 1920	51.7	4.42	N.B.	Yes	60.0	5.8	58.5	.98	1.75	5,828	342	---	64	76

³ Pulp raw, brash, and very dark colored.² Paper very brash and dirty.¹ Hand sheet from pulp ground in ball mill for 60 minutes.

TABLE 13.—Cooking and strength data: Hemlocks and other conifers—Soda or sulphate process

Species	Shipment No.	Cook No.	Date	Quantity of wood used		Cooking data										Black liquor ratio combined to total alkali		
				Moist weight	Oven-dry weight	Impregnating liquor				Penetration		Cooking liquor						
						Before penetration		After penetration		Duration	Pressure per square inch	Temperature	Concentration		Per 100 pounds bone-dry chips			
						Volume	Concentration	Volume	Concentration				NaOH	NaOH	Grams per liter		Grams per liter	NaOH
				Lbs.	Lbs.	Gal- lons	Grams per liter	Gal- lons	Grams per liter	Min- utes	Lbs.	°C.	Grams per liter	Lbs.	Lbs.	Gal- lons	Per cent	
Eastern hemlock (<i>Tsuga canadensis</i>).	226	5	Jan. 25, 1961	73.4	65.5	36.0	70.0	23.6	46.5	30	100	90	106.2	18.1	6.9	20.4	86.1	
		11	Feb. 10, 1916	88.6	73.0	49.4	67.5	34.3	34.4	50.4	15	110	84	100.0	37.2	16.4	6.2	20.0
		51	June 30, 1916	78.0	68.3	52.0	65.0	37.0	36.8	37.0	15	100	84	82.9	35.2	7.0	24.0	
		52	July 3, 1916	78.0	68.3	52.0	62.5	40.0	35.4	38.1	15	103	35	79.8	41.6	17.3	9.0	25.8
		198	Oct. 29, 1917	70.4	61.4	50.0	49.6	35.0	37.7	35.1	20	98	51	73.3	32.4	6.9	23.8	
Carolina hemlock (<i>Tsuga caroliniana</i>).	822	228	Jan. 10, 1918	62.7	53.7	50.0	80.0	36.5	73.3	20	112	64	90.6	20.5	25.5	27.2	82.0	
		758	May 4, 1921	47.1	40.1	41.0	41.0	36.5	73.3	20	112	64	97.4	24.4	30.1	30.1	87.9	
		759	May 5, 1921	54.8	45.6	45.0	45.0	36.5	73.3	20	112	64	75.0	18.8	6.3	30.0	78.3	
		760	May 6, 1921	25.1	20.9	50.0	65.0	35.0	54.8	20	100	30	60.0	15.0	5.0	30.0	84.9	
		45	June 20, 1916	78.0	64.8	52.0	58.2	37.8	48.7	15	105	33	80.4	37.2	17.1	7.9	23.6	
Western hemlock (<i>Tsuga heterophylla</i>).	325	48	June 26, 1916	82.0	67.2	52.0	58.2	34.4	34.8	15	105	33	74.0	29.9	14.7	6.0	23.8	
		49	June 27, 1916	82.0	66.9	52.0	57.5	40.0	47.0	39.2	15	105	35	78.7	37.6	15.4	7.7	24.5
		108	Dec. 6, 1916	79.3	67.2	51.0	72.8	34.2	63.0	20	105	35	76.7	17.4	5.0	27.3	77.5	
		721	Jan. 14, 1921	58.7	47.0	50.0	70.4	39.2	59.6	20	105	35	80.0	20.1	20.5	5.0	27.3	77.5
		782	June 16, 1921	67.9	59.6	50.0	70.4	49.5	59.6	20	104.0	20.1	104.0	20.1	21.8	25.2	79.8	
Tamarack (<i>Larix laricina</i>).	269E	75	Aug. 15, 1916	84.0	76.0	49.6	68.6	36.2	54.3	20	110	61	99.8	39.6	13.0	5.1	15.6	
		78	Aug. 22, 1916	80.0	70.8	49.6	68.6	36.2	54.3	20	110	80	73.5	46.6	17.0	8.0	20.5	
		84	Sept. 1, 1916	70.4	62.6	49.6	68.6	36.2	54.3	20	110	80	73.5	46.6	17.0	8.0	20.5	
		756	May 13, 1921	80.3	70.5	45.0	67.0	37.8	51.4	20	105.5	24.9	105.5	24.9	18.8	6.2	29.8	
		757	May 13, 1921	85.6	74.5	45.0	67.0	37.8	51.4	20	105.5	24.9	105.5	24.9	18.8	6.2	29.8	
Western larch (<i>Larix occidentalis</i>).	---	16	Mar. 21, 1916	111.0	98.0	45.0	70.0	39.9	50.5	20	100	37	83.0	36.4	13.9	6.1	11.7	
		19	Mar. 24, 1916	96.0	82.8	48.0	70.0	40.0	50.5	38.0	20	100	90	138.0	42.0	13.5	4.1	84.0
		755	Feb. 29, 1921	100.3	87.0	48.0	70.0	39.9	50.5	38.0	20	100	90	81.2	25.1	20.3	6.3	30.0
		276	Sept. 20, 1920	71.2	64.4	47.0	82.4	23.6	23.6	21.8	6.3	31.8	74.9					
		276	Sept. 21, 1920	61.8	55.7	47.0	82.4	23.6	23.6	21.1	15.0	4.4	87.1					
Incense cedar (<i>Libocedrus decurrens</i>).	803	278	Sept. 22, 1920	62.8	57.1	47.0	82.4	23.6	23.6	20	100	90	100.1	21.1	15.0	4.4	87.1	
		278	Sept. 22, 1920	62.8	57.1	47.0	82.4	23.6	23.6	20	100	90	100.1	21.1	15.0	4.4	87.1	
		278	Sept. 22, 1920	62.8	57.1	47.0	82.4	23.6	23.6	20	100	90	100.1	21.1	15.0	4.4	87.1	
		278	Sept. 22, 1920	62.8	57.1	47.0	82.4	23.6	23.6	20	100	90	100.1	21.1	15.0	4.4	87.1	
		278	Sept. 22, 1920	62.8	57.1	47.0	82.4	23.6	23.6	20	100	90	100.1	21.1	15.0	4.4	87.1	

Port Orford cedar (<i>Chamaecyparis lawsoniana</i>).	532	724	Jan. 18, 1921	56.6	49.7	---	---	---	---	---	---	100.1	35.4	25.0	8.8	29.9	85.5
		725	Jan. 20, 1921	43.0	36.6	---	---	---	---	---	---	106.1	25.1	26.5	6.3	30.0	65.6
		726	Jan. 21, 1920	50.5	43.0	---	---	---	---	---	---	103.1	25.1	25.8	6.3	30.0	69.8
Southern white cedar (<i>Chamaecyparis thyoides</i>).	891	897	May 18, 1923	83.6	75.0	---	---	---	---	---	---	93.4	46.8	26.7	12.5	32.2	67.3
		898	May 21, 1923	83.5	75.0	---	---	---	---	---	---	99.9	23.9	13.0	6.0	30.0	63.5
		899	May 23, 1923	74.0	64.6	---	---	---	---	---	---	51.9	23.9	13.0	6.0	30.0	78.0
Eastern red cedar (<i>Juniperus virginiana</i>).	813	288	Oct. 12, 1920	86.0	73.8	---	---	---	---	---	---	75.0	24.9	18.8	6.2	30.0	83.0
		295	Nov. 2, 1920	87.0	74.6	---	---	---	---	---	---	64.9	20.0	18.2	5.0	30.0	83.4
		296	Nov. 3, 1920	87.0	74.6	---	---	---	---	---	---	106.6	20.0	18.2	5.0	30.0	83.4
Western red cedar (<i>Thuja plicata</i>).	812	731	Feb. 21, 1921	56.8	48.9	---	---	---	---	---	---	98.3	25.0	24.4	---	23.8	66.9
		732	Feb. 25, 1921	71.3	60.0	---	---	---	---	---	---	73.0	25.0	18.7	6.3	30.0	71.8
		733	Mar. 10, 1921	65.7	57.4	---	---	---	---	---	---	60.2	20.0	13.0	5.0	23.8	84.7
Southern cypress (<i>Taxodium distichum</i>).	398	214	May 20, 1917	69.6	61.6	---	---	---	---	---	---	70.0	31.5	13.9	6.3	23.8	63.0
		215	Nov. 28, 1917	70.4	61.6	---	---	---	---	---	---	101.1	31.5	20.0	6.3	23.7	73.0
		785	June 22, 1921	81.3	69.2	---	---	---	---	---	---	75.0	25.0	18.8	6.3	30.0	81.2
Redwood (<i>Sequoia sempervirens</i>).	8	25	Apr. 4, 1912	54.6	50.9	---	---	---	---	---	---	89.8	---	25.0	---	33.4	78.7
		180	Sept. 12, 1917	73.0	57.5	---	---	---	---	---	---	52.3	30.1	13.9	8.0	31.9	42.0
		182	Oct. 19, 1917	72.0	60.6	---	---	---	---	---	---	47.2	27.0	12.8	7.3	32.5	96.0
Do.	520	784	June 21, 1921	65.6	59.3	---	---	---	---	---	---	75.0	25.0	18.8	6.3	30.0	76.7
		783	June 20, 1921	168.3	63.0	---	---	---	---	---	---	75.1	25.0	18.8	6.3	30.0	72.4
		783	Sept. 6, 1921	128.0	46.8	---	---	---	---	---	---	58.4	17.4	21.0	6.3	43.0	67.6

¹ Color of bleached pulp below standard.² Chips bleached 72 hours in warm water.

TABLE 13.—Cooking and strength data: Hemlocks and other conifers—Soda or sulphate process—Continued

Cooking data—Continued										Strength data										Conditions during tests	
Species	Shipment No.	Cook No.	Date	Steam			Yields based on oven-dry weight of chips charged		Bleach required (35 per cent available chlorine) per 100 pounds oven-dry pulp	Calendered	Weight per ream 24 by 36—500	Thickness	Mullen test per square inch	Strength factor per pound per ream	Average stretch		Average breaking length	Average double folds	Average Elmendorf tearing test	Relative humidity	Temperature
				Maximum pressure per square inch	Pressure increased	Duration at maximum pressure	Crude pulp	Screenings							Oil per ton bone-dry chips	Lbs.					
Eastern hemlock (<i>Tsuga canadensis</i>).	226	5	Jan. 25, 1916	80	30	180	45.2	0.99	---	No.	46.0	4.9	49.3	1.07	2.51	3.33	7,855	397	---	61	---
		11	Feb. 16, 1916	105	20	120	45.7	4.40	---	Yes	48.0	4.1	44.2	1.92	3.33	3.00	7,755	1,031	---	63	---
		51	June 30, 1916	125	30	85	44.7	1.53	---	No	40.5	4.2	39.3	.97	3.00	3.96	6,180	650	---	64	---
		152	July 3, 1916	100	35	115	45.2	.89	30	No	42.5	4.4	45.9	1.08	3.96	5.925	1,382	1,382	---	64	---
		198	Oct. 29, 1917	100	17	150	51.5	.63	---	No	52.9	6.1	55.0	1.04	3.50	6.290	1,284	1,284	---	75	55
Carolina hemlock (<i>Tsuga caroliniana</i>).	322	228	Jan. 10, 1918	105	30	270	46.0	.14	N. B.	No	43.5	4.2	37.4	.86	3.26	6.390	1,668	---	---	69	55
		758	May 4, 1921	100	90	330	34.1	---	N. B.	No	48.1	4.0	26.6	.64	2.95	4.557	268	243	---	65	86
		759	May 5, 1921	100	75	300	35.0	---	N. B.	No	62.2	6.3	29.5	.64	3.52	5.397	496	243	---	64	76
		760	May 6, 1921	100	60	240	42.1	---	N. B.	Yes	25.5	2.2	14.7	.58	1.79	3.952	113	65	---	65	79
		45	June 20, 1916	80	30	180	48.1	.59	---	No	41.5	3.4	42.8	1.03	4.69	6.255	821	---	---	67	---
Western hemlock (<i>Tsuga heterophylla</i>).	325	49	June 27, 1916	115	45	105	46.6	1.52	---	No	44.5	4.1	43.6	.98	3.69	6.330	1,771	---	---	67	---
		108	Dec. 6, 1916	100	40	150	58.8	9.79	---	Yes	38.0	3.1	36.5	.86	3.27	5.280	2,536	---	---	67	---
		721	Jan. 14, 1921	97	85	270	50.2	.43	---	No	40.5	4.6	21.1	.52	1.89	4.540	253	---	---	66	---
		782	June 16, 1921	103	75	360	40.0	---	N. B.	No	61.4	5.5	51.2	.84	3.84	5.967	602	---	---	65	91
		75	Aug. 15, 1916	85	15	180	48.4	8.10	---	Yes	41.5	4.1	44.0	1.06	4.05	5.680	1,591	---	---	70	---
Tamarack (<i>Larix laricina</i>).	26-E	78	Aug. 22, 1916	95	35	150	45.4	.32	---	No	38.0	4.0	38.4	1.01	3.80	5.340	1,010	---	---	66	---
		84	Sept. 1, 1916	100	20	215	43.2	1.25	---	No	42.5	4.3	37.0	.87	3.05	5.380	1,584	---	---	66	---
		756	May 7, 1921	100	90	360	34.0	---	33	No	44.0	4.2	23.5	.53	1.83	4.283	167	153	---	65	86
		757	May 13, 1921	100	90	315	37.1	---	1 24	No	53.0	6.3	44.5	.84	2.65	5.150	1,369	---	---	67	---
		19	Mar. 21, 1916	80	15	180	52.0	9.07	---	No	43.0	4.1	44.8	1.03	3.43	7,100	916	---	---	65	---
Western larch (<i>Larix occidentalis</i>).	---	755	Feb. 29, 1921	100	75	300	34.1	---	---	No	45.5	3.8	27.0	.59	2.17	4,804	216	---	---	66	78
		276	Sept. 20, 1920	100	105	240	34.9	---	36	No	44.5	3.5	43.5	.98	2.75	7,206	1,215	---	---	66	78
		277	Sept. 21, 1920	100	60	240	44.5	.04	---	No	44.5	3.5	43.5	.98	2.75	7,206	1,215	---	---	64	82
Incense cedar (<i>Libocedrus decurrens</i>).	303	278	Sept. 22, 1920	106	80	300	35.4	---	N. B.	No	44.5	3.5	43.5	.98	2.75	7,206	1,215	---	---	64	82
		278	Sept. 22, 1920	106	80	300	35.4	---	N. B.	No	44.5	3.5	43.5	.98	2.75	7,206	1,215	---	---	64	82

Port Orford cedar (<i>Chamaecyparis lawsoniana</i>).	{332}	722	Jan. 18, 1921	100	75	360	37.2	N. B.											
		724	Jan. 20, 1921	100	65	240	35.1	24											
		725	Jan. 21, 1920	100	45	240	35.8	27											
		897	May 18, 1923	90	100	450	40.0	N. B.											
		898	May 21, 1923	90	100	165	42.0	30											
		899	May 23, 1923	90	100	300	36.5	N. B.											
		900	May 23, 1923	90	100	240	37.7	N. B.											
		988	Oct. 12, 1920	102	45	300	36.5	N. B.	Yes	56.6	6.0	59.7	1.06	3.21	5,822	5,120	184	65	72
		995	Nov. 2, 1920	100	55	240	37.4	N. B.	Yes	55.7	4.2	26.5	.48	1.80	3,370	766	64	75	
		996	Nov. 3, 1920	100	60	360	36.6	N. B.	Yes	55.7	4.2	41.1	.74	2.58	7,698	521	65	70	
Western red cedar (<i>Thuja plicata</i>).	{312}	731	Feb. 21, 1921	101	60	300	33.6	N. B.	Yes	45.5	3.3	40.1	.88	2.71	8,875	616	65	70	
		732	Feb. 25, 1921	103	60	300	43.6	27											
		733	Mar. 20, 1921	100	60	240	43.6	N. B.	Yes	46.0	3.6	34.4	.75	2.60	6,356	1,924	188	85	86
		136	May 29, 1917	100	20	120	51.9	N. B.	No.	47.0	4.6	40.4	.86	3.50	3,300	1,108	85	78	
Southern cypress (<i>Taxodium distichum</i>).	{368}	214	Nov. 28, 1917	100	20	235	51.3	N. B.	No.	45.5	5.0	32.2	.71	2.40	5,110	200	62	68	
		785	Nov. 22, 1921	100	115	300	36.8	30											
Redwood (<i>Sequoia sempervirens</i>).	8	25	Apr. 4, 1912	110	60	480	35.9	N. B.											
		180	Sept. 12, 1917	100	15	270	37.8	20											
		192	Oct. 19, 1917	100	25	435	35.8	07											
		784	June 21, 1921	105	65	300	30.7	N. B.	No.	39.5	3.7	29.1	.96	3.50	6,090	1,220	66	79	
Do.	520	783	June 20, 1921	105	75	300	30.0	N. B.	No.										
		785	June 20, 1921	105	75	300	30.0	35											
		793	Sept. 6, 1921	102	70	300	35.4	N. B.	Yes	47.0	4.3	32.7	.70	2.80	5,104	1,093	66	91	

¹ Chips extracted three times in warm water, soaking 72 hours each time.

TABLE 14.—Cooking and strength data: Hardwoods—Diffuse porous—Sulphite process

Species	Ship-ment No.	Cook No.	Date	Quantity of wood used		Cooking liquor				Cooking period				
				Moist weight	Oven-dry weight	Composition			Per 100 pounds chips	Time to maximum temperature	Duration of cook	Maximum temperature	Maximum pressure per square inch	Gas pressure at blow per square inch
						Total	Free	Combined						
				Pounds	Pounds	Per cent	Per cent	Per cent	Gallons	Per cent	Hours	Hours	Pounds	Pounds
DIFFUSE POROUS														
Aspen (<i>Populus tremuloides</i>)		364	Nov. 26, 1917	59.4	52.2	4.15	3.02	1.13			7.00	7.00	153	14
Balsam poplar (<i>Populus balsamifera</i>)	796	460	Sept. 20, 1920	78.0	53.6	5.23	3.65	1.38	112.0		3.50	8.00	154	10
		462	Sept. 22, 1920	81.8	54.2	4.56	3.56	1.00	107.5		8.00	8.00	153	10
		477	Sept. 23, 1920	86.5	52.2	4.51	3.38	1.13	125.6		3.50	7.00	153	4
Largetooth aspen (<i>Populus grandidentata</i>)		570	Apr. 19, 1921	66.3	57.8	5.21	4.13	1.08	104.3		3.25	8.00	153	10
Norway poplar (<i>Populus canadensis eugenei</i>)	807	499	Nov. 16, 1920	106.2	57.7	5.15	4.05	1.10	109.1		8.00	8.00	153	10
Yellow poplar (<i>Liriodendron tulipifera</i>)	750	426	Mar. 17, 1920	71.0	60.9	5.36	4.23	1.13	113.0	44.5	3.75	7.00	153	4
		477	Mar. 18, 1920	80.7	68.7	4.57	3.50	1.07	82.7	32.6	7.00	4.75	154	2
		585	May 31, 1921	70.1	51.6	5.60	4.37	1.23	117.3		8.00	2.75	153	10
Basswood (<i>Tilia glabra</i>)	501	587	June 2, 1921	64.6	50.6	5.00	3.77	1.23	118.5		8.00	0.00	152	6
		362	Nov. 22, 1919	64.7	56.6	4.27	3.17	1.10	108.0	40.0	6.50	7.00	153	10
Black willow (<i>Salix nigra</i>)	368	481	July 29, 1919	62.6	57.2	4.37	3.29	1.08	87.5		7.00	3.00	154	10
Sandbar willow (<i>Salix longifolia</i>)		492	Nov. 10, 1920	39.0	34.4	5.34	4.17	1.17	119.2		8.00	3.50	153	10
		595	June 15, 1921	86.4	70.0	5.58	4.30	1.28	86.2		8.00	4.50	153	4
Red maple (<i>Acer rubrum</i>)	821	597	June 17, 1921	79.8	64.1	5.55	4.36	1.03	87.0		8.00	3.75	152	6
		514	Jan. 10, 1921	95.0	83.1	5.27	4.24	1.13	87.0		7.00	4.00	148	10
Sugar maple (<i>Acer saccharum</i>)		556	Mar. 22, 1921	79.7	71.2	5.18	4.13	1.05	74.2		8.00	4.75	153	10
		485	Oct. 25, 1920	97.7	83.3	5.42	4.37	1.05	90.2		7.00	2.50	148	4
Paper birch (<i>Betula papyrifera</i>)	794	488	Oct. 26, 1920	109.9	82.0	5.81	3.91	.91	74.8		8.00	4.50	153	10
		367	Nov. 28, 1917	93.7	79.6	4.84	3.74	1.10			8.00	5.50	155	6
Yellow birch (<i>Betula lutea</i>)	500	601	Sept. 22, 1921	115.4	88.0	5.44	4.48	.96	71.9		8.00	4.25	152	10
Black gum (<i>Nyssa sylvatica</i>)	821	577	Apr. 29, 1921	57.9	51.8	5.04	4.12	.92	124.5		7.75	3.00	147	14
		578	May 17, 1921	90.9	78.8	5.45	4.16	1.29	75.8		8.00	2.25	153	10
Tupelo gum (<i>Nyssa aquatica</i>)	814					5.44	4.36	1.08			7.00	4.25	153	4

TABLE 14.—Cooking and strength data: Hardwoods—Diffuse porous—Sulphate process—Continued

Cooking data—Continued				Strength data										Conditions during test			
Species	Ship- ment No.	Cook No.	Date	Yields based on oven-dry weight of chips charged		Bleach avail- able chlorine per 100 pounds oven- dry pulp	Calen- dered 24 x 36— 500	Weight per ream 24 x 36— 500	Thick- ness 0.001 in.	Mullen test per square inch	Strength factor per pound per ream	Average break- ing length	Average double- fold	Average Elmen- dorf tear- ing test	Relative humid- ity	Tem- pera- ture	
				Crude pulp	Screen- ings												
DIFFUSE POROUS																	
Aspen (<i>Populus tremu- loides</i>)		364	Nov. 26, 1917	50.3	Per cent	Pounds	Yes.	51.0	4.6	24.6	0.48	2.07	4,262	28	Grams	Per cent	° F.
		460	Sept. 20, 1920	45.7	0.05	10	Yes.	58.5	5.0	27.4	.47	1.77	4,516	26	73	63	88
Balsam poplar (<i>Populus balsamifera</i>)	796	462	Sept. 22, 1920	47.1	.03	7	Yes.	79.0	5.5	37.2	.47	1.83	4,148	30	88	65	86
		463	Sept. 23, 1920	51.0	.09	6	Yes.	75.5	5.0	39.4	.52	2.33	4,800	63	84	66	83
Largetooth aspen (<i>Populus grandidentata</i>)		570	Apr. 19, 1921	46.7	.90	18	Yes.	66.1	4.7	18.7	.28	1.76	2,808	1	66	75	75
Norway poplar (<i>Populus canadensis eugenei</i>)	807	496	Nov. 16, 1920	48.5	.13	11	Yes.	59.5	4.4	28.3	.48	1.62	4,740	13	65	68	68
		499	Nov. 19, 1920	50.0	.19	16	Yes.	75.5	5.4	31.5	.42	1.44	4,446	6	65	71	71
Yellow poplar (<i>Liriodendron tulipifera</i>)	750	426	Mar. 17, 1920	47.2	.08	20	Yes.	62.3	5.1	14.9	.24	1.65	3,071	14	66	72	72
		427	Mar. 18, 1920	45.4	.60	24	Yes.	55.5	5.0	15.7	.28	1.65	3,614	18	66	74	74
		585	May 31, 1921	46.4	---	2	N.B.	55.7	4.8	15.2	.27	1.61	2,729	6	66	90	90
Basewood (<i>Tilia glabra</i>)	501	587	June 2, 1921	48.4	.71	15	Yes.	52.0	4.1	19.3	.37	2.43	3,710	18	66	94	94
		362	Nov. 22, 1917	57.3	.05	18	Yes.	59.5	5.5	27.1	.46	1.81	4,419	19	61	69	69
Black willow (<i>Salix nigra</i>)	368	378	July 29, 1919	50.8	---	15	Yes.	57.1	4.1	20.0	.35	1.66	3,933	15	68	71	71
Sandbar willow (<i>Salix long- ifolia</i>)		481	Oct. 19, 1920	45.3	.20	7	Yes.	76.5	5.5	25.7	.34	1.42	3,695	5	64	72	72
		492	Nov. 10, 1920	47.8	.36	10	Yes.	85.0	6.5	40.4	.48	1.57	2,952	6	66	93	93
Red maple (<i>Acer rubrum</i>)	821	595	June 15, 1921	48.7	.22	9	Yes.	56.0	4.0	16.5	.30	1.75	2,948	3	66	93	93
Sugar maple (<i>Acer saccha- rum</i>)		597	June 17, 1921	47.9	.94	18	Yes.	65.0	5.2	19.2	.30	1.77	2,948	3	66	93	93
		514	Jan. 10, 1921	44.1	.12	8	Yes.	92.5	7.2	38.0	.41	1.34	4,585	21	65	71	71
Paper birch (<i>Betula papy- rifera</i>)	794	556	Mar. 22, 1921	47.0	.62	18	Yes.	66.0	6.0	32.3	.49	1.96	4,776	23	65	74	74
		485	Oct. 25, 1920	40.6	.30	10	Yes.	89.7	6.9	30.6	.34	1.35	3,208	8	64	76	76
		488	Oct. 29, 1920	49.2	.20	17	Yes.	56.6	4.0	17.5	.31	1.27	3,354	21	64	73	73
Yellow birch (<i>Betulaurea</i>)	500	367	Nov. 28, 1917	47.2	.03	20	Yes.	53.8	5.0	18.7	.35	1.82	3,263	14	68	70	70
		601	Sept. 22, 1921	45.8	.85	16	Yes.	63.2	4.9	20.2	.32	1.71	3,466	7	65	73	73
Black gum (<i>Nyssa sylvat- ica</i>)	821	599	Oct. 19, 1921	45.6	.03	15	Yes.	60.4	5.1	15.6	.26	1.53	2,735	26	65	70	70

Tupelo gum (<i>Nyssa aquatica</i>).	577	Apr. 29, 1921	46.5	.78	22	Yes--	108.5	9.0	22.2	.20	1.38	2,242	8	203	65	85
Red gum (<i>Liquidambar styraciflua</i>).	578	May 17, 1921	43.2	.17	12	Yes--	79.3	6.3	21.8	.28	2.01	3,034	6	138	65	88
Cucumber magnolia (<i>Magnolia acuminata</i>).	317	Dec. 5, 1916	44.6	.42	35	Yes--	70.0	6.9	15.7	.22	1.30	2,840	2	---	62	72
Sweet bay (<i>Magnolia virginiana australis</i>).	363	Nov. 23, 1917	46.7	.06	37	Yes--	52.8	5.3	16.8	.32	1.90	2,900	4	---	64	73
Sycamore (<i>Platanus occidentalis</i>).	380	July 30, 1919	45.8	.03	28	Yes--	68.0	6.2	19.8	.29	1.26	3,048	5	---	63	66
Butternut (<i>Juglans cinerea</i>).	385	Aug. 6, 1919	48.2	.13	25	Yes--	68.0	6.1	18.7	.27	1.64	3,360	6	---	65	71
Ohio Buckeye (<i>Aesculus glabra</i>).	590	June 7, 1921	44.5	.44	15	Yes--	53.0	4.1	14.6	.28	1.92	2,294	4	---	66	86
	592	June 9, 1921	43.1	.37	12	Yes--	54.0	3.9	18.5	.34	2.58	3,170	85	---	66	93
	411	Nov. 29, 1919	46.7	---	11	Yes--	65.1	5.8	10.2	.16	1.27	2,178	2	---	65	69
	563	Apr. 7, 1921	47.2	.47	18	Yes--	68.0	5.7	14.4	.21	1.26	3,159	16	---	66	76
	543	Mar. 1, 1921	46.0	.05	18	Yes--	74.6	5.3	20.1	.27	2.47	2,777	5	---	65	97
	545	Mar. 3, 1921	46.7	.13	18	Yes--	71.0	5.6	23.8	.34	2.06	3,239	6	---	66	72
	606	Oct. 4, 1921	48.9	.72	24	Yes--	67.0	5.1	20.3	.30	1.82	3,646	5	---	64	78
	618	Nov. 16, 1921	(*)	---	24	Yes--	64.1	5.6	31.4	.49	1.58	4,868	15	105	65	69

² Pulp very shivvy.³ Soft, uniformly cooked pulp, light colored and free from shive or specks.⁴ Yield data lost. Probably 45 to 50 per cent.

TABLE 15.—Cooking and strength data: Hardwoods—Diffuse-porous—Soda or sulphate process

Species	Shipment No.	Cook No.	Date	Quantity of wood used		Cooking data											Black liquor ratio combined to total alkali			
						Impregnating liquor						Penetration		Cooking liquor						
				Moist weight	Oven-dry weight	Before penetration			After penetration			Duration	Pressure per square inch	Concentration		NaOH		Na ₂ S	Per 100 pounds bone-dry chips	Volume
						Volume	NaOH	Na ₂ S	Volume	NaOH	Na ₂ S			Grams per liter	NaOH					
				Lbs.	Lbs.	Gal- lons	Grams per liter	NaOH	Na ₂ S	Gal- lons	Grams per liter	NaOH	Na ₂ S	Min- utes	Lbs.	° C.		Grams per liter	NaOH	Grams per liter
DIFFUSE POROUS																				
Aspen (<i>Populus tremuloides</i>)	484	{ 37 38 42	Dec. 28, 1916	76.0	58.7	50.0	75.0		38.2	60.3		20	100	81.2	21.8	32.2	88.4	Per cent		
			Dec. 29, 1916	76.0	59.1	50.0														
			Jan. 9, 1917	60.0	52.9	52.0	56.0		37.2	45.4		20	105	81	20.2	23.4	88.5			
Balsam Poplar (<i>Populus balsamifera</i>)	501	210	Nov. 22, 1917	61.0	53.2	50.1	51.5		39.0	40.9	34.0	20	98	82.2	17.3	29.6	90.5			
			Oct. 1, 1920	90.1	63.2															
			Oct. 4, 1920	77.8	51.2															
Eastern cottonwood (<i>Populus deltoides</i>)	796	{ 282 283																		

821	767	May 25, 1912	71.6	54.5	---	---	---	---	---	78.5	19.6	20.0	5.0	30.6	95.1
Sugar maple (<i>Acer saccharum</i>)	768	May 26, 1921	106.2	82.9	---	---	---	---	---	100.0	---	25.0	---	30.0	91.1
837	769	Oct. 7, 1921	104.2	90.6	---	---	---	---	---	75.0	25.0	18.8	6.3	30.0	95.0
Paper birch (<i>Betula papyrifera</i>)	800	Oct. 10, 1921	103.9	90.5	---	---	---	---	---	100.0	---	25.1	---	30.0	87.8
794	283	Oct. 27, 1920	104.8	90.2	---	---	---	---	---	124.0	---	26.1	---	25.4	85.5
205	284	Nov. 1, 1920	106.3	91.4	---	---	---	---	---	97.3	19.7	24.4	5.0	30.0	82.2
Yellow birch (<i>Betula lutea</i>)	500	Nov. 12, 1917	93.1	80.4	---	---	---	---	---	90.0	31.1	12.4	4.3	16.4	93.0
154	205	July 2, 1917	102.0	82.2	50.0	35.0	38.3	34.3	35.0	80.2	---	20.3	---	30.3	93.0
226	154	Jan. 8, 1918	74.6	63.5	---	---	---	---	---	91.0	---	27.9	---	36.6	75.0
7	226	July 9, 1909	25.0	21.8	---	---	---	---	---	90.0	---	28.2	---	37.2	---
Beech (<i>Fagus grandifolia</i>)	7	Aug. 19, 1909	25.0	22.1	---	---	---	---	---	103.0	---	28.4	---	37.3	---
818	20	Dec. 4, 1920	134.8	79.2	---	---	---	---	---	89.0	11.6	23.7	3.1	32.0	86.2
Black gum (<i>Nyssa sylvatica</i>)	818	Dec. 3, 1920	135.9	76.8	---	---	---	---	---	78.5	20.0	19.6	5.0	30.0	92.4
814	745	Apr. 14, 1921	87.9	75.6	---	---	---	---	---	100.0	---	25.2	---	30.3	92.3
Tupelo gum (<i>Nyssa aquatica</i>)	814	Apr. 18, 1921	85.8	73.6	---	---	---	---	---	103.3	---	28.4	---	33.0	84.5
Red gum (<i>Liquidambar styraciflua</i>)	818	Jan. 25, 1921	153.4	73.8	---	---	---	---	---	87.7	11.3	24.1	3.1	33.0	87.7
39	736	Feb. 4, 1921	142.5	70.6	---	---	---	---	---	79.6	19.9	20.3	5.1	30.6	89.8
801	742	Apr. 11, 1921	122.4	90.8	---	---	---	---	---	74.4	---	20.0	---	32.2	87.0
Cucumber magnolia (<i>Magnolia acuminata</i>)	801	Apr. 17, 1918	71.0	57.4	---	---	---	---	---	80.0	20.0	20.0	5.0	30.0	90.0
511	225	June 3, 1921	74.1	64.5	---	---	---	---	---	100.0	20.0	20.0	5.0	30.0	94.8
Sweet bay (<i>Magnolia virginiana australis</i>)	511	June 6, 1921	102.1	87.2	---	---	---	---	---	80.0	---	20.0	---	30.0	91.3
814	774	June 7, 1921	105.6	92.8	---	---	---	---	---	100.0	---	25.0	---	30.0	---
Sycamore (<i>Platanus occidentalis</i>)	814	June 7, 1921	105.6	92.8	---	---	---	---	---	80.0	---	25.0	---	43.6	---
18	254	Jan. 30, 1920	91.6	81.4	---	---	---	---	---	98.0	---	22.8	---	27.8	99.4
Butternut (<i>Juglans cinerea</i>)	18	Apr. 3, 1921	91.5	80.5	---	---	---	---	---	80.0	20.0	20.0	5.0	30.0	93.0
791	737	Apr. 28, 1921	81.5	64.9	---	---	---	---	---	77.8	---	19.3	---	30.0	94.5
Ohio Buckeye (<i>Aesculus glabra</i>)	791	Mar. 28, 1921	78.4	63.5	---	---	---	---	---	77.8	---	19.3	---	30.0	80.0
863	738	Mar. 29, 1921	78.4	63.5	---	---	---	---	---	73.4	19.7	19.8	4.9	30.0	80.0
Man Grove (<i>Rhizophora mangle</i>)	863	Oct. 3, 1921	110.3	58.5	---	---	---	---	---	73.0	25.0	18.8	6.3	30.0	91.9
751	798	Oct. 6, 1921	108.8	57.0	---	---	---	---	---	100.0	---	25.0	---	30.0	89.4
Oct. 13, 1920	751	Oct. 13, 1920	40.9	35.6	---	---	---	---	---	68.6	17.1	20.0	5.0	35.0	84.7

1 Shavings used.

Cooking data—Continued				Strength data										Conditions during test			
Species	Ship-ment No.	Cook No.	Date	Yields based on oven-dry weight of chips charged		Bleach required (35 per cent available chlorine) per 100 pounds oven-dry pulp	Calen-dered pounds	Weight per ream 24x36—500	Thick-ness	Mullen test per square inch	Strength factor per pound ream	Aver-age stretch	Aver-age break-ing length	Aver-age double-folds	Aver-age Elmen-dorf tearing test	Rela-tive humid-ity	Tem-pera-ture
				Crude pulp	Screen-ings												
				Per cent	Per cent	Pounds	Yes	Pounds	(0.001 in.	Pounds	Points	Per cent	Meters		Grams	Per cent	° F.
RING POROUS		490	Nov. 8, 1920	45.1	0.06	1.36	Yes	73.6	5.4	26.8	0.36	1.75	3.612	6	6	64	75
		495	Nov. 15, 1920	49.7	1.26	2.36	Yes	86.9	6.2	38.9	.45	1.85	4.305	17	17	67	68
	802	388	Aug. 12, 1919	43.8		3.38	Yes	76.5	6.1	13.4	.18	1.64	2.090	2	2	67	82
		508	Apr. 15, 1921	51.4	.29	N. B.	Yes	64.2	4.9	37.0	.58	2.62	5.040	24	24	66	77
		582	May 23, 1921	43.4	.05	12	Yes	55.7	4.1	23.3	.42	1.91	3.175	7	7	65	80
		586	June 1, 1921	36.4		10	Yes	52.9	3.8	19.3	.36	2.42	3.082	7	7	65	82
		607	Oct. 6, 1921	55.6		N. B.	Yes	118.0	3.0	33.2	.28	1.82	3.073	2	2	65	85
		611	Oct. 21, 1921	38.8	29.00	(*)	Yes	94.4	7.6	34.9	.26	1.11	3.041	1	145	66	71
	862	414	Jan. 12, 1920	45.4	.12	17	Yes	61.4	5.9	8.4	.14	.68	1.960	2	106	66	79
		416	Feb. 10, 1920	45.7	.81	12	Yes	68.9	6.1	14.1	.20	1.59	2.752	5	2	65	70
		579	May 18, 1921	44.8	1.80	N. B.	Yes	90.6	7.4	20.7	.23	1.80	2.352	2	131	65	87
		581	May 20, 1921	49.3	3.37	N. B.	Yes	64.2	6.6	16.9	.26	2.04	2.733	2	56	66	79
		365	Nov. 28, 1917	45.3	.07	6	Yes	57.4	5.8	22.4	.39	2.04	3.090	11	11	70	71
		551	Mar. 15, 1921	45.6	1.21	18	Yes	73.6	6.0	19.9	.27	1.69	3.012	8	142	65	78
		366	Dec. 5, 1917	49.7	.40	722	Yes	57.4	6.2	22.1	.39	1.69	3.012	10	142	60	74
		531	Aug. 11, 1919	44.0	.40	724	Yes	53.8	4.5	14.3	.26	1.34	2.903	4	4	66	68
		526	Jan. 28, 1921	45.7	.30	635	Yes	81.0	7.2	11.6	.14	1.26	1.976	1	1	66	70
	531	Apr. 18, 1921	44.2	4.17	630	Yes	66.9	5.8	19.5	.28	3.97	2.794	3	3	66	76	
	560	Mar. 29, 1921	42.0	4.17	618	Yes	74.0	5.7	20.5	.28	1.67	2.591	5	5	66	72	
	564	Apr. 8, 1921	42.3	.89	618	Yes	57.5	4.3	13.5	.24	1.50	2.896	7	7	65	76	
	567	Apr. 14, 1921	49.9	4.68	N. B.	Yes	68.9	5.6	16.4	.24	1.73	2.130	1	1	66	76	
	571	Apr. 20, 1921	49.4	10.80	N. B.	Yes	78.4	7.1	10.5	.14	.91	1.854	1	60	65	82	
MISCELLANEOUS																	
Cabbage palmetto (Sabal palmetto)		573	Apr. 22, 1921	36.0		N. B.	Yes	72.7	7.4	16.6	.23	1.15	2.149	3	3	67	92

¹ Unbleached pulp pink. ² Unbleached pulp specky and pink. ³ Unbleached pulp clear but green. ⁴ Unbleached pulp very dark colored and raw. ⁵ Unbleached pulp dark colored and specky. ⁶ Unbleached pulp dark colored and raw. ⁷ Unbleached pulp of fair color but specky. ⁸ Unbleached pulp dark colored, raw, and brash.

Species	Shipment No.	Cook No.	Date	Cooking data—Continued			Strength data			Conditions during tests	
				Maximum pressure per square inch	Pressure increased	Duration at maximum pressure	Crude pulp	Screenings	Oil per ton bone-dry chips	Bleach required (35 per cent available chlorine) per 100 pounds oven-dry pulp	Calendered
				Lbs.	Min-utes	Min-utes	Per cent	Per cent	Gal-tons	Lbs.	
RING POROUS											
Common catalpa (Catalpa bignonioides).	802	287	Nov. 4, 1920	100	75	300	35.6	---	---	12	---
		298	Nov. 5, 1920	105	60	360	42.9	---	---	18	---
		65	July 28, 1916	120	30	180	37.8	0.02	---	14	---
Chestnut (Castanea dentata).	226	66	July 31, 1916	120	15	165	33.8	.04	---	12	---
		144	June 13, 1917	100	15	240	43.0	.00	---	N. B.	---
Hackberry (Celtis occidentalis).		762	May 17, 1921	102	70	360	32.4	---	---	18	---
		763	May 18, 1921	100	75	300	41.0	---	---	27	---
Sassafras (Sassafras varifolium).	862	801	Oct. 11, 1921	105	60	360	40.4	---	---	N. B.	---
		802	Oct. 12, 1921	100	60	300	29.0	---	---	26	---
Rock elm (Ulmus racemosa).	564	252	Jan. 26, 1920	82	105	480	45.3	---	---	20	---
		281	Sept. 30, 1920	105	90	285	45.5	---	---	21	---
Slippery elm (Ulmus fulva).	7	764	May 19, 1921	50	60	900	41.6	---	---	24	---
		765	May 23, 1921	100	60	360	33.2	---	---	27	---
American elm (Ulmus americana).		786	June 23, 1921	100	70	300	39.3	---	---	18	---
		787	June 24, 1921	102	60	360	40.3	---	---	27	---
White ash (Fraxinus americana).	505	255	Feb. 9, 1920	92	75	345	41.2	---	---	24	---
		788	June 27, 1921	100	75	300	38.9	---	---	20	---
Red oak (Quercus borealis maxima).	531	794	Sept. 29, 1921	100	60	300	38.4	.03	---	24	---
		211	Nov. 23, 1917	80	25	215	58.7	---	---	38	---
White oak (Quercus alba).	531	227	Jan. 9, 1918	95	25	310	34.8	.03	---	---	---
		795	Sept. 30, 1921	100	70	300	43.6	---	---	---	---
Mockernut hickory (Hicoria alba).	791	739	Apr. 6, 1921	102	45	300	29.8	---	---	30	---
		740	Apr. 7, 1921	100	60	360	36.4	---	---	N. B.	---
Black locust (Robinia pseudo-acacia).	822	752	Apr. 26, 1921	100	75	360	41.2	---	---	N. B.	---
		753	Apr. 27, 1921	87	70	330	44.2	---	---	N. B.	---
Alanthus (Alanthus altissima).	968	2042	Mar. 3, 1924	100	120	240	48.0	---	---	6	---
		2047	Apr. 1, 1924	100	90	270	50.4	---	---	8	---

1 Extracted chips retained on screen.

2 Extracted chips unscreened.

3 Unextracted chips.

Cooking data—Continued										Strength data																																				
Species	Shipment No.	Cook No.	Date	Steam			Yields based on oven-dry weight of chips charged			Bleach required (35 per cent available chlorine) per 100 pounds oven-dry pulp	Calendered	Weight per ream 24 x 36-500	Thickness	Mullen test per square inch	Strength factor per pound per ream	Average stretch	Average breaking length	Average double folds	Average Elmendorf tearing test	Condi- tions dur- ing tests																										
				Maximum pres- sure per square inch	Pressure increased	Min- utes	Duration at maxi- mum pressure	Crude pulp	Screenings											Oil per ton bone- dry chips	Per cent	Gal- lons	Per cent	Points	Meters	Gms.	Relative humidity	Temperature																		
MISCELLANEOUS	213	{ 3 3 754 789	{ Oct. 31, 1912 Nov. 6, 1912 Nov. 4, 1912 Apr. 25, 1921 Apr. 28, 1921	{ 50 50 80 102 102	{ 60 45 315 240 240	{ 300 300 315 360 360	{ 40.2 39.2 24.9 35.4 32.0	{ 40.2 39.2 24.9 35.4 32.0	{ 33 33 33 33 33	{ No. No. No. No. No.	{ 52.0 79.0 7.7 26.7 26.7	{ 5.2 7.7 7.7 7.7 7.7	{ 16.1 26.7 26.7 26.7 26.7	{ 0.31 0.34 0.34 0.34 0.34	{ 1.60 2.06 2.06 2.06 2.06	{ 3,221 3,268 3,268 3,268 3,268	{ 9 19 19 19 19	{ 66 66 66 66 66	{ 92 92 92 92 92																											
CHILEAN WOODS	711	{ 5 7	{ Feb. 16, 1909 Feb. 24, 1909	{ 100 100	{ 30 15	{ 120 540	{ 360 420	{ 42.1 33.2	{ 0.06 0.00	{ 18 15	{ 33 33	{ 42.0 42.0	{ 4.4 4.4	{ 23.0 23.0	{ 0.55 0.55	{ 2.35 2.35	{ 5,290 5,290	{ 78 78																												
Olivillo Laurel (Laurelia aromatica) (Cogue (Nothofagus dombeyl) Lingue (Persca lingue) Roble-pellin (Nothofagus ob- liqua) Quillai (Quillaja saponaria)		{ 13 14 15 16	{ Mar. 23, 1915 Mar. 24, 1915 Mar. 25, 1915 Mar. 26, 1915	{ 100 100 100 100	{ 90 90 360 60	{ 330 330 42.0 390	{ 38.8 40.3 42.0 41.0	{ 0.03 0.03 0.06 0.05	{ 40 32 18	{ No. 32 18	{ 42.0 42.0 4.4 23.0	{ 4.4 4.4 0.06 0.05	{ 23.0 23.0 0.55 2.35	{ 0.55 0.55 0.34 0.34	{ 2.35 2.35 3.268 3.268	{ 5,290 5,290 3,268 3,268	{ 78 78 19 19																													

1 Only bark used.

2 Leaves.

3 Stalks.

4 Bleached and run with 25 per cent bleached spruce sulphite into excellent book paper.

6 Excellent pulp.

6 Bleaching action slower than usual.

7 Unbleached pulp light colored and of good average fiber length.

ORGANIZATION OF THE UNITED STATES DEPARTMENT OF AGRICULTURE

April 25, 1927

<i>Secretary of Agriculture</i>	W. M. JARDINE.
<i>Assistant Secretary</i>	R. W. DUNLAP.
<i>Director of Scientific Work</i>	A. F. WOODS.
<i>Director of Regulatory Work</i>	WALTER G. CAMPBELL.
<i>Director of Extension Work</i>	C. W. WARBURTON.
<i>Director of Information</i>	NELSON ANTRIM CRAWFORD.
<i>Director of Personnel and Business Admin- istration</i>	W. W. STOCKBERGER
<i>Solicitor</i>	R. W. WILLIAMS.
<i>Weather Bureau</i>	CHARLES F. MARVIN, <i>Chief</i> .
<i>Bureau of Agricultural Economics</i>	LLOYD S. TENNY, <i>Chief</i> .
<i>Bureau of Animal Industry</i>	JOHN R. MOHLER, <i>Chief</i> .
<i>Bureau of Plant Industry</i>	WILLIAM A. TAYLOR, <i>Chief</i> .
<i>Forest Service</i>	W. B. GREELEY, <i>Chief</i> .
<i>Bureau of Chemistry</i>	C. A. BROWNE, <i>Chief</i> .
<i>Bureau of Soils</i>	MILTON WHITNEY, <i>Chief</i> .
<i>Bureau of Entomology</i>	L. O. HOWARD, <i>Chief</i> .
<i>Bureau of Biological Survey</i>	E. W. NELSON, <i>Chief</i> .
<i>Bureau of Public Roads</i>	THOMAS H. MACDONALD, <i>Chief</i> .
<i>Bureau of Home Economics</i>	LOUISE STANLEY, <i>Chief</i> .
<i>Bureau of Dairy Industry</i>	C. W. LARSON, <i>Chief</i> .
<i>Fixed Nitrogen Research Laboratory</i>	F. G. COTTREL, <i>Director</i> .
<i>Office of Experiment Stations</i>	E. W. ALLEN, <i>Chief</i> .
<i>Office of Cooperative Extension Work</i>	C. B. SMITH, <i>Chief</i> .
<i>Library</i>	CLARIBEL R. BARNETT, <i>Librarian</i> .
<i>Federal Horticultural Board</i>	C. L. MARLATT, <i>Chairman</i> .
<i>Insecticide and Fungicide Board</i>	J. K. HAYWOOD, <i>Chairman</i> .
<i>Packers and Stockyards Administration</i>	JOHN T. CAINE III, <i>in Charge</i> .
<i>Grain Futures Administration</i>	J. W. T. DUVEL, <i>in Charge</i> .

This bulletin is a contribution from

<i>Forest Service</i>	W. B. GREELEY, <i>Chief</i> .
<i>Branch of Research</i>	EARLE H. CLAPP, <i>Assistant, For- ester, in Charge</i> .
<i>Forest Products Laboratory</i>	CARLILE P. WINSLOW, <i>Director</i> .
<i>Section of Pulp and Paper</i>	J. D. RUE, <i>in Charge</i> .

ADDITIONAL COPIES
OF THIS PUBLICATION MAY BE PROCURED FROM
THE SUPERINTENDENT OF DOCUMENTS
GOVERNMENT PRINTING OFFICE
WASHINGTON, D. C.
AT
20 CENTS PER COPY