A 13-2714 1980
1980

INFORMATION LEAFLET
FOREIGN WOODS

Forest Products Laboratory,¹ Forest Service
U. S. Department of Agriculture
1954

ROBLE BLANCO, AMAPA, MAYFLOWER
Tabebuia pentaphylla (L.) Hemsl.
Family: Bignoniaceae

By

JEANNETTE M. KRYN, Forest Products Technologist
Division of Silvicultural Relations

Distribution and Habitat

The genus Tabebuia is widely distributed throughout tropical America. It is divided into three main groups of trees: Roble (a Spanish name for oak), "White Cedar," and Lapacho. Each group is represented by species with distinct wood characteristics. The Roble group, discussed in this report, includes several species, but the best known is Tabebuia pentaphylla. The wood bears a superficial resemblance to oak, but it lacks the large rays. This species is quite common in Mexico, Central America, Ecuador, Colombia, Venezuela, and the West Indies. It grows in various habitats, from wet lowlands to dry mountainsides (4, 13, 15, 20, 21).²

¹Maintained at Madison, Wis., in cooperation with the University of Wisconsin.

²Underlined numbers in parentheses refer to the list of numbered references at the end of the report.

Other Common Names

Roble blanco is also known by the following names (4, 9, 21, 23, 26):

Amapa rosa	- Mexico	Maqueliz	- Guatemala, Honduras
Amapola	- Mexico	Maquil	- Mexico
Apamate	- Venezuela	Matilisquate	- Guatemala, Honduras
Guayacán	- Costa Rica	Orumo	- Venezuela
Hokab	- Mexico	Palo de rosa	- Mexico
Macuelizo	- Honduras	Palo yugo	- Mexico
Macuil	- Mexico	Pink poui	- Trinidad
Macuilés	- Salvador	Poirier	- Martinique
Macuilixuatl	- Mexico	Roble de sabana	- Costa Rica
Maculigua	- Salvador	Roble del río	- Colombia
Maculiz	- Mexico	Roble morado	- Colombia
Mano de león	- Guatemala, Honduras	Rosa morado	- Mexico

The Tree

Size

Roble blanco may reach a height of 95 feet and a diameter of 2 feet or more. Buttresses often extend from 7 to 10 feet up the trunk. Clear boles 20 to 35 and occasionally to 50 feet above the buttresses may occur (3, 4, 15, 17, 21, 22, 23).

Bark

The grayish bark is rough and scaly near the base of the tree, but it is smooth higher up (11, 19, 21).

Leaves

The leaves have five leaflets and are in pairs along the stem and clustered near the ends of the branches. The tree is deciduous (19, 23).

Flowers and Fruit

The flowers are showy, ranging in color from white to deep pink, and the tree is valued for ornamental planting. The fruits are long, slender pods with winged seeds (8, 11, 12, 15, 23, 24, 30).

The Wood

Color

The heartwood is light brown with either a grayish or somewhat golden hue. Fine lines of deep brown form a conspicuous pattern, especially on the tangential surface. The sapwood is yellowish to white when freshly cut, becoming light brown after drying and exposure, and not very distinct from the heartwood (4, 6, 9, 10, 12, 18, 21, 27).

Texture, Grain, Figure

Roble blanco has a medium to rather coarse texture. The grain may be interlocked, showing a ribbon-stripe figure on the radial or quartersawn surface of the wood, or it may be straight. The tangential or flatsawn surface often shows a distinctive figure of fine brown lines, caused by the abundant parenchyma that contains dark, gummy material (4, 9, 10, 21, 25, 31).

Luster

The luster is low to medium (21).

Odor and Taste

The wood is odorless and tasteless when dry (4, 11).

Weight

Roble blanco is rated moderately heavy to heavy (4, 9, 21), with an average specific gravity of 0.52 (0.44 to 0.63) based on weight when oven-dry and volume when green. It averages about 55 pounds per cubic foot when green and 38 pounds when air-dry (4).

Mechanical Properties:

Values obtained for the mechanical properties of roble blanco in the green and air-dry condition are given in table 1. Values for white ash (Fraxinus americana) and white oak (Quercus alba) are included for comparison (32).

Seasoning and Shrinkage

Roble blanco is rated easy to season. Slight checking and warping may occur with rapid drying, but these defects can be minimized by slower drying (32). Kiln schedule 4 of the British Forest Products Research Laboratory has been

recommended (1). The U. S. Forest Products Laboratory schedule that appears most appropriate for 4/4 stock is T4-D2 (28). Shrinkage data for roble blanco are given in table 2.

When tested at Yale University, roble blanco showed only fair weathering characteristics. Exposed, unpainted wood remained free from warp but developed surface roughness and considerable checking. The heartwood readily absorbs moisture (32).

Durability

The heartwood of roble blanco is variable in its resistance to decay. It is given an average rating of "moderately durable" in resistance to a white-rot fungus (*Polyporus versicolor*) and "very durable" in its resistance to a brown-rot fungus (*Poria monticola*) (32). It is rated low in resistance to insect attack by Dickinson, et al (4), but a report by the Forest Department of British Honduras indicates that resistance to fungal and insect attack is moderately high (11).

Working Characteristics

Roble blanco is very easy to work with both hand and machine tools and takes a smooth finish. It holds its place well when manufactured. It has good nailholding characteristics, but it is advisable to prebore the nail holes in thick stock. The wood finishes attractively in natural color and takes stains with good results (4, 5, 21, 27).

Uses

The wood is used locally for ox yokes, house construction, boat building, piling, carpentry, interior finish and flooring, wagons, and packing boxes (2, 4, 21, 24, 29, 33). The future demand for the wood in this country will probably be for uses for which it is now best known, namely furniture, millwork, flooring, and general construction (4).

Structure

Growth rings may be distinct to indistinct. They are delimited by an increase in fiber density and fine lines of terminal parenchyma. Vessels are distinct without magnification and appear on quartersawn or flatsawn surfaces as coarse brown grooves. Parenchyma is terminal, wing-like about the pores, and confluent. Ripple marks are distinct and regular (7, 9, 11, 16).

References

- (1) BRITISH FOREST PRODUCTS RESEARCH LABORATORY
1952. KILN-DRYING SCHEDULES. Dept. of Sci. and Indus. Res.
Leaflet No. 42, Revised. Princes Risborough, Aylesbury,
Bucks, England.
- (2) CUMMINGS, LEWIS A.
1929. THE FORESTS OF VENEZUELA. Yale Univ. School Forestry,
Trop. Woods No. 18, pp. 38-39, New Haven, Conn.
- (3) CURRAN, HUGH M.
1929. THE LANDS OF LOBA, COLOMBIA. Yale Univ. School Forestry,
Trop. Woods No. 19, pp. 15, 19, New Haven, Conn.
- (4) DICKINSON, FRED. E., HESS, R. W., AND WANGAARD, F. F.
1949. PROPERTIES AND USES OF TROPICAL WOODS, I. Yale Univ.
School Forestry, Trop. Woods No. 95, pp. 112-116,
New Haven, Conn.
- (5) FRITZ, EMANUEL
1926. "AMAPA" FOR INTERIOR TRIM AND FLOORING. Yale Univ.
School Forestry, Trop. Woods No. 8, pp. 8-9,
New Haven, Conn.
- (6) HOLDRIDGE, L. R., TEESDALE, L. V., MEYER, J. E., LITTLE E., JR.,
HORN, E. F., AND MARRERO, JOSE
1947. THE FORESTS OF WESTERN AND CENTRAL ECUADOR. Pp. 67, 71.
The U. S. Forest Serv., Washington, D. C.
- (7) JOHNSTON, D. R.
1952. THE ANATOMY OF SOME SPECIES OF TABEBUIA. Timber News,
Vol. 60, pp. 337-338.
- (8) KLUGE, H. C., AND RECORD, S. J.
1926. TREES OF THE BAYANO RIVER WATERSHED, PANAMA. Yale Univ.
School Forestry, Trop. Woods No. 5, p. 5, New Haven, Conn.
- (9) KRIEBS, DAVID A.
1950. COMMERCIAL FOREIGN WOODS ON THE AMERICAN MARKET. P. 58.
Trop. Woods Lab, Pennsylvania State College, State
College, Pa.
- (10) KYNOCH, WILLIAM, AND NORTON, NEWELL
1938. MECHANICAL PROPERTIES OF CERTAIN TROPICAL WOODS, CHIEFLY
FROM SOUTH AMERICA. Michigan School Forestry and
Conserva. Bull. No. 7, 87 pp., Ann Arbor, Mich.
- (11) LAMB, A. F. A.
1946. NOTES ON FORTY-TWO SECONDARY HARDWOOD TIMBERS OF BRITISH
HONDURAS. Brit. Honduras Forest Dept. Bull. No. 1,
pp. 60-62, Belize.

- (12) LAMB, GEORGE N.
1948. FOREIGN WOODS: MAYFLOWER (Tabebuia pentaphylla).
Wood Prod. Vol. 53, No. 7, p. 24, Chicago.
- (13) LUNDELL, C. L.
1937. THE VEGETATION OF PETEN. Carnegie Inst. Pub. No. 478,
244 pp., Washington, D. C.
- (14) MARKWARDT, L. J. and WILSON, T. R. C.
1935. STRENGTH AND RELATED PROPERTIES OF WOODS GROWN IN THE
UNITED STATES. U. S. Dept. Agr., Tech. Bull. 479,
99 pp., Washington, D. C.
- (15) MERKER, C. A., BARBOUR, W. R., SCHOLTEN, J. A., and DAYTON, W. A.
1943. THE FORESTS OF COSTA RICA. Pp. 67, 71. U. S. Forest Serv.,
Washington, D. C.
- (16) METCALFE, C. R. and CHALK, L.
1950. ANATOMY OF THE DICOTYLEDONS. Pp. 1002-1013. England.
- (17) PITTIER, H.
1926. MANUAL DE LAS PLANTAS USUALES DE VENEZUELA. 458 pp.
Litographia del Comercia, Caracas, Venezuela.
- (18) RECORD, SAMUEL J.
1927. TREES OF HONDURAS. Yale Univ. School Forestry, Trop. Woods,
No. 10, pp. 14-15, 46, New Haven, Conn.
- (19) _____
1929. TREES AND SHRUBS COLLECTED BY F. C. ENGLESING IN NORTH-
EASTERN NICARAGUA. Yale Univ. School Forestry, Trop. Woods,
No. 17, p. 22, New Haven, Conn.
- (20) _____ and HESS, R.
1940. AMERICAN TIMBERS OF THE FAMILY BIGNONIACEAE. Yale Univ.
School Forestry, Trop. Woods, No. 63, pp. 24-25, New
Haven, Conn.
- (21) _____
1943. TIMBERS OF THE NEW WORLD. Pp. 83-89. Yale Univ. Press.,
New Haven, Conn.
- (22) _____ and KUYLEN, H.
1926. TREES OF THE LOWER RIO MOTAGUA VALLEY, GUATEMALA.
Yale Univ. School Forestry, Trop. Woods, No. 7, pp. 11,
13-14, 28, New Haven, Conn.
- (23) STANDLEY, P. C.
1926. TREES AND SHRUBS OF MEXICO. Contrib. U. S. Natl. Herbarium
Vol. 23, Part 5, pp. 1320-1321, Washington, D. C.

- (24) STANDLEY, P. C.
1928. FLORA OF THE PANAMA CANAL ZONE. Contrib. U. S. Natl.
Herbarium Vol. 27, p. 343, Washington, D. C.
- (25) _____
1931. FLORA OF THE LACETILLA VALLEY, HONDURAS. Field Mus. Nat.
Hist., Bot. Ser., Vol. 10, pp. 356-357, Chicago.
- (26) _____
1937-38. FLORA OF COSTA RICA. Field Mus. Nat. Hist., Bot. Ser. 18,
Part 3, pp. 1129-1130, Chicago.
- (27) _____ and RECORD, S. J.
1936. THE FORESTS AND FLORA OF BRITISH HONDURAS. Field Mus.
Nat. Hist., Bot. Ser. Vol. 12, pp. 363-364, Chicago.
- (28) TORGESON, O. W.
1951. SCHEDULES FOR THE KILN DRYING OF WOOD. U. S. Forest
Products Lab. Rept. D1791, 9 pp., Madison, Wis.
- (29) WADSWORTH, FRANK H.
1943. ROBLE, A VALUABLE FOREST TREE IN PUERTO RICO. Caribbean
Forester, Vol. 4, No. 2, pp. 59-76.
- (30) _____
1944. TABEBUIA PALLIDA and TABEBUIA PENTAPHYLIA. Caribbean
Forester, Vol. 5, No. 2, p. 99.
- (31) WANGAARD, F. F.
1949. TROPICAL WOOD RESEARCH. Furn. Manuf., Vol. 64, No. 8,
pp. 50-54, 56.
- (32) _____ and MUSCHLER, A. F.
1952. PROPERTIES AND USES OF TROPICAL WOODS, III. Yale Univ.
School Forestry, Trop. Woods, No. 98, pp. 159-163, New
Haven, Conn.
- (33) WILLIAMS, L. _____ Venezuela
1939. MADERAS ECONOMICAS DE VENEZUELA. /Min. de Agr. Y Cria.,
Bol. No. 2, pp. 89-90, Caracas.

Table 1.--Mechanical properties of roble blanco (Tabebuia pentaphylla),
white oak (Quercus alba), and white ash (Fraxinus americana)¹

Property	Species ²		
	Roble blanco: (<u>Tabebuia</u> <u>pentaphylla</u>)	White oak: (<u>Quercus</u> <u>alba</u>)	White ash: (<u>Fraxinus</u> <u>americana</u>)
Moisture content			
Green... percent:	68.2	68	42
Air-dry ³ ... percent:	13.5	12	12
Specific gravity			
Based on green volume and oven-dry weight...	0.52	0.60	0.55
Based on volume and weight when oven-dry...	0.57	0.71	0.64
Static bending			
Fiber stress at proportional limit			
Green... p.s.i.	6,600	4,700	5,100
Air-dry ³ ... p.s.i.	9,480	8,200	8,900
Modulus of rupture			
Green... p.s.i.	10,770	8,300	9,600
Air-dry ³ ... p.s.i.	13,780	15,200	15,400
Modulus of elasticity			
Green... 1,000 p.s.i.	1,450	1,250	1,460
Air-dry ³ ... 1,000 p.s.i.	1,600	1,780	1,770
Work to proportional limit			
Green... in.-lb. per cu. in.	1.66	1.08	1.04
Air-dry ³ ... in.-lb. per cu. in.	3.18	2.27	2.60
Work to maximum load			
Green... in.-lb. per cu. in.	11.7	11.6	16.6
Air-dry ³ ... in.-lb. per cu. in.	12.5	14.8	17.6
Compression parallel to grain			
Fiber stress at proportional limit			
Green... p.s.i.	4,040	3,090	3,190
Air-dry ³ ... p.s.i.	5,890	4,760	5,790
Maximum crushing strength			
Green... p.s.i.	4,910	3,560	3,990
Air-dry ³ ... p.s.i.	7,340	7,440	7,410
Modulus of elasticity			
Green... 1,000 p.s.i.	1,510		
Air-dry ³ ... 1,000 p.s.i.	1,740		
Hardness ⁴			
Green - end... lb.	1,030	1,120	1,010
Green - side... lb.	910	1,060	960
Air-dry ³ - end... lb.	1,310	1,520	1,720
Air-dry ³ - side... lb.	*960	1,360	1,320

Table 1.--Mechanical properties of roble blanco (Tabebuia pentaphylla), white oak (Quercus alba), and white ash (Fraxinus americana)¹ (continued)

Property	Species ²		
	Roble blanco: (<u>Tabebuia</u> <u>pentaphylla</u>)	White oak: (<u>Quercus</u> <u>alba</u>)	White ash: (<u>Fraxinus</u> <u>americana</u>)
Compression perpendicular to the grain			
Stress at proportional limit			
Green...p.s.i.	790	830	810
Air-dry ³ ...p.s.i.	940	1,320	1,410
Tension perpendicular to grain			
Green...p.s.i.	790	770	590
Air-dry ³ ...p.s.i.	*560	800	940
Shear			
Green...p.s.i.	1,250	1,250	1,380
Air-dry ³ ...p.s.i.	1,450	2,000	1,950
Cleavage			
Green...lb. per in. of width	380	420	330
Air-dry ³ ...lb. per in. of width	*270	450	480
Toughness ⁵ ...in.-lb. per specimen	147.0	614.9	

¹This table shows results of tests on roble blanco made by the Yale School of Forestry in cooperation with the Office of Naval Research and the Bureau of Ships, U. S. Navy Dept. Average strength values for all logs are presented (32). The results of tests on white oak and white ash, cited in the same Yale report, were taken from U. S. Dept. Agriculture Tech. Bull. 479 (14). Strength values for roble blanco from Venezuela are not included in this table, but have been determined on limited material at a different moisture content by Kynoch and Norton (10).

²Source and number of logs: Roble blanco, British Honduras, 3 logs, Honduras, 3 logs, and Panama, 3 logs; white oak, United States, 20 logs; white ash, United States, 23 logs.

³Air-dry values adjusted to 12 percent moisture content except where designated (*), in which case the actual moisture content at time of testing (see Moisture Content in table) applies.

⁴The load in pounds required to embed a 0.444-inch steel ball to half its diameter.

⁵Toughness values are the average of tests of green and air-dry specimens 5/8 by 5/8 by 10 inches loaded on the tangential face over an 8-inch span.

⁶Value obtained for plank material received from the New York Naval Shipyard.

Table 2.--Shrinkage values for roble blanco (Tabebuia pentaphylla)¹

Species and source	Shrinkage ²			
	Radial	Tangential	Longitudinal	Volumetric
	Percent	Percent	Percent	Percent
Roble blanco (<u>Tabebuia pentaphylla</u>)				
Panama.....	3.6	6.2	0.09	10.4
British Honduras.....	3.6	6.1	.18	8.7
Honduras.....	3.7	5.9	.15	9.5
Average (Panama, Brit. Honduras, Honduras).....	3.6	6.1	.14	9.5
Venezuela.....	2.6	5.9		9.3

¹This table shows results of tests on roble blanco made by the Yale School of Forestry in cooperation with the Office of Naval Research and the Bureau of Ships, U. S. Navy Department (4, 32). The results of tests on material from Venezuela were taken from the report of Kynoch and Norton (10).

²Shrinkage values represent shrinkage from the green to the oven-dry condition expressed as a percentage of the green dimension.